



INSPECTION CERTIFICATE

PANTECH STEEL INDUSTRIES SDN. BHD. (509731-A)

LOT 13258 & 13259, Jalan Haji Abd. Manan,

Off Jalan Meru, 42200 Kapar, Selangor, Malaysia.

Tel: 603-3393 1633 Fax: 603-3393 1733 E-mail: info@pantechsteel.com



Quality Management System is certified under ISO 9001. Approval. No.: 0047996
PED 2014/68/EU Annex 1 Clause 4.3
Cert. No.: 0343/PED/MUM/0810070/1

WROUGHT CARBON STEEL BUTTWELDING FITTINGS

INSPECTION DOCUMENT: EN10204:2004 Type 3.1

Certificate No : PSI 139408-01

Date : 24-Oct-2023

Purchaser :

Order No.	Invoice No.	Starting Material	Specification for Fittings- Seamless										Specification for Inspection					
72319-2	E000018114	Seamless Pipe	ASTM A234 -23 WPB / ASME SA234 -23 WPB NACE MR0103-15/ NACE MR0175/ISO15156-15*										ASME B16.9 - 18 / ASTM A960 - 23					
Batch No.	Heat No. Pipe	Product & Size	Quantity (pcs)		Visual Examination		Dimensional Inspection		Heat Treatment		Magnetic Particle Testing							
B5707	23C208192	4" 90 DEG LR STD ELBOW	272		GOOD		GOOD		H		N.A							
B4823MT	13320968	3" XS TEE	200		GOOD		GOOD		C & S		GOOD							
B1324C	M47912	6" x 4" XS CON RED	200		GOOD		GOOD		C & S		N.A							
B4212	13320967	4" 90 DEG LR XS ELBOW	200		GOOD		GOOD		H		N.A							
B4310C	23303113	10" x 8" STD CON RED	120		GOOD		GOOD		C & S		N.A							
Specification		Chemical Composition (%)											Tensile Test ¹			Hardness		
		C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Pb	CE	YS	TS	E ²	(HB)	
		x100	x100	x100	x1000	x1000	x100	x100	x100	x100	x1000		x100	(KSI / MPa)	(%)	1	2	
Min	-	10	29	-	-	-	-	-	-	-	-	-	240	415	-	-	-	
Max	-	10	29	-	-	-	-	-	-	-	-	-	240	415	-	-	-	
Batch No.	30	-	106	50	58	40	40	15	40	80	-	50	-	-	-	197		
B5707	20	22	44	17	5	2	3	0	1	2	< 0.10	28	405	534	32.6	126	131	
B4823MT	13	17	74	13	6	0	7	2	3	3	< 0.10	27	323	466	34.6	131	137	
B1324C	13	21	102	25	8	2	1	0	1	35	< 0.10	31	343	457	35.6	131	136	
B4212	13	16	75	12	4	0	5	1	3	3	< 0.10	27	341	443	37.8	126	134	
B4310C	22	20	56	19	9	0	10	2	4	6	< 0.10	34	332	465	35.6	132	139	

WE CERTIFY THAT ALL PRODUCTS WERE MANUFACTURED, SAMPLED, TESTED, AND INSPECTED SOLELY BY THE MANUFACTURER LISTED AT THE ADDRESS ABOVE IN ACCORDANCE WITH INDICATED SPECIFICATION AND FOUND TO MEET REQUIREMENTS. MATERIAL IS FREE FROM MERCURY AND RADIOACTIVE CONTAMINATION.

TENSILE REQUIREMENT: CONFORMS TO ASTM A370 STANDARD, LONGITUDINAL DIRECTION, GAUGE LENGTH 2" (50mm)

* FULLY KILLED

* HARDNESS ACCORDING TO NACE MR0103/ NACE MR0175/ISO15156

NOTE:

C: Cold formed at temperature below 620°C

S: Stress relieved in temperature between 595°C - 690°C and cooled in still air.

H: Hot formed in temperature between 620°C - 980°C and cooled in still air.

MT: Magnetic Particle Testing

N: Normalised at 910°C

Q: Heated to 910°C and quench in water.

T: Temper between 590°C - 690°C.

*1: YS = Yield strength TS=Tensile strength E = Elongation

*2: For thickness above 7.94 mm, the minimum elongation value, E is 30. Else, E = 48t + 15, where t = specimen thickness, in

Manufactured in Malaysia



Quality Assurance Manager