



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

WELDBEND CORPORATION
P O BOX 945650
MAITLAND, FL
PO: S014201970

<u>Quantity</u>		<u>Product</u>								<u>Heat Code</u>				<u>Heat Treatment</u>				<u>Steel Mill</u>			
51		4" Class 900 Weld Neck XSB RF								JF2				Heat Treat: Normalized				CMC STEEL			
<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>	<u>Al</u>	<u>Ti</u>	<u>B</u>	<u>Cb</u>	<u>CE (IIW)</u>	<u>Tens.</u>	<u>Yield</u>	<u>Elong</u>	<u>ROA</u>	<u>BHN</u>	<u>BHN2</u>	A 105-23 Dimensional Specification: B16.5
L 0.20	1.05	0.008	0.019	0.20	0.35	0.09	0.05	0.024	0.00	0.000	0.001	0.0006	0.001	0.419	79,100	47,300	31.20	58.00	152	152	A 105

8		4" XS Straight Tee								25N46					Heat Treat: Normalized								NIPPON		
	<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>	<u>Al</u>	<u>Ti</u>	<u>B</u>	<u>Cb</u>	<u>CE (IIW)</u>	<u>Tens.</u>	<u>Yield</u>	<u>Elong</u>	<u>ROA</u>	<u>BHN</u>	<u>BHN2</u>	A 234-18 WPB Dimensional Specification: B16.9			
L	0.11	1.30	0.011	0.002	0.27	0.02	0.03	0.12	0.010	0.00	0.030	0.010	0.0001	0.000	0.356	70,100	50,000†	34.40	-	153	152	WPB			

18		4" x 2" XS Reducing Tee								19N78		Heat Treat: Normalized										NIPPON		
	<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>	<u>Al</u>	<u>Ti</u>	<u>B</u>	<u>Cb</u>	<u>CE (IIW)</u>	<u>Tens.</u>	<u>Yield</u>	<u>Elong</u>	<u>ROA</u>	<u>BHN</u>	<u>BHN2</u>	A 234 WPB-13		
L	0.11	1.28	0.018	0.005	0.25	0.01	0.02	0.11	0.010	0.01	-	0.013	0.0000	0.000	0.351	67,300	47,300	37.30	-	133	133	Dimensional Specification: B16.9		
																						WPB		

We hereby certify that the material meets the following

- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MRO-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WPB (AND SA-234)
- All non high-yield flanges meet the requirements of ASTM A-105 WPB (AND SA-105)
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.
- Bars, Billets or Blooms for flanges and certain caps and tees.
- MTR only valid with QR code linking to traceability.weldbend.com

† This indicates that the reported yield is capped at 50,000 psi.

Copyright © 2023 Weldbend Corp.

Richard Purpura

Richard Purpura

Quality Assurance Department

3/10/2025



Scan For Online
Report

We hereby certify that the material meets the following:

- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content.
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1
- L denotes ladle chemistry, P denotes product chemistry.

Generated by nklimala@weldbend.com

Cert #410240

Page 1 of 3