



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

Quantity

Product

Heat Code

Heat Treatment

Steel Mill

9

4" Class 900 Blind RF

3DF78


Heat Treat: Normalized

ACCAIERIE CALVISANO

$\frac{C}{L}$	$\frac{Mn}{1.00}$	$\frac{P}{0.012}$	$\frac{S}{0.002}$	$\frac{Si}{0.20}$	$\frac{Cu}{0.10}$	$\frac{Ni}{0.07}$	$\frac{Cr}{0.08}$	$\frac{Mo}{0.010}$	$\frac{V}{0.01}$	$\frac{Al}{0.025}$	$\frac{Ti}{0.018}$	$\frac{B}{0.0004}$	$\frac{Cb}{0.001}$	$\frac{CE (IWM)}{0.397}$
---------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	--------------------	------------------	--------------------	--------------------	--------------------	--------------------	--------------------------

Tens.	Yield	Elong	ROA	BHN	BHN2
74,100	45,900	33.10	66.70	143	143

A 105-18
Dimensional Specification: B16.5



2

3" Class 900 Blind RF

1A671

Heat Treat: Normalized

CMC STEEL

$\frac{C}{L}$	$\frac{Mn}{1.02}$	$\frac{P}{0.013}$	$\frac{S}{0.019}$	$\frac{Si}{0.24}$	$\frac{Cu}{0.29}$	$\frac{Ni}{0.08}$	$\frac{Cr}{0.09}$	$\frac{Mo}{0.017}$	$\frac{V}{0.00}$	$\frac{Al}{0.002}$	$\frac{Ti}{0.000}$	$\frac{B}{0.0001}$	$\frac{Cb}{0.002}$	$\frac{CE (IWM)}{0.416}$
---------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	--------------------	------------------	--------------------	--------------------	--------------------	--------------------	--------------------------

Tens.	Yield	Elong	ROA	BHN	BHN2
74,000	43,800	32.70	59.90	151	152

A 105-18
Dimensional Specification: B16.5



2

2" Class 1500 Blind RF

3DL55

Heat Treat: Normalized

RIVA

$\frac{C}{L}$	$\frac{Mn}{1.03}$	$\frac{P}{0.013}$	$\frac{S}{0.004}$	$\frac{Si}{0.25}$	$\frac{Cu}{0.20}$	$\frac{Ni}{0.08}$	$\frac{Cr}{0.12}$	$\frac{Mo}{0.020}$	$\frac{V}{0.00}$	$\frac{Al}{0.026}$	$\frac{Ti}{0.020}$	$\frac{B}{0.0000}$	$\frac{Cb}{0.002}$	$\frac{CE (IWM)}{0.399}$
---------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	-------------------	--------------------	------------------	--------------------	--------------------	--------------------	--------------------	--------------------------

Tens.	Yield	Elong	ROA	BHN	BHN2
76,300	50,000†	34.50	68.90	150	151

A 105-23
Dimensional Specification: B16.5



- We hereby certify that the material meets the following:
- All fittings and flanges meet NACE MR0-175/ISO 15156-Latest Revision.
 - All fittings and flanges meet NACE MR0-103 - Latest Revision.
 - All non high-yield fittings meet the requirements of ASTM A-234 WP8 (AND SA-234)
 - All non high-yield flanges meet the requirements of ASTM A-105 WP8 (AND SA-105)
 - All elbows, tees and reducers are seamless, except as noted.
 - Plate for caps and welded fittings.
 - Bars, Billets or Blooms for flanges and certain caps and tees.
 - MTR only valid with QR code linking to traceability.weldbend.com
 - † This indicates that the reported yield is capped at 50,000 psi.
- Copyright © 2023 Weldbend Corp.

Richard Purpura

Richard Purpura

Quality Assurance Department
3/3/2025



Scan For Online Report

- We hereby certify that the material meets the following:
- ISO 9001:2015 CERTIFIED MANUFACTURER
 - Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
 - No Weld Repair Performed. No Lead Content. No Mercury Content.
 - Knowledgeably making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
 - Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
 - MTR issued in accordance with EN 10204 paragraph 3.1

Generated by kcoullas@weldbend.com