



Material Test Report

Steel Mill

SERIES 4000
10" XS STRAIGHT BAR TEE-Y52

DALMINE

SP75 WPHY 52-04
Dimensional Specification: SP75

Test Temperature: -50 °F Percent Shear: 100/100/100 Average: 100
Absorbed Energy (ft/lbs): 198/206/187 Average: 197
Lateral Expansion (mils): 68/71/64 Average: 68

CMC STEEL

A 705-18
Dimensional Specification: B16.5

A
105

Richard Purpura



Page 1 of 1