



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

WELDBEND CORPORATION
P O BOX 945650
MAITLAND, FL
PO: S014201970

<u>Quantity</u>		<u>Product</u>								<u>Heat Code</u>				<u>Heat Treatment</u>				<u>Steel Mill</u>			
1		6" Std Cap WPHY52								1NS082				Quench & Tempered				METINVEST TRAMETAL			
<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>	<u>Al</u>	<u>Ti</u>	<u>B</u>	<u>Cb</u>	<u>CE (SP75)</u>	<u>Tens.</u>	<u>Yield</u>	<u>Elon</u>	<u>ROA</u>	<u>BHN</u>	<u>BHN2</u>	<u>SP75 WPHY 52-08</u>
0.15	1.45	0.010	0.002	0.29	0.03	0.03	0.04	0.000	0.04	0.037	0.018	0.0000	0.024	0.395	98,400	82,200	26.20	76.30	216	221	Dimensional Specification: B16.9
0.13	1.47	0.012	0.014	0.30	0.04	0.03	0.04	0.010	0.04	0.030	0.020	0.0005	0.020								Y-52
Fine Grain Practice																					