



SINCE 1905

Mills Iron Works, Inc.

CELEBRATING OVER 100 YEARS OF QUALITY AND SERVICE!
FITTING MANUFACTURED IN GARDENA, CA USA

CERTIFIED MATERIAL TEST REPORT
CERTIFICATE OF COMPLIANCE

DATE 09/13/24

P.O. Box 2229
Gardena, CA 90247
(323) 321-6520
WWW.MILLSIRON.COM

MIW

SOLD TO:

DNOW L.P.
MT. PLEASANT DSC
1701 GOVER PKWY
MOUNT PLEASANT MI 48858

P.O./S.O. 662552323 2413451 ITEM NO. 001

QTY 3 TAG OR P/N

DESCR 4 X 2-1/2 XH CON W/R HEAT CODE NO. 223Vn

OTHER

THE BASE MATERIAL FOR THIS ITEM MEETS THE PROPERTIES OF ASTM A106 GR B 4" XH SEAMLESS PIPE.
THE MTR FOR THAT MATERIAL RECORDS THE FOLLOWING INFORMATION:

		CHEMICAL COMPOSITION											TENSILE PROPERTIES				HARDNESS	
HEAT NUMBER	20117	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	PSI YIELD	PSI TENSILE	2 % EL. IN	% R/A	BHN MAX	
		L	0.19	0.800	0.0150	0.008	0.25	0.07	0.05	0.03	0.200	0.0050	0.0046	800	70100	34.0	68.0	197
MILL	ZELEZIAR SLOVAKIA	P											RECTANGULAR/LONGITUD					

OTHER INFORMATION
LCE = 0.36 , CONFORM TO THE REQUIREMENTS OF NACE MR0175 / ISO 15156.

WE CERTIFY THAT THE ITEM DESCRIBED ABOVE COMPLIES WITH THE REQUIREMENTS OF:

- * RAW MATERIAL MANUFACTURED IN SLOVAKIA
- * HARDNESS (BHN) AS TESTED = 135 & 139

FITTING SPEC. A234/SA234WPB 19
HT. TREAT: UNIFORMLY HEATED TO A TEMPERATURE ABOVE THE TRANSFORMATION RANGE AND SUBSEQUENTLY COOLED IN AIR AT ROOM TEMPERATURE.

YOUR DWG/SPECS: TENSILE PROPERTIES ARE FROM HEAT-TREATED SAMPLES.

SIGNATURE
PLANT MANAGER