

Our Order 2480779-2-1 Your Order 4500901380
Heat 2136620
Desc Pipe ERW API 5L X52,6.625 x .280 - 6" STD DRL

Packing List 370058-1 (8/6/2024)

Image 526150

TEX-TUBE

P.O. BOX 55710 • HOUSTON, TEXAS 77255-5710
(713) 686-4351 x 219 *PHONE*
(713) 685-3247 *FAX*
www.tex-tube.com

Certificate of Tests

PAGE: 1

No. Folio: 1001000518

02/06/2024

SALES ORDER: 1001000518

SOLD TO: 0000100046
EDGEN MURRAY CORPORATION
PO BOX 84160
BATON ROUGE LA 70884

SHIP TO: 0000900045
EDGEN MURRAY - HOUSTON
8445 MILLER RD 2
HOUSTON TX 77049

INVOICE: 0005174938 **PURCHASE ORDER:** DIS - 304488

Item Number:

Description:

11000055

5L- X52 6-5/8X.280 (18.99#)BR,DRL,PEB

Our Order 2480779-2-1 Your Order 4500901380
Heat 2136620
Desc Pipe ERW API 5L X52,6.625 x .280 - 6" STD DRL

Packing List 370058-1 (8/6/2024)

Image 526150

TEX-TUBE

P.O. BOX 55710 • HOUSTON, TEXAS 77255-5710
(713) 686-4351 x 219 PHONE
(713) 685-3247 FAX
www.tex-tube.com

02/06/2024

Certificate of Tests

PAGE: 2

Purchase Order:

DIS - 304488

Sales Order:

1001000518

Heat Number

2136620

Vendor Name

Nucor Hickman - Armored AR US

Mfg. Date

01/04/2024

Item Number

11000055

Description

5L-X52 6-5/8X.280 (18.99#)BR,DRL,PEB

CHEMICAL ANALYSIS

	C	Mn	P	S	Ni	Cr	Cu	Mo	Si	Ti	V	CE
Ladle	0.0400	1.0700	0.0140	0.0010	0.0400	0.0700	0.1300	0.0100	0.2300	0.0150	0.0050	0.1181
	Al:	0.0300	Sn:	0.0060	N:	0.0060	B:	0.0010	Ca:	0.0020	Nb:	0.0330
Chem	0.0370	1.1524	0.0143	0.0006	0.0435	0.0664	0.1319	0.0108	0.2476	0.0151	0.0043	0.1158
	Al:	0.0385	Sn:	0.0051	N:	0.0389	B:	0.0002	Ca:	0.0015	Nb:	0.0372
Chem	0.0553	1.1495	0.0137	0.0005	0.0440	0.0670	0.1338	0.0111	0.2408	0.0147	0.0040	0.1338
	Al:	0.0363	Sn:	0.0051	N:	0.0506	B:	0.0002	Ca:	0.0019	Nb:	0.0362

Acceptance Criteria: CEPCM = 0.2500

MECHANICAL PROPERTIES

YS (ksi): 69.90 TS (ksi): 74.60

EL (%): 31.00

HRB: 85.00

Y/T(%): 0.94

CHARPY TEST RESULTS

BODY

ORIENTATION: TRANSVERSE
Spec. Size (in) : .394"X.197"X2.165"
Test Temp.(of) 0
Location 3T90

Specimen(S)	Energy (ft/lbs.)	%Shear
1	92.00	100.00
2	90.00	100.00
3	98.00	100.00
Average	93.33	100.00

Acceptance Criteria Min. FT/lbs : Min. FT/Lbs 10

COMMENTS

MINIMUM HYDROSTATIC TEST PRESSURE (psi): 3,310 FOR 5 SECONDS

MANUFACTURED TO THE 46TH EDITION OF API 5L SPECIFICATION
MANUFACTURED IN THE USA
HIGH FREQUENCY WELDED PRODUCT
WELD SEAM ANNEALING AT 1600 DEGREES F. MINIMUM
ULTRASONIC TESTED TO N-10 NOTCH, 1/8 DRILLED HOLE
FLATTENING TEST PASSED
1 INCH L90 STRIP SPECIMEN
THIS MATERIAL MEETS: ASTM A53B-22, ASME SA53B-21 LATEST EDITION
API 5L PSL 2 GRADE X52M
MEETS HARDNESS REQUIREMENTS OF NACE MRO 175/ISO 15156-2 CLAUSE A.2.1.1
MEETS ISO 10474 3.1/B/EN 10204: 3.1 / STANDARDS ARE LATEST REVISION
MELTED AND MANUFACTURED IN THE U.S.A.
STEEL SUPPLIER: Nucor Hickman - Armored AR US
COIL MANUFACTURER: Nucor Hickman - Armored AR US

The above analyses and tensile properties are correct to the best of my knowledge and belief.

Quality Control Dept