



Mill Test Report				
DNOW L.P.		Purchase Order:		66268198
PO BOX 40985		Sales Order:		341638
HOUSTON TX 77240		Line Item:	3	Qty: 2

Item Code:	02 24500 99	Material:	A/SA105N LATEST EDITION	
Description:	3 900# RF BL FLANGE ANSI B16.5		Manufactured in the U.S.A.	
FID:	A7892	Heat Code:	22800586	

Element		Ladle
C	Carbon	0.1900
Mn	Manganese	1.2100
P	Phosphorous	0.0090
S	Sulphur	0.0040
Si	Silicon	0.2500
Cu	Copper	0.0090
Ni	Nickel	0.0270
Cr	Chromium	0.0180

Element		Ladle
N	Nitrogen	
Mo	Molybdenum	0.0090
V	Vanadium	0.0030
CbNb	Columbium/Niobium	0.0010
Ti	Titanium	
Al	Aluminum	
B	Boron	0.0000
Sn	Tin	


Additional Chemicals	
CRMOVNICU;0.066 CRMO 0.027	

Melting Practice	EFVR	Reduction Ratio	>3
------------------	------	-----------------	----

Mechanical Test Results			
Tensile (PSI)	76,870		
Yield (PSI)	52,793		
Elong (%)	33.00		
Red (%)	72.00		
CE	0.4001		
PCM			
HBW	156	to	155
CVN Test Temperature	-50		°F
Ft/Lbs.	115	189	105
Shear (%)	50	80	50
MLE	1.20	1.90	1.10
Charpy Sample	10 X 10 X 55mm		
QTC Type & Size			

Heat Treatment Information	
Normalizing Temperature (°F)	1670
Normalizing Time (HRS)	2

Additional Comments	

	4/15/2025
ROLANDO PASTRAN - Quality Representative	Date

Product is compliant with NACE MR0175/ISO 15156 / Product is compliant with NACE MR0103.
No weld repair is performed.
The product is free of Mercury contamination.
Tensile test is taken from round specimen.
Yield Strength is determined using 0.2% offset method, unless otherwise specified.
When reported on the MTR: Tensile testing per ASTM E 8, Charpy impact testing per ASTM E 23 and Brinell Hardness Testing per ASTM E 10.
Federal Flange manufactures products according to a certified QMS conforming to ISO 9001:2015.
Products are manufactured in compliance to EN 10204 Type 3.1.

Physical Address: 4014 Pinemont Dr | Houston, TX 77018
Telephone: (713) 681-0606 | Fax: (713) 681-3005