

PURCHASER : DODSON GLOBAL
 STANDARD : ASTM A234 WPB-23
 ASME SA234 WPB-21
 MATERIALS : ASTM A106 Gr.B
 INSP. SPEC. : ASME B16.9-18



INSPECTION CERTIFICATE

RIGID INDUSTRIES CO., LTD.

8, MEI-CHUNG RD. NIAO-SONG,
 KAOHSIUNG 83301, TAIWAN
 TEL: 886-77310527-8
 FAX: 886-77315887

DATE: 2023-05-05

ORDER NO: 324591

P.I. NO: 22G05-9

CERTIFI. NO: 230406-1

ACCORDING TO EN10204/DIN50049/3.1

ITEM NO.	PRODUCT & SIZE	QUANTITY PCS	* MFG NO. *	VISUAL & DIMENSIONAL INSPECTION	HARDNESS MAX 197 HB	HEAT TREATMENT (NOTE)	MAGNETIC PARTICLE EXAMINATION
4	TEE 6" XH	125	22D1722	GOOD	174-175	S	GOOD
5	RED-TEE 2X1" XH	10	20B7271	GOOD	165-175	S	GOOD
6	RED-TEE 2X1" XH	70	20M7684	GOOD	133-143	S	GOOD
7	RED-TEE 4X2" STD	230	22G0297	GOOD	156-168	S	GOOD
8	RED-TEE 4X2" XH	1320	22G2141	GOOD	137-140	S	GOOD
9	RED-TEE 4X2.1/2" STD	21	22C0697	GOOD	162-170	S	GOOD
10	RED-TEE 6X3" XH	70	22G174Z	GOOD	138-149	S	GOOD

ITEM NO.	MATERIAL CHARGE NO.	CHEMICAL COMPOSITION %											* PHYSICAL TEST				C.E.
		C x100	Si x100	Mn x100	P x1000	S x1000	Cu x100	Ni x100	Cr x100	Mo x100	V x100	Nb x1000	Y S KSI	T S KSI	*** E %	**	
		MIN.	10	29									35.0	60.0	30.0		
	STANDARD	MAX.	30	165	50	58	40	40	40	15	8						50
4	WY2016022	11	21	125	11	4	4	3	6	<1	<1	<1	46.4	67.1	32.8	L	34
5	17317171	13	13	78	11	4	4	2	7	3	<1	<1	49.2	69.7	33.8	L	28
6	0813284	15	30	70	14	3	10	5	5	3	1	<1	47.5	68.4	32.9	L	29
7	WC11B01997	11	24	127	10	4	1	3	8	1	1	4	46.1	66.6	31.7	L	34
8	10307441	12	16	73	7	4	5	5	5	2	<1	1	47.5	68.0	31.5	L	26
9	WC11B01997	11	24	127	10	4	1	3	8	1	1	4	46.4	65.7	33.9	L	34
10	WF1087584Z	12	26	125	10	4	5	3	11	2	<1	1	45.2	65.6	32.5	L	36

(NOTE): A: HOT FORMED WITH FINAL TEMPERATURE BETWEEN 620°C - 980°C, AIR COOLING.

N: NORMALIZING AT TEMPERATURE 880°C X0.5HR, AIR COOLING.

S: COLD FORMED WITH STRESS RELIEF AT TEMPERATURE 650°C X0.5HR

NACE MR0175-2021 PART 2 & ANNEX A/ISO 15156-2:2020 & NACE MR0103-2015/ISO 17945: SATISFACTORY

MATERIAL IS VACUUM DEGASSING/FULLY KILLED FINE GRAIN STEEL AND FREE OF WELD REPAIRS.

* TYPE OF SPECIMEN: STRIP (WIDTH: 1 in./GAUGE LENGTH: 2 in.) ** SAMPLING DIRECTION: L=LONGITUDINAL T=TRANSVERSE

*** ACTUAL THICKNESS OF SPECIMEN(S) LESS THAN 5/16" E=48t+15 (L) E=32t+10 (T)

WE HEREBY CERTIFY THAT THE PRODUCT DESCRIBED HEREIN HAS BEEN MANUFACTURED IN ACCORDANCE WITH THE SPECIFICATIONS CONCERNED AND ALSO WITH THE PURCHASER'S REQUIREMENTS AND THAT THE TEST RESULTS SHOWN HEREIN ARE CORRECT.

Daniel Kung

MANAGER OF Q.A. DEPT.