

INSPECTION CERTIFICATE

PANTECH STEEL INDUSTRIES SDN. BHD. (509731-A)

LOT 13258 & 13259, Jalan Haji Abd. Manan,
Off Jalan Meru, 42200 Kapar, Selangor, Malaysia.

Tel: 603-3393 1633 Fax: 603-3393 1733 E-mail: info@pantechsteel.com



Quality Management System is certified
under ISO 9001. Approval No.: 0047996
PED 2014/68/EU Annex 1 Clause 4.3
Cert. No.: 0343/PED/MUM/0810070/1

WROUGHT CARBON STEEL BUTTWELDING FITTINGS

INSPECTION DOCUMENT: EN10204:2004 Type 3.1

Certificate No : PSI 139758-04

Date : 30-Jan-2024

Purchaser :

Order No.	Invoice No.	Starting Material	Specification for Fittings- Seamless										Specification for Inspection					
72418	E000018350	Seamless Pipe	ASTM A234 -23 WPB / ASME SA234 -23 WPB NACE MR0103-15/ NACE MR0175/ISO15156-15*										ASME B16.9 - 18 / ASTM A960 - 23					
Batch No.	Heat No. Pipe	Product & Size	Quantity (pcs)	Part Code	Visual Examination	Dimensional Inspection	Heat Treatment	Magnetic Particle Testing										
B4606MT	231030569	3" x 2 1/2" STD RED TEE	100	3-I2DI-IS4BTBAC	GOOD	GOOD	C & S	GOOD										
B7508	13322445	6" 45 DEG LR STD ELBOW	100	6-I---IS4B4BAC	GOOD	GOOD	H	N.A										
B6104	23C108683	4" 45 DEG LR XS ELBOW	15	4-M---IS4B4BAC	GOOD	GOOD	H	N.A										
VC303	17-111620	2 1/2" 90 DEG LR S160 ELBOW	8	2DQ---IS4BLBAC	GOOD	GOOD	H	N.A										
B6910	23305634	10" 90 DEG LR S20 ELBOW	10	10E---IS4BLBAC	GOOD	GOOD	H	N.A										
Specification		Chemical Composition (%)											Tensile Test *1			Hardness		
		C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	Pb	CE	YS	TS	E ²	(HB)	
		x100	x100	x100	x1000	x1000	x100	x100	x100	x100	x1000		x100	(KSI / MPa)		(%)	1	2
Min		-	10	29	-	-	-	-	-	-	-	-	-	240	415	-	-	
Max		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Batch No.		30	-	106	50	58	40	40	15	40	80	-	50	-	-	-	197	
B4606MT		21	21	46	15	6	2	3	0	2	1	< 0.10	30	402	514	32.4	128	134
B7508		18	20	54	15	7	2	4	0	3	4	< 0.10	28	366	518	31.8	123	128
B6104		18	22	46	18	5	2	3	0	1	2	< 0.10	27	417	539	32.2	128	134
VC303		19	25	52	20	11	1	3	0	2	0	< 0.10	28	285	440	37.8	137	132
B6910		21	20	37	18	6	2	9	2	3	1	< 0.10	30	347	493	32.6	131	138

WE CERTIFY THAT ALL PRODUCTS WERE MANUFACTURED, SAMPLED, TESTED, AND INSPECTED SOLELY BY THE MANUFACTURER LISTED AT THE ADDRESS ABOVE IN ACCORDANCE WITH INDICATED SPECIFICATION AND FOUND TO MEET REQUIREMENTS. MATERIAL IS FREE FROM MERCURY AND RADIOACTIVE CONTAMINATION.

TENSILE REQUIREMENT: CONFORMS TO ASTM A370 STANDARD, LONGITUDINAL DIRECTION, GAUGE LENGTH 2" (50mm)

* FULLY KILLED

* HARDNESS ACCORDING TO NACE MR0103/ NACE MR0175/ISO15156

NOTE:

C: Cold formed at temperature below 620°C

S: Stress relieved in temperature between 595°C - 690°C and cooled in still air.

H: Hot formed in temperature between 620°C - 980°C and cooled in still air.

MT: Magnetic Particle Testing

N: Normalised at 910°C


Q: Heated to 910°C and quench in water.

T: Temper between 590°C - 690°C.

*1: YS = Yield strength TS=Tensile strength E = Elongation

*2: For thickness above 7.94 mm, the minimum elongation value, E is 30. Else, E = 48t + 15, where t = specimen thickness, in

Manufactured in Malaysia



Quality Assurance Manager