



CERTIFICATE OF TESTS

Page 7

Printed: 03/24/2025

Heat: 24102151
Material: 5L-X52 4-1/2X.337 (15.00#)BR,DRL,PEB (11000102)
Vendor: Big River Steel - Osceola AR US (180431)

Purchase Order: 26708947
Sales Order: 1001001265
MFG Date: 09/20/2024

CHEMICAL PROPERTIES

	C	MN	P	S	NI	CR	CU	MO	SI	TI	V	CE
Ladle	0.0500	1.0400	0.0100	0.0020	0.0400	0.0500	0.0800	0.0180	0.1700	0.0010	0.0030	0.1179
	Al: 0.0320		Sn: 0.0043		N: 0.0069		B: 0.0003		Ca: 0.0028		Nb: 0.0020	
Chem	0.0665	1.0487	0.0082	0.0013	0.0383	0.0424	0.0606	0.0139	0.1793	0.0009	0.0048	0.1326
	Al: 0.0304		Sn: 0.0039		N: 0.0159		B: 0.0001		Ca: 0.0022		Nb: 0.0019	
Chem	0.0673	1.0644	0.0080	0.0012	0.0386	0.0430	0.0625	0.0143	0.1826	0.0008	0.0048	0.1344
	Al: 0.0303		Sn: 0.0041		N: 0.0201		B: 0.0001		Ca: 0.0021		Nb: 0.0021	

Acceptance Criteria: CEPCM = 0.2500

MECHANICAL PROPERTIES

YS (ksi): 70.20 TS (ksi): 74.50 EL (%) : 26.00 HRB: 89.00 Y/T(%): 0.94

CHARPY TEST RESULTS (BODY)

Orientation : TRANSVERSE	Specimen(S)	Energy (ft-lb)	%Shear
Spec. Size (in) : .394"X.197"X2.165"	1	93.00	100.00
Test Temp (°F) : -20	2	90.00	100.00
Location : 3T90	3	89.00	100.00
	Average	90.67	100.00


Acceptance Criteria Min. (ft-lb) : 10

COMMENTS

MINIMUM HYDROSTATIC TEST PRESSURE (PSI) : 4,700 PER 5 SECONDS

MANUFACTURED TO THE 46TH EDITION OF API 5L SPECIFICATION
MANUFACTURED IN THE USA-HIGH FREQUENCY WELDED PRODUCT
WELD SEAM ANNEALING AT 1600 DEGREES F.MINIMUM
ULTRASONIC TESTED TO N-10 NOTCH 1/8 DRILLED HOLE
FLATTENING TEST PASSED
1 INCH L90 STRIP SPECIMEN
THIS MATERIAL MEETS :ASTM A53B-24,ASME SA53B-21 LATEST EDITION
API 5L PSL 2 GRADE X52M
MEETS HARDNESS REQUIREMENTS OF NACE MRO 175/ISO 15156-2, CLAUSE A.2.1.1
MEETS ISO 10474 3.1.B/EN 10204: 3.1 / STANDARDS ARE LATEST REVISION
MELTED AND MANUFACTURED IN THE U.S.A.
STEEL SUPPLIER: Big River Steel - Osceola AR US
COIL MANUFACTURER: Big River Steel - Osceola AR US

The above analyses and tensile properties are correct to the best of my knowledge and belief.


Quality Control Dept