



CERTIFICATE OF TESTS

Page 9

Printed: 03/24/2025

Heat: 24160792
Material: 5L- X52 4-1/2X.337 (15.00#)BR.DRL.PEB (11000102)
Vendor: Big River Steel - Osceola AR US (180431)

Purchase Order: 26708947
Sales Order: 1001001265
MFG Date: 01/30/2025

CHEMICAL PROPERTIES

	C	MN	P	S	NI	CR	CU	MO	SI	TI	V	CE
Ladle	0.0500	0.5500	0.0090	0.0020	0.0400	0.0400	0.0900	0.0100	0.1200	0.0010	0.0020	0.0901
Chem	Al: 0.0390		Sn: 0.0060		N: 0.0078		B: 0.0001		Ca: 0.0025		Nb: 0.0130	
Chem	0.0593	0.6055	0.0081	0.0015	0.0442	0.0432	0.1001	0.0111	0.1318	0.0013	0.0029	0.1037
Chem	Al: 0.0456		Sn: 0.0059		N: 0.0265		B: 0.0002		Ca: 0.0023		Nb: 0.0185	
Chem	0.0661	0.6000	0.0083	0.0014	0.0441	0.0427	0.0992	0.0109	0.1301	0.0012	0.0027	0.1099
Chem	Al: 0.0450		Sn: 0.0057		N: 0.0141		B: 0.0001		Ca: 0.0028		Nb: 0.0178	

Acceptance Criteria: CEPCM = 0.2500

MECHANICAL PROPERTIES

YS (ksi): 69.50 TS (ksi): 72.40 EL (%): 29.00 HRB: 86.00 Y/T(%): 0.96

CHARPY TEST RESULTS (BODY)

Orientation : TRANSVERSE	Specimen(S)	Energy (ft-lb)	%Shear
Spec. Size (in) : .394"X.197"X2.165"	1	67.00	100.00
Test Temp (°F) : -20	2	73.00	100.00
Location : 3T90	3	75.00	100.00
	Average	71.67	100.00

Acceptance Criteria Min. (ft-lb) : 10

COMMENTS

MINIMUM HYDROSTATIC TEST PRESSURE (PSI) : 4,700 PER 5 SECONDS

MANUFACTURED TO THE 46TH EDITION OF API 5L SPECIFICATION
MANUFACTURED IN THE USA-HIGH FREQUENCY WELDED PRODUCT
WELD SEAM ANNEALING AT 1600 DEGREES F.MINIMUM
ULTRASONIC TESTED TO N-10 NOTCH 1/8 DRILLED HOLE
FLATTENING TEST PASSED
1 INCH L90 STRIP SPECIMEN
THIS MATERIAL MEETS :ASTM A53B-24,ASME SA53B-21 LATEST EDITION
API 5L PSL 2 GRADE X52M
MEETS HARDNESS REQUIREMENTS OF NACE MRO 175/ISO 15156-2, CLAUSE A.2.1.1
MEETS ISO 10474 3.1.B/EN 10204: 3.1 / STANDARDS ARE LATEST REVISION
MELTED AND MANUFACTURED IN THE U.S.A.
STEEL SUPPLIER: Big River Steel - Osceola AR US
COIL MANUFACTURER: Big River Steel - Osceola AR US

The above analyses and tensile properties are correct to the best of my knowledge and belief.


Quality Control Dept