



CERTIFICATE OF TESTS

Page 10

Printed: 03/24/2025

Heat: 24160812
Material: 5L- X52 4-1/2X.337 (15.00#)BR,DRL,PEB (11000102)
Vendor: Big River Steel - Osceola AR US (180431)

Purchase Order: 26708947
Sales Order: 1001001265
MFG Date: 01/30/2025

CHEMICAL PROPERTIES

	C	MN	P	S	NI	CR	CU	MO	SI	TI	V	CE
Ladle	0.0600	0.5500	0.0100	0.0020	0.0400	0.0400	0.0900	0.0140	0.1400	0.0010	0.0020	0.1015
	Al: 0.0340		Sn: 0.0056		N: 0.0072		B: 0.0002		Ca: 0.0034		Nb: 0.0120	
Chem	0.0689	0.6016	0.0087	0.0011	0.0442	0.0428	0.1017	0.0110	0.1404	0.0009	0.0030	0.1134
	Al: 0.0390		Sn: 0.0059		N: 0.0110		B: 0.0002		Ca: 0.0040		Nb: 0.0175	
Chem	0.0616	0.5969	0.0084	0.0008	0.0438	0.0405	0.1000	0.0108	0.1407	0.0011	0.0029	0.1055
	Al: 0.0380		Sn: 0.0056		N: 0.0147		B: 0.0001		Ca: 0.0035		Nb: 0.0163	

Acceptance Criteria: CEPCM = 0.2500

MECHANICAL PROPERTIES

YS (ksi): 68.40 TS (ksi): 71.80 EL (%) : 28.00 HRB: 85.00 Y/T(%): 0.95

CHARPY TEST RESULTS (BODY)

Orientation : TRANSVERSE	Specimen(S)	Energy (ft-lb)	%Shear
Spec. Size (in) : .394"X.197"X2.165"	1	77.00	100.00
Test Temp (°F) : -20	2	72.00	100.00
Location : 3T90	3	79.00	100.00
	Average	76.00	100.00

Acceptance Criteria Min. (ft-lb) : 10

COMMENTS

MINIMUM HYDROSTATIC TEST PRESSURE (PSI) : 4,700 PER 5 SECONDS

MANUFACTURED TO THE 46TH EDITION OF API 5L SPECIFICATION
MANUFACTURED IN THE USA-HIGH FREQUENCY WELDED PRODUCT
WELD SEAM ANNEALING AT 1600 DEGREES F.MINIMUM
ULTRASONIC TESTED TO N-10 NOTCH 1/8 DRILLED HOLE
FLATTENING TEST PASSED
1 INCH L90 STRIP SPECIMEN
THIS MATERIAL MEETS :ASTM A53B-24,ASME SA53B-21 LATEST EDITION
API 5L PSL 2 GRADE X52M
MEETS HARDNESS REQUIREMENTS OF NACE MRO 175/ISO 15156-2, CLAUSE A.2.1.1
MEETS ISO 10474 3.1.B/EN 10204: 3.1 / STANDARDS ARE LATEST REVISION
MELTED AND MANUFACTURED IN THE U.S.A.
STEEL SUPPLIER: Big River Steel - Osceola AR US
COIL MANUFACTURER: Big River Steel - Osceola AR US

The above analyses and tensile properties are correct to the best of my knowledge and belief.


Quality Control Dept