



CERTIFICATE OF TESTS

Page 12

Printed: 03/24/2025

Heat: 24165671
Material: 5L-X52 4-1/2X.337 (15.00#)BR,DRL,PEB (11000102)
Vendor: Big River Steel - Osceola AR US (180431)

Purchase Order: 26708947
Sales Order: 1001001265
MFG Date: 01/30/2025

CHEMICAL PROPERTIES

	C	MN	P	S	NI	CR	CU	MO	SI	TI	V	CE
Ladle	0.0600	1.0200	0.0120	0.0020	0.0500	0.0500	0.0800	0.0200	0.2200	0.0010	0.0040	0.1278
	Al: 0.0300		Sn: 0.0050		N: 0.0092		B: 0.0001		Ca: 0.0030		Nb: 0.0020	
Chem	0.0685	1.1380	0.0103	0.0009	0.0485	0.0510	0.0914	0.0128	0.2324	0.0010	0.0043	0.1432
	Al: 0.0341		Sn: 0.0049		N: 0.0139		B: 0.0002		Ca: 0.0033		Nb: 0.0054	
Chem	0.0704	1.1305	0.0099	0.0007	0.0483	0.0502	0.0904	0.0127	0.2310	0.0009	0.0041	0.1444
	Al: 0.0334		Sn: 0.0048		N: 0.0157		B: 0.0001		Ca: 0.0032		Nb: 0.0049	

Acceptance Criteria: CEPCM = 0.2500

MECHANICAL PROPERTIES

YS (ksi): 68.30 TS (ksi): 73.00 EL (%): 31.00 HRB: 87.00 Y/T(%): 0.94

CHARPY TEST RESULTS (BODY)

Orientation : TRANSVERSE	Specimen(S)	Energy (ft-lb)	%Shear
Spec. Size (in) : .394"X.197"X2.165"	1	80.00	100.00
Test Temp (°F) : -20	2	79.00	100.00
Location : 3T90	3	81.00	100.00
	Average	80.00	100.00

Acceptance Criteria Min. (ft-lb) : 10

COMMENTS

MINIMUM HYDROSTATIC TEST PRESSURE (PSI) : 4,700 PER 5 SECONDS

MANUFACTURED TO THE 46TH EDITION OF API 5L SPECIFICATION
MANUFACTURED IN THE USA-HIGH FREQUENCY WELDED PRODUCT
WELD SEAM ANNEALING AT 1600 DEGREES F.MINIMUM
ULTRASONIC TESTED TO N-10 NOTCH 1/8 DRILLED HOLE
FLATTENING TEST PASSED
1 INCH L90 STRIP SPECIMEN
THIS MATERIAL MEETS :ASTM A53B-24,ASME SA53B-21 LATEST EDITION
API 5L PSL 2 GRADE X52M
MEETS HARDNESS REQUIREMENTS OF NACE MRO 175/ISO 15156-2, CLAUSE A.2.1.1
MEETS ISO 10474 3.1.B/EN 10204: 3.1 / STANDARDS ARE LATEST REVISION
MELTED AND MANUFACTURED IN THE U.S.A.
STEEL SUPPLIER: Big River Steel - Osceola AR US
COIL MANUFACTURER: Big River Steel - Osceola AR US

The above analyses and tensile properties are correct to the best of my knowledge and belief.


Quality Control Dept