


DNOW

Run Stronger.

Packing Slip 314386429



Customer PO 4400089855	Sales Order 102373727	Shipment Refer to Item	Packing Slip	**** THIS IS NOT AN INVOICE DO NOT PAY FROM THIS DOCUMENT	Date: 09/20/2024
Bill to CONSUMERS ENERGY ONE ENERGY PLAZA JACKSON MI 49201-2357		Ship To CONSUMERS ENERGY (ED) CODE 333 OVERSEL PRODUCTION 4141 142ND AVENUE ROUTE 1 HAMILTON MI 49419		Interim Ship To	
BLANKET PO: 4400089855 ACCOUNTING #: 40285890		LEASE/JOB NAME: HAMILTON		ORDERED BY: KEVIN SIMS	

Sort Seq: Customer Purchase Order

Item	Material	Description	Qty	UM
4	106092	FLANGE WELDECK U 4 IN XS CLASS 900 RAISED FACE A/SA105N FORGED CARBON STEEL ASME B16.5 COMMODITY-730791 Notes: STOCK AT MFG /Shipment 827291506 / PO ITEM: 000004	2	EA
6	F931000	FREIGHT /Shipment 827293826 / PO ITEM: 000006	1	EA

This Sales Document is subject to and controlled by the DNOW L.P. and its Affiliates Worldwide Terms and Conditions of Sale, a copy of which can be found at <https://hubs.la/OO14pZT00> as well as QR Code.
Payment Terms: Net 60 Days Delivery Terms: EXW Seller's Premises Currency: USD

DELIVERY ON TIME? YES ☐ NO ☐ DELIVERY ACCURATE? YES ☐ NO ☐

X

Signature

Print Name Here

Date

Questions: DNOW L.P. 1701 GOVER PKWY MOUNT PLEASANT MI 48858-8140 Phone: 989-773-9948

3E 24 Hour Emergency Response Contact +1-800-451-8346 (ACCESS# 334115) DNOW



SISUNGM NOP
MI04
Page 1 of 1
09/20/2024 06:15:18
T&Cs





Flanges-Precision Machining

1321 Valley Center Dr.
Bay City, MI 48706

Phone (989) 686-0350
Toll Free (800) 248-5060
Fax (989) 686-0399

Material Test Report

Date: 09/18/2024

Sold To: DNOW - MT.PLEASANT
P.O. BOX 40985

Ship To: DNOW-MT PLEASANT
1701 GOVER PKWY

USA

USA

Order No: 0754985

Ship Instructions:

PO No: 662555936

Item Description

4 900# WN RF XH A105 ASTM A105M-21/ASME SA105M-21 NORMALIZED

Heat No.

2FRF

C%	Mn%	P%	S%	Si%	Cr%	Cu%	Ni%	Mo%	V%	Cb%	N%	Al%	Ti%
.18	1.04	.014	.002	.24	.09	.09	.06	.01	.005	.002	.009	.034	.022

B%

.0004

Tensile (PSI)	Yield (PSI)	Elong %	Reduction %	Brinell	Rockwell	CE
71,100	46,700	35.2	66.4	145-147		.384
Grain Size	Test Size	Impact (FT LBS)	Charpy	Shear	Lateral Exp.	
		//		//	//	

"THE RECORDING OF FALSE, FICTITIOUS, OR FRAUDULENT STATEMENT OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE."

DIN 10204:2004 3.1

NACE MR0175-2021 ISO 15156-2 2020 NACE MR0103/2015 ISO 17945-1 2015

NO WELD REPAIR/MERCURY FREE

YIELD STRENGTH WAS DETERMINED USING THE 0.2% OFFSET METHOD.

FULLY KILLED AND FINE GRAIN PRACTICED

NORMALIZED AT 920°C COOLED IN STILL AIR

THIS IS A DIGITALLY CREATED DOCUMENT

Brian Dennis

BRIAN DENNIS/QUALITY CONTROL