

2" Bare Pipe

42908
1 of 3**BENTELER**
Steel/TubeBENTELER Steel/Tube
1 Benteler Drive/Shreveport LA 71115 USA
Tel: +1 318-218-4149
gms.shreveport@benteler.com**INSPECTION CERTIFICATE EN 10204-3.1**
EN 10204:2005-01Document No.: 485-1401720/001/P
Purchase Order No.: 11358
Benteler Order No.: 48003023
Dispatch Note No.:
Product: SEAMLESS STEEL TUBESInspection No.:
Manufacturer: BSTMC Shreveport USA
Manufacturer's brand: 
Stamp of the inspection representative: MI
Steelmaking process: ELECTRIC FURNACE

Page: 1 / 3

Dada Pipe Sales, Inc.
PO Box 300850
HOUSTON TX 77230
USA**Terms of delivery:**ASTM-A 53-2020, ASME SA-53, ASME BPVC.III-A-2021, ASTM-A 106-19a, ASME SA-106, ASME BPVC.III-A-2021, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018, PSL 2, ANSINACE MR0175/ISO 15156-1: 2020, ANSINACE MR0175/ISO 15156-2:
2020, ANSINACE MR0103/ISO 17845:2015**Dimensions-tolerances:**ASTM-A 106-19a, ASME SA-106, ASME BPVC.III-A-2021, ASTM-A 53-2020, ASME SA-53, ASME BPVC.III-A-2021, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018**Steel grade:**

GRADE B, GRADE C, GRADE BN, GRADE X42N

Delivery condition:

N

Product marking:FS: BENTELER BENTELER-Sign API 5L-1072 API-Sign Month/Year Conditions Dimension: O.D. * t inch Steel Grade
PSL2 SMLS Heat No. Tube length feet Test Pressure PSI Production No. Customer's material no.

AEZ = Etching ink coating FK = color marking FB = paint stenciling FBD = Color jet printer FBI = Color jet printer inside LK = Laser marking PKE = tag marking PS = die stamp TS = ink jet spray marking

Item	Dimensions	Heat No.	Test pressure	
			PSI	bar
0001	2 NPS - SCH 80 35,000 FT - 45,000 FT	316179	2970	5

Country of melt and pourMelted & Manufactured in USA
Rucor, Jewett, TX, US**Heat analysis [%]**

Item	Heat No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	V	Nb	Ti	B
0001	316179	0.160	0.233	1.01	0.011	0.002	0.14	0.03	0.07	0.24	0.004	0.002	0.002	0.0004

1. Formula: $CE \equiv C + (Mn/5) + ((Cr+Mo+V)/5) + ((Cu+Ni)/15) \leq 0.43 \%$ 2. Formula: $Cr+Cu+Mo+Ni+V \leq 1.00 \%$ 3. Formula: $Nb+V \leq 0.08 \%$ 4. Formula: $Nb+Ti+V \leq 0.15 \%$

42908
2 of 3

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

455-1401720/001/P

Inspection No.:

Page: 2 / 3

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0001	316179	0,384	0,484	0,006	0,008

Product analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0001	316179	0.150	0.240	1.01	0.010	0.001	0.13	0.03	0.06	0.24	0.004	0.002	0.003	0.0003
0001	316179	0.160	0.250	1.00	0.007	0.001	0.14	0.03	0.06	0.24	0.004	0.001	0.003	0.0003

1. Formula: $CE_{IIW} = C + (Mn/6) + ((Cr+Mo+V)/5) + ((Cu+Ni)/15) \leq 0,43 \%$

2. Formula: $Cr+Cu+Mo+Ni+V \leq 1,00 \%$

3. Formula: $Nb+V \leq 0,06 \%$

4. Formula: $Nb+Ti+V \leq 0,15 \%$

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0001	316179	0,371	0,464	0,006	0,009
0001	316179	0,381	0,474	0,005	0,008

Test results

The tubes have been submitted to a leak tightness test by: Hydrostatic test: acc. to API 5L, Test pressure/Time-record, the test records/charts shall be available for examination by the inspector **PASSED**

The tubes are non destructive tested: ET - Test standard: acc. to API 5L; ET - Test method: acc. to ASTM-E 309; ET - Test drilled hole: 0,125 IN.; ET - Notch shape/hole: drilled hole **PASSED**

Visual inspection: **PASSED** Bending test: **PASSED** Dimensions examination: **PASSED**

Results of mechanical testing

Tensile test longitudinal at RT, Strip test specimen

Item	Specimen No.	Heat No.	Specimen dimensions	Yield strength	Tensile strength	Elongation	1. Formula	Rt 0,5/Rm
Requirements				RT 0,5 % PSI 42100-71800	Rm PSI 70000-85000	A2 %		MAX 0,93
0001	000011	316179	0,749 X 0,218	53374	78611	35,00	19,00	0,68
0001	001642	316179	0,751 X 0,216	53519	78030	33,00	19,00	0,68