

43087
2 of 3

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

466-1421239/001/P

Inspection No.:

Page: 2 / 3

Product analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NS	TI	B
0002	316438	0.180	0.280	0.97	0.008	0.002	0.11	0.03	0.07	0.15	0.003	0.001	0.003	0.0004
0002	316438	0.180	0.270	0.97	0.009	0.003	0.11	0.03	0.06	0.14	0.003	0.001	0.003	0.0004

1. Formula: $CE_{IIW} = C + (Mn/5) + ((Cr+Mo+V)/5) + ((Cu+Ni)/15) \leq 0.43 \%$

2. Formula: $Cr+Cu+Mo+Ni+V \leq 1.00 \%$

3. Formula: $Nb+V \leq 0.06 \%$

4. Formula: $Nb+Ti+V \leq 0.15 \%$

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0002	316438	0,385	0,363	0,004	0,007
0002	316438	0,384	0,343	0,004	0,007

Test results

The tubes have been submitted to a leak tightness test by: Hydrostatic test: acc. to API 6L. Test pressure/Time-record, the test records/charts shall be available for examination by the inspector. **PASSED**

The tubes are non destructive tested: ET - Test standard: acc. to API 5L; ET - Test method: acc. to ASTM-E 309; ET - Test drilled hole: 0,125 IN.; ET - Notch shape/hole: drilled hole. **PASSED**

Visual inspection: **PASSED** Bending test: **PASSED** Dimensions examination: **PASSED**

Results of mechanical testing

Tensile test longitudinal at RT, Strip test specimen

Item	Specimen No.	Heat No.	Specimen dimensions	Yield strength	Tensile strength	Elongation	1. Formula	Rt 0,5/Rm
Requirements				RT 0,5 % PSI 42100-71800	Rm PSI 70000-95000	A2" %		MAX 0,93
0002	000011	316438	0,748 X 0,215	53374	78175	32,00	19,00	0,68
0002	001582	316438	0,750 X 0,219	52214	77595	34,00	19,00	0,67

Elongation formula

1. Formula $AF = 625000 \cdot AXC^{0,2} / U^{0,9}$

Protection

outside surface varnished

160
BENTELER Steel/Tube
1 Benteler Drive|Shreveport|LA 71115|USA
Tel.: +1 318-216-4149
qms.shreveport@benteler.com

43087
3 of 3

BENTELER 
Steel/Tube

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

465-1421238/001/P

Inspection No.:

Page: 3 / 3

Item	Heat No.	Production No.
0002	316438	15030843

Remark

NACE Standard: Hardness acc. to ANSI/NACE MR0175/ISO 15156: HRC max 22 as per ASTM A370 table 2&3., Hardness acc. to ANSI/NACE MR0103/ISO 17945: HRC max. 22 as per ASTM A370 table 2&3.; Certificate remarks: material free from mercury contamination, Data converted from SI units, No weld repair has been carried out;
Certificate-Remark: LONGHORN

Plant 465, 1 BENTELER DRIVE, LA 71115 Shreveport, 09.10.2023, TEL: 678-386-3371

Inspection representative
PIDICHETTI / AM

We certify that the supplied product has been processed, sampled, tested, and inspected in accordance with the agreed specifications and/or references mentioned herein and meet the requirements for the grade indicated. This document was prepared by means of electronic data processing and is valid without signature.

160 / ~~20~~ Coated 2" 20'

BENTELER Steel/Tube
1 Benteler Drive|Shreveport|LA 71115|USA
Tel.: +1 318-216-4149
qms.shreveport@benteler.com

43087
1 of 3

BENTELER 
Steel/Tube

INSPECTION CERTIFICATE EN 10204-3.1

EN 10204:2005-01

Document No.: 465-1421239/001/P
Purchase Order No.: 11449
Benteler Order No.: 48010053
Dispatch Note No.:
Product: SEAMLESS STEEL TUBES

Inspection No.:
Manufacturer: BSTMC Shreveport USA
Manufacturer's brand: 
Stamp of the inspection representative: MI
Steelmaking process: ELECTRIC FURNACE

Page: 1 / 3

Dixie Pipe Sales, Inc.
PO Box 300650
HOUSTON TX 77230
USA

Terms of delivery: ASTM-A 53-2020, ASME SA-53, ASME BPVC.II.A-2021, ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2021, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018, PSL-2, ANSINACE MR0175/ISO 15156-1: 2020, ANSINACE MR0175/ISO 15156-2:
2020, ANSINACE MR0103/ISO 17946:2015

Dimensions-tolerances: ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2021, ASTM-A 53-2020, ASME SA-53, ASME BPVC.II.A-2021, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018

Steel grade: GRADE B, GRADE C, GRADE BN, GRADE X42N

Delivery condition: N

Item	Dimensions	Heat No.	Test pressure	
			PSI	sec
0002	2 NPS - SCH 80 35,000 FT - 45,000 FT	316438	2970	5

Country of melt and pour

Melted & Manufactured in USA
Nucor, Jewett, TX, US

Heat analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0002	316438	0.160	0.255	0.98	0.011	0.005	0.12	0.03	0.06	0.14	0.003	0.001	0.002	0.0002

1. Formula: $CE_{IIV} = C + (Mn/5) + ((Cr + Mo + V)/5) + ((Cu + Ni)/15) \leq 0.43 \%$

2. Formula: $Cr + Cu + Mo + Ni + V \leq 1.00 \%$

3. Formula: $Nb + V \leq 0.06 \%$

4. Formula: $Nb + Ti + V \leq 0.15 \%$

Formula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0002	316438	0.367	0.353	0.004	0.006