

BENTELER Steel/Tube
1 Benteler Drive|Shreveport|LA 71115|USA
Tel.: +1 318-216-4215
qms.shreveport@benteler.com

INSPECTION CERTIFICATE EN 10204-3.1
EN 10204:2005-01

Document No.: 465-1522656/001/P
Purchase Order No.: 26707633
Inspection No.:
Manufacturer: BSTMC Shreveport USA
Page: 1 / 3

DNOW L.P.
7402 N. Eldridge Parkway
HOUSTON TX 77041
USA

Benteler Order No.: 48010732
Dispatch Note No.:
Product: SEAMLESS STEEL TUBES
Manufacturer's brand:
Stamp of the inspection representative: MI
Steelmaking process: ELECTRIC FURNACE

Terms of delivery:

ASTM-A 53-2020, ASME SA-53, ASME BPVC.II.A-2023, ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2023, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018, PSL 2, ANSINACE MR0175-2021/ISO 15156-1:2020, ANSINACE MR0175-2021/ISO 15156-2:2020, ANSINACE MR0103/ISO 17945:2015, ASME B36.10-2022

Dimensions-tolerances:

ASTM-A 106-19a, ASME SA-106, ASME BPVC.II.A-2023, ASTM-A 53-2020, ASME SA-53, ASME BPVC.II.A-2023, API Specification 5L
Forty-Sixth Edition April 2018 incl. Errata 1, May 2018

Steel grade:

GRADE B, GRADE C, GRADE BN, GRADE X42N

Delivery condition:

N

Product marking:

S: BENTELER - BENTELER-Sign - API 5L 1072 - API-Sign - Month/Year - A/SA 53 A/SA 106 NACE - 3,500" OD x 0,300" WT - B/C/BN/X42N - PSL 2 - SMLS - Heat No. - Tube length feet - 2,970 - 15040723 - LONGHORN

Item

Dimensions

Item	Dimensions	ITEM CODE	Heat No.	Test pressure
0010	3 NPS - SCH 80 35.000 FT - 45.000 FT	1095416	321229	PSI sec 2970 5

Country of melt and pour

Melted & Manufactured in USA
Nucor, Jewett, TX, US

Heat analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0010	321229	0.170	0.244	1.00	0.010	0.001	0.11	0.02	0.06	0.15	0.004	0.001	0.002	0.0001

1. Formula: $CE \ IIW=C+(Mn/6)+((C+Mn+V)/5)+((Cu+Ni)/15) \leq 0.43 \ %$
2. Formula: $C+Cu+Mo+Ni+V \leq 1.00 \ %$
3. Formula: $Nb+V \leq 0.06 \ %$
4. Formula: $Nb+Ti+V \leq 0.15 \ %$

INSPECTION CERTIFICATE EN 10204-3.1

Document No.:

465-1522656/001/P

Inspection No.:

Page: 2 / 3

F ormula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0010	321229	0.377	0.344	0.005	0.007

Product analysis [%]

Item	Heat No.	C	SI	MN	P	S	CR	MO	NI	CU	V	NB	TI	B
0010	321229	0.160	0.240	0.96	0.008	0.001	0.11	0.02	0.06	0.16	0.003	0.001	0.002	0.0001
0010	321229	0.170	0.240	0.96	0.011	0.002	0.11	0.02	0.06	0.17	0.003	0.001	0.002	0.0002

1. Formula: $CE \leq C + (Mn/6) + ((C + Mo + V)/5) + ((Cu + Ni)/15) \leq 0.43 \%$
2. Formula: $C + Cu + Mo + Ni + V \leq 1.00 \%$
3. Formula: $Nb + V \leq 0.06 \%$
4. Formula: $Nb + Ti + V \leq 0.15 \%$

F ormula results

Item	Heat No.	1. Formula	2. Formula	3. Formula	4. Formula
0010	321229	0.361	0.353	0.004	0.006
0010	321229	0.372	0.363	0.004	0.006

T est results

The tubes have been submitted to a leak tightness test by:

Hydrostatic test: acc. to API 5L; Test pressure/Time-record, the test records/charts shall be available for examination by the inspector

PASSED

The tubes are non destructive tested:

ET - Test standard: acc. to API 5L; ET - Test method: acc. to ASTM-E 309; ET - Test drilled hole: 0.125 IN.; ET - Notch shape/hole: drilled hole

PASSED

Visual inspection:

PASSED

Dimensions examination:

PASSED

Results of mechanical testing

T ensile test longitudinal at RT, Strip test specimen

Item	Specimen No.	Heat No.	Specimen dimensions	Yield strength	Tensile strength	Elongation	1. Formula	Rt 0.5/Rm
Requirements			IN	RT 0.5 % PSI	Rm PSI	A2" %		MAX 0.93
0010	000011	321229		0.752 X 0.293	48443	35.00		0.65
0010	002362	321229		0.752 X 0.310	48733	35.00		20.00
								20.00
								0.64

BENTELER Steel/Tube
1 Benteler Drive|Shreveport|LA 71115|USA
Tel.: +1 318-216-4215
qms.shreveport@benteler.com

INSPECTION CERTIFICATE EN 10204-3.1

Document No.: 465-1522656/001/P Inspection No.: Page: 3 / 3

Elongation formula

1. Formula: $A_F = 625000 \cdot AXC^{0.2} / U^{0.9}$

Notched bar impact test [1 CHARPY_V]

Specimen position: longitudinal (L); Test temperature: -50 °F

Item	Specimen No.	Heat No.	Specimen dimensions			Absorbed energy		Impact strength		Shear fracture			
			Length	Width	Height	single	average			single	average	single	average
0010	000011	321229	mm	mm	mm	ft-lbf	ft-lbf	MIN 000		%	%		
			55	5.00	10.00	28							
				5.00	10.00	32							
				5.00	10.00	27							

Protection

outside surface varnished

Item	Heat No.	Production No.
0010	321229	15040723

Remark

NACE Standard: Hardness acc. to ANSI/NACE MR0175/ISO 15156: HRC max 22 as per ASTM A370 table 2&3, Hardness acc. to ANSI/NACE MR0103/ISO 17945: HRC max. 22 as per ASTM A370 table 2&3; Certificate remarks: material free from mercury contamination, Data converted from SI units, No weld repair has been carried out;

Certificate-Remark: LONGHORN

Plant 465, 1 BENTELER DRIVE, LA 71115 Shreveport, 04/19/2025, TEL.: 0318-216-4260

Inspection representative
ME

We certify that the supplied product has been processed, sampled, tested, and inspected in accordance with the agreed specifications and/or references mentioned herein and meet the requirements for the grade indicated. This document was prepared by means of electronic data processing and is valid without signature.