



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

Quantity

Product

Heat Code

Heat Treatment

Steel Mill

9

4" Class 900 Blind RF

3DF78

Heat Treat: Normalized

ACCAIERIE CALVISANO

C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (I/M)	Tens.	Yield	Elong	ROA	BHN	BHN2
L	0.20	1.00	0.012	0.002	0.20	0.07	0.08	0.010	0.01	0.025	0.018	0.0004	0.001	0.397	74,100	45,900	33.10	66.70	143	143



2

3" Class 900 Blind RF

1A671

Heat Treat: Normalized

CMC STEEL

C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (I/M)	Tens.	Yield	Elong	ROA	BHN	BHN2
L	0.20	1.02	0.013	0.019	0.24	0.08	0.09	0.017	0.00	0.002	0.000	0.0001	0.002	0.416	74,000	43,800	32.70	59.90	151	152



2

2" Class 1500 Blind RF

3DL55

Heat Treat: Normalized

RIVA

C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (I/M)	Tens.	Yield	Elong	ROA	BHN	BHN2
L	0.18	1.03	0.013	0.004	0.25	0.08	0.12	0.020	0.00	0.026	0.020	0.0000	0.002	0.399	76,300	50,000†	34.50	68.90	150	151



We hereby certify that the material meets the following:

- All fittings and flanges meet NACE MR0-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MR0-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WP8 (AND SA-234)
- All non high-yield flanges meet the requirements of ASTM A-105 WP8 (AND SA-105)
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.
- Bars, Billets or Blooms for flanges and certain caps and tees.
- MTR only valid with QR code linking to traceability.weldbend.com
- † This indicates that the reported yield is capped at 50,000 psi.

Copyright © 2023 Weldbend Corp.

Richard Purpura



Scan For Online Report

Richard Purpura

Quality Assurance Department
3/3/2025

Cert #4095543

We hereby certify that the material meets the following:

- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content.
- Knowledgeably making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1

Generated by kcoullas@weldbend.com