



Mill Test Report				
DNOW L.P.		Purchase Order:	66268198	
PO BOX 40985		Sales Order:	341638	
HOUSTON TX 77240		Line Item:	4	Qty: 4

Item Code:	FF 413AA 01 0A	Material:	A/SA105N LATEST EDITION	
Description:	10 900# RF BL FLANGE ANSI B16.5		Manufactured in the U.S.A.	
FID:	A9734	Heat Code:	4318590	

Element	Ladle
C	Carbon 0.2000
Mn	Manganese 1.2200
P	Phosphorous 0.0150
S	Sulphur 0.0040
Si	Silicon 0.2700
Cu	Copper 0.0060
Ni	Nickel 0.0090
Cr	Chromium 0.0250

Element	Ladle
N	Nitrogen
Mo	Molybdenum 0.0010
V	Vanadium 0.0013
CbNb	Columbium/Niobium 0.0040
Ti	Titanium
Al	Aluminum 0.0300
B	Boron 0.0003
Sn	Tin

Additional Chemicals	

Melting Practice	EAF LRF VD	Reduction Ratio	4:1
------------------	------------	-----------------	-----

Mechanical Test Results			
Tensile (PSI)	79,439		
Yield (PSI)	52,541		
Elong (%)	30.82		
Red (%)	74.11		
CE	0.4098		
PCM			
HBW	159	to	163
CVN Test Temperature	-50 °F		
Ft/Lbs.	102	98	89
Shear (%)	60	60	55
MLE	55	56	50
Charpy Sample	10 x 10 x 55MM		
QTC Type & Size			

Heat Treatment Information	
Normalizing Temperature (°F)	1670
Normalizing Time (HRS)	4
Cooling Media (TYPE)	air

Additional Comments	
FULLY KILLED & FINE GRAIN PRACTICE	

	4/15/2025
ROLANDO PASTRAN - Quality Representative	Date

Product is compliant with NACE MR0175/ISO 15156 / Product is compliant with NACE MR0103. No weld repair is performed. The product is free of Mercury contamination. Tensile test is taken from round specimen. Yield Strength is determined using 0.2% offset method, unless otherwise specified. When reported on the MTR: Tensile testing per ASTM E 8, Charpy Impact testing per ASTM E 23 and Brinell Hardness Testing per ASTM E 10 Federal Flange manufactures products according to a certified QMS conforming to ISO 9001:2015. Products are manufactured in compliance to EN 10204 Type 3.1.	
--	--

Physical Address: 4014 Pinemont Dr Houston, TX 77018 Telephone: (713) 681-0606 Fax: (713) 681-3005	
---	--