

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000206309

Page 1 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 07/25/2024

CUSTOMER

BONNEY ORDER NO. B000348606

ORDER NO.: 26650702

SHIP TO: DNOW L.P. (MOUNT PLEASANT)
1701 GOVER PKWY
MOUNT PLEASANT MI 48858
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
66578	2	9	D903	2 3000 A105 UNAR T
				SA/A105
				MALE
				Al 0.025 C 0.200 Co 0.003 Cr 0.100 Cu 0.060 Mn 1.080 Mo 0.005 Nb 0.009 Ni 0.020 P 0.006 S 0.021 Si 0.230 V 0.003 CE(Long Formula) = 0.41 T/S(PSI) 75,100 Y/S(PSI) 44,400 EL(%) 37.50 RA(%) 59.40 Brinell Hardness 150 BHN 152 BHN
66578	2	D889	FEMALE	2 3000 A105 UNAR T
				SA/A105
				Al 0.021 C 0.210 Co 0.002 Cr 0.110 Cu 0.030 Mn 1.040 Mo 0.004 Nb 0.009 Ni 0.020 P 0.006 S 0.020 Si 0.230 V 0.003 CE(Long Formula) = 0.41 T/S(PSI) 75,800 Y/S(PSI) 46,900 EL(%) 34.00 RA(%) 60.30 Brinell Hardness 154 BHN 154 BHN
66578	2	H6CIA ✓	NUT	2 3000 A105 UNAR T
				SA/A105
				C 0.170 Cb 0.000 Co 0.005 Cr 0.150 Cu 0.150 Mn 1.040 Mo 0.030 Ni 0.060 P 0.010 S 0.019 Si 0.270 V 0.032 CE(Long Formula) = 0.40 T/S(PSI) 81,562 Y/S(PSI) 57,937 EL(%) 32.85 RA(%) 61.55 Brinell Hardness 159 BHN 156 BHN
174797	3	25	51317	6 X 2 3000 A105 SOCK S
				SA/A105
				C 0.190 Cb 0.002 Co 0.006 Cr 0.120 Cu 0.220 Mn 0.950 Mo 0.020 Ni 0.070 P 0.011 S 0.018 Si 0.169 V 0.022 CE(Long Formula) = 0.40 T/S(PSI) 77,496 Y/S(PSI) 51,306 EL(%) 34.00 RA(%) 34.00 Brinell Hardness 147 BHN 144 BHN

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Paige Smith

Paige Smith

Quality Assurance Representative

CMTR: Rev 3