

350

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000203067

Page 1 of 1

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14488 CROGHAN PIKE • MOUNT UNION, PA 17088-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4908

www.bonneyforge.com

DATE 05/20/2024

CUSTOMER: DNOW L.P.

BONNEY ORDER NO. B000345308

CUSTOMER

ORDER NO.: 662461556

SHIP TO: DNOW L.P. (MOUNT PLEASANT)
1701 GOVER PKWY
MOUNT PLEASANT MI 48858
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS.	
258903	8	51317	4 -31/2X 2 3000 A105 THRD T	
			SA/A105	
			C 0.190 Cb 0.002 Co 0.006 Cr 0.120 Cu 0.220 Mn 0.950 Mo 0.020 Ni 0.070	
			P 0.011 S 0.018 Si 0.169 V 0.022	
			CE(Long Formula) = 0.40	
			T/S(PSI) 77,496 Y/S(PSI) 51,306 EL(%) 34.00 RA(%) 34.00	
Brinell Hardness		147 BHN	144 BHN	

1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2 - 2015 EDITION.
3. CERTIFYING ASTM A105-21 / ASME SA105-21 EDITION.
4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
5. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Paige Smith
Paige Smith
Quality Assurance Representative