

# CERTIFIED MILL TEST REPORT



The Best Value -  
Price, Quality, Service  
All The Time.

LOG NO. F00000000184615

Page 12 of 14

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 05/04/2023

CUSTOMER

BONNEY ORDER NO. B000326307

ORDER NO.: 26527500

SHIP TO: DNOW L.P. (WILLISTON)  
5072 OWAN INDUSTRIAL PARK  
WILLISTON ND 58801-9064  
United States

| ITEM  | QUANTITY | LOT NO. | GRADE OR SPECIFICATION NO. | CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:                                                                                                                                                                                              |
|-------|----------|---------|----------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 49    | 25       | 51184   | 1/2 2000 A105 45EL T       | SA/A105                                                                                                                                                                                                                                       |
| 89661 |          |         |                            | C 0.190 Co 0.006 Cr 0.080 Cu 0.120 Mn 1.040 Mo 0.014 Nb 0.009 Ni 0.040<br>P 0.008 S 0.021 Si 0.190 Sn 0.004 V 0.003<br>CE(Long Formula) = 0.39<br>T/S(PSI) 80,719 Y/S(PSI) 53,679 EL(%) 32.80 RA(%) 57.47<br>Brinell Hardness 144 BHN 150 BHN |
| 50    | 25       | D680    | 1/4X 1/8 3M/6M A105 HXBU T | SA/A105                                                                                                                                                                                                                                       |
| 89523 |          |         |                            | Al 0.019 C 0.200 Co 0.004 Cr 0.100 Cu 0.060 Mn 1.010 Mo 0.004 Nb 0.009<br>Ni 0.020 P 0.008 S 0.019 Si 0.200 V 0.004<br>CE(Long Formula) = 0.40<br>T/S(PSI) 80,100 Y/S(PSI) 55,800 EL(%) 35.00 RA(%) 66.20<br>Brinell Hardness 146 BHN 140 BHN |
| 51    | 100      | D358    | 3/8X 1/4 3M/6M A105 HXBU T | SA/A105                                                                                                                                                                                                                                       |
| 89525 |          |         |                            | C 0.190 Cb 0.013 Co 0.003 Cr 0.070 Cu 0.040 Mn 1.110 Mo 0.006 Ni 0.020<br>P 0.005 S 0.021 Si 0.230 V 0.004<br>CE(Long Formula) = 0.40<br>T/S(PSI) 82,200 Y/S(PSI) 54,600 EL(%) 27.00 RA(%) 63.70<br>Brinell Hardness 143 BHN 149 BHN          |
| 52    | 8        | 51529   | 2 3000 A105 STEL T         | SA/A105                                                                                                                                                                                                                                       |
| 89605 |          |         |                            | Al 0.019 C 0.210 Co 0.003 Cr 0.120 Cu 0.050 Mn 1.040 Mo 0.004 Nb 0.010<br>Ni 0.020 P 0.007 S 0.017 Si 0.230 V 0.004<br>CE(Long Formula) = 0.41<br>T/S(PSI) 78,431 Y/S(PSI) 49,197 EL(%) 30.60 RA(%) 58.40<br>Brinell Hardness 141 BHN 141 BHN |

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by 

Natalie Miller

Quality Assurance Representative