

CERTIFIED MILL TEST REPORT



The Best Value
Price, Quality, Service
All The Time.

LOG NO. F00000000212580

Page 1 of 1

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 11/19/2024

CUSTOMER

BONNEY ORDER NO. B000354319


ORDER NO.: 26669968

SHIP TO: DNOW L.P. (ODESSA)
5301 WEST MURPHY STREET
ODESSA TX 79763
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
89585	50	51905	1/2 3000 A105 90EL T	
			SA/A105	
			Al 0.025 C 0.200 Co 0.002 Cr 0.100 Cu 0.030 Mn 1.050 Mo 0.003 Nb 0.011	
			Ni 0.010 P 0.004 S 0.021 Si 0.240 V 0.005	
			CE(Long Formula) = 0.40	
			T/S(Psi) 81,756 Y/S(Psi) 52,062 EL(%) 33.15 RA(%) 61.09	
145286	25	51896	6-4X2 3000 A105 FLEX T	
			SA/A105	
			Al 0.034 C 0.200 Co 0.006 Cr 0.150 Cu 0.290 Mn 1.020 Mo 0.020 Nb 0.004	
			Ni 0.070 P 0.011 S 0.024 Si 0.246 V 0.024	
			CE(Long Formula) = 0.43	
			T/S(Psi) 81,219 Y/S(Psi) 51,999 EL(%) 32.85 RA(%) 57.39	
			Brinell Hardness 156 BHN 156 BHN	

1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2 - 2015 EDITION.
3. CERTIFYING ASTM A105-24 / ASME SA105-23 EDITION.
4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
5. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by 

Billie Jo Clemens
Quality Assurance Representative