

CERTIFIED MILL TEST REPORT



The Best Value
Price, Quality, Service
All The Time.

LOG NO. F00000000212580

Page 1 of 1

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 11/19/2024

CUSTOMER

BONNEY ORDER NO. B000354319

ORDER NO.: 26669968

SHIP TO: DNOW L.P. (ODESSA)
5301 WEST MURPHY STREET
ODESSA TX 79763
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
12	50	51905	1/2 3000 A105 90EL T	SA/A105
89585			Al 0.025 C 0.200 Co 0.002 Cr 0.100 Cu 0.030 Mn 1.050 Mo 0.003 Nb 0.011 Ni 0.010 P 0.004 S 0.021 Si 0.240 V 0.005 CE(Long Formula) = 0.40 T/S(Psi) 81,756 Y/S(Psi) 52,062 EL(%) 33.15 RA(%) 61.09 Brinell Hardness 156 BHN 156 BHN	
16	25	51896	6-4X2 3000 A105 FLEX T	SA/A105
145286			Al 0.034 C 0.200 Co 0.006 Cr 0.150 Cu 0.290 Mn 1.020 Mo 0.020 Nb 0.004 Ni 0.070 P 0.011 S 0.024 Si 0.246 V 0.024 CE(Long Formula) = 0.43 T/S(Psi) 81,219 Y/S(Psi) 51,999 EL(%) 32.85 RA(%) 57.39 Brinell Hardness 159 BHN 159 BHN	

1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2 - 2015 EDITION.
3. CERTIFYING ASTM A105-24 / ASME SA105-23 EDITION.
4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
5. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative