

CERTIFIED MILL TEST REPORT



**The Best Value -
Price, Quality, Service
All The Time.**

LOG NO. F00000000213370

Page 4 of 7

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 12/09/2024

CUSTOMER

BONNEY ORDER NO. B000355767

ORDER NO.: 26686974

SHIP TO: DNOW L.P. (WILLISTON)
5072 OWAN INDUSTRIAL PARK
WILLISTON ND 58801-9064
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
89587	9	425	51825	1 3000 A105 90EL T
				SA/A105
				Al 0.023 C 0.210 Co 0.002 Cr 0.120 Cu 0.040 Mn 1.050 Mo 0.003 Nb 0.009
				Ni 0.020 P 0.007 S 0.024 Si 0.220 V 0.004
				CE(Long Formula) = 0.41
				T/S(Psi) 81,332 Y/S(Psi) 55,305 EL(%) 29.80 RA(%) 60.23
89587	9	51948	1 3000 A105 90EL T	SA/A105
				Al 0.021 C 0.200 Co 0.003 Cr 0.130 Cu 0.040 Mn 1.070 Mo 0.003 Nb 0.009
				Ni 0.010 P 0.006 S 0.020 Si 0.220 V 0.003
				CE(Long Formula) = 0.41
				T/S(Psi) 81,675 Y/S(Psi) 50,147 EL(%) 32.10 RA(%) 63.47
				Brinell Hardness 144 BHN 144 BHN
3657	10	50	51814	2X1 3000 A105 THRD T
				SA/A105
				Al 0.026 C 0.210 Co 0.010 Cr 0.140 Cu 0.100 Mn 0.990 Mo 0.020 Nb 0.001
				Ni 0.040 P 0.008 S 0.022 Si 0.270 V 0.003
				CE(Long Formula) = 0.42
				T/S(Psi) 74,916 Y/S(Psi) 47,512 EL(%) 32.70 RA(%) 64.05
89547	11	75	D871	2 X 1/2 3M/6M A105 HXBU T
				SA/A105
				Al 0.028 C 0.210 Co 0.003 Cr 0.120 Cu 0.060 Mn 1.100 Mo 0.002 Nb 0.010
				Ni 0.020 P 0.007 S 0.019 Si 0.210 V 0.004
				CE(Long Formula) = 0.42
				T/S(Psi) 77,300 Y/S(Psi) 48,300 EL(%) 38.00 RA(%) 57.80
89547	11	75	D871	2 X 1/2 3M/6M A105 HXBU T
				SA/A105
				Al 0.028 C 0.210 Co 0.003 Cr 0.120 Cu 0.060 Mn 1.100 Mo 0.002 Nb 0.010
				Ni 0.020 P 0.007 S 0.019 Si 0.210 V 0.004
				CE(Long Formula) = 0.42
				T/S(Psi) 77,300 Y/S(Psi) 48,300 EL(%) 38.00 RA(%) 57.80

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Billie Jo Clemens
Billie Jo Clemens
Quality Assurance Representative