

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000213443

Page 3 of 7

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 12/10/2024

CUSTOMER

BONNEY ORDER NO. B000355839

ORDER NO.: 26687287

SHIP TO: DNOW L.P. (ODESSA)
5301 WEST MURPHY STREET
ODESSA TX 79763
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
89562	100	D957 ✓	1 3000 A105 COUP T	SA/A105
			Al 0.023 C 0.200 Co 0.006 Cr 0.150 Cu 0.180 Mn 1.050 Mo 0.020 Nb 0.005	
			Ni 0.060 P 0.011 S 0.019 Si 0.187 V 0.020	
			CE(Long Formula) = 0.43	
			T/S(PSI) 73,600 Y/S(PSI) 50,100 EL(%) 46.00 RA(%) 51.00	
			Brinell Hardness 158 BHN 159 BHN	
145279	125	51979	36-3/4X1/2 3000 A105 FLEX T	SA/A105
			Al 0.021 C 0.200 Co 0.010 Cr 0.130 Cu 0.120 Mn 0.980 Mo 0.010 Nb 0.002	
			Ni 0.050 P 0.009 S 0.020 Si 0.250 V 0.004	
			CE(Long Formula) = 0.40	
			T/S(PSI) 74,490 Y/S(PSI) 46,769 EL(%) 36.45 RA(%) 59.34	
			Brinell Hardness 144 BHN 144 BHN	
89590	171	51887	2 3000 A105 90EL T	SA/A105
			Al 0.039 C 0.190 Co 0.006 Cr 0.200 Cu 0.250 Mn 1.010 Mo 0.020 Nb 0.003	
			Ni 0.060 P 0.013 S 0.021 Si 0.225 V 0.020	
			CE(Long Formula) = 0.43	
			T/S(PSI) 78,213 Y/S(PSI) 49,389 EL(%) 35.70 RA(%) 64.61	
			Brinell Hardness 141 BHN 139 BHN	
89632	225	51816 ✓	1 3000 A105 TEE T	SA/A105
			Al 0.024 C 0.210 Co 0.002 Cr 0.120 Cu 0.030 Mn 1.050 Mo 0.004 Nb 0.011	
			Ni 0.020 P 0.007 S 0.022 Si 0.220 V 0.003	
			CE(Long Formula) = 0.41	
			T/S(PSI) 79,568 Y/S(PSI) 50,828 EL(%) 33.80 RA(%) 61.31	
			Brinell Hardness 153 BHN 153 BHN	

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Billie Jo Clemens
Billie Jo Clemens
Quality Assurance Representative