



BONNEY FORGE

## MILL TEST REPORTS

Bonney Forge  
14496 Croghan Pike  
Mt. Union, PA 17066

## CERTIFIED MILL TEST REPORT

DNOW 5/13/2025

LOT NO.

52053

CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS

3-36 X 1" 3M A105 Thredolet™ Threaded

|                                                         |       |    |       |    |       |    |       |    |       |
|---------------------------------------------------------|-------|----|-------|----|-------|----|-------|----|-------|
| C                                                       | 0.210 | MN | 1.040 | P  | 0.007 | S  | 0.022 | SI | 0.210 |
| NI                                                      | 0.020 | CR | 0.110 | MO | 0.003 | CU | 0.060 | CO | 0.002 |
| V                                                       | 0.003 | AL | 0.025 | Nb | 0.010 |    |       |    |       |
| CE(LONG FORMULA)= 0.412                                 |       |    |       |    |       |    |       |    |       |
| T/S(PSI) 80471 Y/S(PSI) 50762 EL(%) 30.050 RA(%) 60.160 |       |    |       |    |       |    |       |    |       |
| BRINELL HARDNESS 156, 156                               |       |    |       |    |       |    |       |    |       |

1. CERTIFYING ASTM A105-21 / ASME SA105-21 EDITION.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2.
3. THE MATERIAL SUPPLIED WAS INSPECTED AND MANUFACTURED IN ACCORDANCE WITH EN DIN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT.
4. THE ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.

THIS DOCUMENT HAS BEEN ELECTRONICALLY SUBMITTED.

|        |        |
|--------|--------|
| Cancel | Logout |
|--------|--------|