

8 std tee y52

979940



TECTUBI RACCORDI S.p.A.

Via Roma 150, 29027 Podenzano (PC), Italy

mail: info@tectubiraccordi.com

Tel: ++39 0523555111

Fax: ++39 0523555118

INSPECTION CERTIFICATE EN 10204 - 2004

☒ 3.1 ☐ 3.2

NUMBER 152404 -1

REVISION 0

DATE 30/03/2018

ORDER:

60717713

JOB:

CLIENT ITEM	ITEM	Qty	DESCRIPTION	HEAT	SPECIFICATION	MATERIAL	STEEL MAKER	CERT.N.	RAW MATERIAL
110	110	780	EQ. TEE BW 8" SCH. STD - SMLS Product Code: 5PTB8-T18	978940	ASTM A850/A850M-10 ASME B850/B850M-10 MSS SP-75 Ed. 2008	WPHY52	TENARIS DALMINE	01/17/14821	PIPE

CHEMICAL COMPOSITION

☒ BY LADLE ANALYSIS *☒ BY CHECK ANALYSIS 0 **

HEAT	Test	C	Mn	Si	P	S	Cr	Ni	Ti	Cu	V	Nb	Mo	Al	V+Nb	CE	B	Cu+Ni+Cr+Mo
	min.		1.00	0.15														
	max.	0.20	1.45	0.40	0.03	0.01	0.30	0.50	0.05	0.35	0.10	0.04	0.25	0.06	0.12	0.42	0.0010	1.00
978940	LADLE	0.120	1.250	0.330	0.013	0.001	0.110	0.130	0.002	0.130	0.070	0.016	0.010	0.032	0.086	0.384	0.000	0.38
979940	CHECK	0.130	1.260	0.330	0.013	0.001	0.110	0.130	0.002	0.130	0.070	0.016	0.010	0.032	0.086	0.395	0.000	0.38

The chemical values and tensile properties are a true and correct copy of the certificate issued by the supplier of raw materials or by the laboratory which has determined them.

MECHANICAL PROPERTIES

☐ ON RAW MATERIAL *☒ ON FINISHED FITTINGS **☐ SUPPLEMENTARY REQ. ***

Tensile Test	Temp. °C	Y.S.	U.T.S.	E%	Impact Test	Temp. °C	KCV	Shear Area	Lt. Exp.	Hardness	Red.	REMARKS
		MPA	MPA		Sens. Direct		(Joule)	%	mm	HBW	Area %	
	min.	360	455	25		min.	28		min.	min.		
	max.	465	525			average	34		max.	235		
380641	381	585	35.3	L	10 x 7.5	128 - 123 - 120	85 - 85 - 80	1.64 - 1.55 - 1.59	159 ± 168	67.43		Melting process: Electric Furnace Manufacturing method: Cold Formed Heat treatment: Normalised at 820°C (1H/1" WTH) still air cooling Visual and dimensional examination in accordance with: ASME B16.9 - Ed. 2012 ASME B16.25 - Ed. 2012

ACTIVITIES

CERTIFICATE

RESULT

ACTIVITIES

CERTIFICATE

RESULT

Material according to:

NACE MR 01-75 ISO 15156 & NACE MR 01-03 Latest Edition

Ultrasonic Examination of Wth. Through the Body: Satisfactory

MT on the weld area performed with satisfactory results

All material supplied is certified to be free of mercury contamination & no mercury bearing equipment was used during manufacturing

Work inspector

Customer Inspector

Third part Inspector

DATE

SIGNATURE

DATE

SIGNATURE

DATE

SIGNATURE

We hereby certify that the materials listed below have been manufactured in compliance with the order and mentioned rules.

☒ EU DIRECTIVE 97/23/EC ANNEXE I SECT. 4.3 & 7.5