

8512 tee Y52

979940



TECTUBI RACCORDI S.p.A.

Via Roma 150, 20027 Podenzano (PO), Italy

mail: info@tectubiraccordi.com

Tel: ++39 0523555111

Fax: ++39 0523555318

INSPECTION CERTIFICATE EN 10204 - 2004

☒ 3.1 ☐ 3.2

NUMBER 152404 -1

REVISION 0

DATE 30/03/2010

ORDER:

60717T13

JOB:

CLIENT ITEM	ITEM	Qty	DESCRIPTION	HEAT	SPECIFICATION	MATERIAL	STEEL MAKER	CERT.N.	RAW MATERIAL
110	110	780	EQ. TEE BW 8" SCH. STD - SMLS Product Code: 5PT68-T13	979840	ASME B16.9-2009-10 ASME B16.9-2009-10 MSS SP-75 Ed. 2008	WPHY52	TENARIS DALMINE	01/17/14821	PIPE

CHEMICAL COMPOSITION																			
☒ BY LADLE ANALYSIS *										☒ BY CHECK ANALYSIS 0 **									
HEAT	Test	C	Mn	Si	P	S	Cr	Ni	Ti	Cu	V	Nb	Mo	Al	V+Nb	CE	B	Cu+Ni+Cr+Mo	
	min.		1.00	0.15															
	max.	0.20	1.45	0.40	0.03	0.01	0.30	0.50	0.05	0.35	0.10	0.04	0.25	0.06	0.12	0.42	0.0010	1.00	
979840	LADLE	0.120	1.250	0.330	0.013	0.001	0.110	0.130	0.002	0.130	0.070	0.016	0.010	0.032	0.086	0.384	0.000	0.38	
979940	CHECK	0.130	1.260	0.330	0.013	0.001	0.110	0.130	0.002	0.130	0.070	0.016	0.010	0.032	0.086	0.395	0.000	0.38	

The chemical values and tensile properties are a true and correct copy of the certificate issued by the supplier of raw materials or by the laboratory which has determined them.

MECHANICAL PROPERTIES

Tensile Test

Temp. °C: +20

Impact Test

☐ ON RAW MATERIAL *

Temp. °C: -46

☒ ON FINISHED FITTINGS **☐ SUPPLEMENTARY REQ. ***

	Y.S. MPA	U.T.S. MPA	E%	Sens. Direct.	Dim. Sample	KCV (Joule)	Shear Area %	Lol. Exp. mm	Hardness HBW	Red. Area %
	min.	360	455	25		min. 28		min. 0.53	min.	
	max.	465	625			average 34			max. 235	
380641	381	585	35.3	L	10 x 7.5	128 - 123 - 120	85 - 85 - 80	1.64-1.55-1.69	159 + 168	67.43

REMARKS

Melting process: Electric Furnace
Manufacturing method: Cold Formed
Heat treatment: Normalised at 820°C (1H/1" WTH) still air cooling

Visual and dimensional examination in accordance with:
ASME B16.9 - Ed. 2012
ASME B16.25 - Ed. 2012

Material according to:
NACE MR 01-75 ISO 15156 & NACE MR 01-03 Latest Edition

Ultrasonic Examination of Wth. Through the Body: Satisfactory

MT on the catch area performed with satisfactory results

All material supplied is certified to be free of mercury contamination & no mercury bearing equipment was used during manufacturing

ACTIVITIES

CERTIFICATE

RESULT

ACTIVITIES

CERTIFICATE

RESULT

Work inspector

Customer inspector

Third part inspector



DATE

SIGNATURE

DATE

SIGNATURE

DATE

SIGNATURE

We hereby certify that the materials listed below have been manufactured in compliance with the order and mentioned rules.

☒ EU DIRECTIVE 97/23/EC ANNEX I SECT. 4.3 & 7.5