



6600 South Harlem Avenue  
Argo, IL 60501-1930

WELDBEND CORPORATION  
PO Box 40385  
Houston, TX  
PO: 26681917

## Material Test Report

| Quantity | Product                       |          |          |           |           |           |           |           |          |           | Heat Code | Heat Treatment         |           |                 |              |              |              |            |            |             |                                                  | Steel Mill        |
|----------|-------------------------------|----------|----------|-----------|-----------|-----------|-----------|-----------|----------|-----------|-----------|------------------------|-----------|-----------------|--------------|--------------|--------------|------------|------------|-------------|--------------------------------------------------|-------------------|
| 15       | 3" Class 900 Weld Neck XSB RF |          |          |           |           |           |           |           |          |           | 1A757     | Heat Treat: Normalized |           |                 |              |              |              |            |            |             |                                                  | CMC STEEL         |
| <u>C</u> | <u>Mn</u>                     | <u>P</u> | <u>S</u> | <u>Si</u> | <u>Cu</u> | <u>Ni</u> | <u>Cr</u> | <u>Mo</u> | <u>V</u> | <u>Al</u> | <u>Ti</u> | <u>B</u>               | <u>Cb</u> | <u>CE (IIW)</u> | <u>Tens.</u> | <u>Yield</u> | <u>Elong</u> | <u>ROA</u> | <u>BHN</u> | <u>BHN2</u> | A 105-18<br>Dimensional Specification: B16.5     |                   |
| L 0.20   | 1.05                          | 0.012    | 0.024    | 0.20      | 0.22      | 0.09      | 0.10      | 0.020     | 0.00     | 0.002     | 0.001     | 0.0002                 | 0.001     | 0.420           | 80,600       | 50,000†      | 29.00        | 47.00      | 159        | 158         | A 105                                            |                   |
|          |                               |          |          |           |           |           |           |           |          |           |           |                        |           |                 |              |              |              |            |            |             |                                                  |                   |
| 4        | 4" Class 900 Weld Neck XSB RF |          |          |           |           |           |           |           |          |           | JE8       | Heat Treat: Normalized |           |                 |              |              |              |            |            |             |                                                  | CMC STEEL         |
| <u>C</u> | <u>Mn</u>                     | <u>P</u> | <u>S</u> | <u>Si</u> | <u>Cu</u> | <u>Ni</u> | <u>Cr</u> | <u>Mo</u> | <u>V</u> | <u>Al</u> | <u>Ti</u> | <u>B</u>               | <u>Cb</u> | <u>CE (IIW)</u> | <u>Tens.</u> | <u>Yield</u> | <u>Elong</u> | <u>ROA</u> | <u>BHN</u> | <u>BHN2</u> | A 105-23<br>Dimensional Specification: B16.5     |                   |
| L 0.19   | 1.00                          | 0.008    | 0.018    | 0.22      | 0.28      | 0.08      | 0.04      | 0.022     | 0.00     | 0.000     | 0.000     | 0.0005                 | 0.001     | 0.393           | 79,600       | 47,600       | 31.10        | 59.00      | 154        | 154         | A 105                                            |                   |
|          |                               |          |          |           |           |           |           |           |          |           |           |                        |           |                 |              |              |              |            |            |             |                                                  |                   |
| 432      | 2" XSLR 90° Elbow             |          |          |           |           |           |           |           |          |           | A230523   | Hot Formed             |           |                 |              |              |              |            |            |             |                                                  | MICHIGAN SEAMLESS |
| <u>C</u> | <u>Mn</u>                     | <u>P</u> | <u>S</u> | <u>Si</u> | <u>Cu</u> | <u>Ni</u> | <u>Cr</u> | <u>Mo</u> | <u>V</u> | <u>Al</u> | <u>Ti</u> | <u>B</u>               | <u>Cb</u> | <u>CE (IIW)</u> | <u>Tens.</u> | <u>Yield</u> | <u>Elong</u> | <u>ROA</u> | <u>BHN</u> | <u>BHN2</u> | A 234-18 WPB<br>Dimensional Specification: B16.9 |                   |
| L 0.18   | 0.71                          | 0.005    | 0.010    | 0.21      | 0.12      | 0.06      | 0.06      | 0.020     | 0.00     | 0.020     | 0.000     | 0.0000                 | 0.000     | 0.325           | 70,400       | 50,000†      | 23.40        | -          | 150        | 155         | SEGM<br>WPB                                      |                   |

We hereby certify that the material meets the following:

- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MRO-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WPB (AND SA-234)
- All non high-yield flanges meet the requirements of ASTM A-105 WPB (AND SA-105)
- All elbows, tees and reducers are seamless, except as noted.
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.

- Bars, Billets or Blooms for flanges and certain caps and tees.
- MTR only valid with QR code linking to traceability.weldbend.com

† This indicates that the reported yield is capped at 50,000 psi.  
Copyright © 2023 Weldbend Corp.

Richard Purpura

Richard Purpura  
Quality Assurance Department  
11/16/2024



Scan For Online  
Report

We hereby certify that the material meets the following:

- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content, No Mercury Content.
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1

Generated by kcoulas@weldbend.com

Page 1 of 4

Cert #402923