



2750 HOLMES RD.
HOUSTON, TEXAS 77051 USA
TEL: (713) 799-9235

CERTIFICATE OF CONFORMANCE

DATE :
CUSTOMER:
CUSTOMER PO#:

March 14, 2025
ALLOY PIPING PRODUCTS
419718

[illegible]

WE HEREBY CERTIFY THAT TO THE BEST OF OUR KNOWLEDGE THE MATERIAL CALLED FOR ON THE ABOVE ORDER COMPLIES WITH AND WAS PURCHASED IN ACCORDANCE WITH THE SPECIFICATIONS REQUIRED.

Jesus D. Serrano

Digitally signed by Jesus D. Serrano
DN: CN=Jesus D. Serrano, E=jesusse@texaspipe.com
Reason: I am the author of this document
Location:
Date: 2025.03.19 11:18:10-05'00'
Foxit PDF Editor Version: 2024.4.1

AUTHORIZED SIGNATURE

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 05/21/24
Time: 15:24:24
Page: 1/3

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 18047
Heat Number	Item Number	Item Description	Quantity	
BC6861-1011395	6-M4-M-ISZCTBAP	6 X 4 T XH WPHY52 A860/MSS SP-75		

Starting Material	Seamless Pipe
-------------------	---------------

Order Spec:				
Item Spec:	ASTM A860 2022	MSS SP-75 2019		

Result ID: 1 Heat Analysis		Chemical Composition (wt%)					
Element	Content	Element	Content	Element	Content	Element	Content
C	0.1400	Mn	1.4100	P	0.0170	S	0.0022
Ni	0.0230	Cr	0.0790	Mo	0.0110	Cu	0.0760
Nb	0.0400	Ti	0.0250	Al	0.0300	B	0.0005
						Si	0.3600
						V	0.0051

Summary Results							
CE	0.40	Sum CuNiCrMo	0.1890	Sum Cr+Mo	0.0900	Sum Nb+V	0.0451
						MN/C RATIO	10.0714

Result ID: 2 Product Analysis		Chemical Composition (wt%)					
Element	Content	Element	Content	Element	Content	Element	Content
C	0.1300	Mn	1.4200	P	0.0170	S	0.0060
Ni	0.0300	Cr	0.0800	Mo	0.0200	Cu	0.0700
Nb	0.0400	Ti	0.0200	Al	0.0300	B	0.0002
						Si	0.3400
						V	0.0100

Summary Results							
CE	0.40	Sum CuNiCrMo	0.2000	Sum Cr+Mo	0.1000	Sum Nb+V	0.0500
						MN/C RATIO	10.9231

TEST RESULTS			
Work Order: 1011395	Load Designation:	Test Set:	

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 05/21/24
Time: 15:24:24
Page: 2/3

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 18047
Heat Number	Item Number	Item Description		Quantity
BC6861-1011395	6-M4-M-ISZCTBAP	6 X 4 T XH WPHY52 A860/MSS SP-75		

Result ID: 1		Charpy Test		
Specimen Size: .394 X .394 In		Test Temperature: 20 °F		
Sample Area: Base		Location: 1/2 T Longitudinal		
	Sample 1	Sample 2	Sample 3	
Shear(%)	72	70	70	Average Shear: 71
Absorbed Energy(ft-lbs)	158	164	160	Avg Absorbed Energy: 161 Minimum Absorbed Energy: 158
Lateral Expansion (In):	0.053	0.053	0.055	

Result ID: 2		Charpy Test		
Specimen Size: .394 X .394 In		Test Temperature: -50 °F		
Sample Area: Base		Location: 1/2 T Longitudinal		
	Sample 1	Sample 2	Sample 3	
Shear(%)	68	70	65	Average Shear: 68
Absorbed Energy(ft-lbs)	144	148	142	Avg Absorbed Energy: 145 Minimum Absorbed Energy: 142
Lateral Expansion (In):	0.050	0.051	0.049	

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 05/21/24
Time: 15:24:24
Page: 3/3

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 18047
Heat Number	Item Number	Item Description		Quantity
BC6861-1011395	6-M4-M-ISZCTBAP	6 X 4 T XH WPHY52 A860/MSS SP-75		

Result ID: 1		Tensile Test	
Specimen type: Longitudinal Rectangular		Gauge Length: 2.00 In	
Tensile Strength: 81.8 KSI		Yield Strength: 61.1 KSI	
Elongation: 33.2 %		Reduction:	

Result ID: 1		Hardness Test	
Hardness: 150 - 158 HBW			

SUPPLEMENTAL INFORMATION

Bevels in accordance with ASME B16.25, unless noted otherwise.

Dimensions and tolerances in accordance with the latest edition of ASME B16.9.

Material, when shipped, is free from contamination by mercury, radium, alpha source and low melting elements.

Material supplied in accordance with a Quality Management System certified to ISO:9001-2015. CERTIFICATE NUMBER: Q1674

Hardness is acceptable in accordance with NACE MR0175-2021/ISO 15156:2020 and MR0103/ISO 17945:2015
We hereby certify that the materials listed above have been manufactured, sampled, tested and inspected in accordance with specifications and grade listed, and have been found to meet the requirements.

Heat Treat Statement:
Quenched at 1652°F / Tempered at 1202°F

Starting Material Manufacturer: Heng Yang Valin, China, (Heat: 20304408)
Forming / Heat Treat: Sivanandha, India

Stacy Bellow
QA Manager

05/17/24
Date