

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 06/21/24
Time: 15:23:18
Page: 1/4

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 19899
Heat Number	Item Number	Item Description		Quantity
BD5203-1013372	12M----ISZC7BAP	12 CAP XH WPHY52 A860/MSS SP-75		

Starting Material	Plate
-------------------	-------

Order Spec:				
Item Spec:	ASTM A860 2022	MSS SP-75 2019		

Result ID: 1 Heat Analysis		Chemical Composition (wt%)					
Element	Content	Element	Content	Element	Content	Element	Content
C	0.1800	Mn	1.3000	P	0.0180	S	0.0020
Ni	0.0100	Cr	0.0100	Mo	0.0010	Cu	0.0400
Nb	0.0230	Ti	0.0020	Al	0.0300	B	0.0004
						Si	0.2200
						V	0.0010

Summary Results							
CE	0.40	Sum CuNiCrMo	0.0610	Sum Cr+Mo	0.0110	Sum Nb+V	0.0240
						MN/C RATIO	7.2222

Result ID: 2 Product Analysis		Chemical Composition (wt%)					
Element	Content	Element	Content	Element	Content	Element	Content
C	0.1700	Mn	1.3100	P	0.0180	S	0.0010
Ni	0.0000	Cr	0.0200	Mo	0.0020	Cu	0.0100
Nb	0.0260	Ti	0.0030	Al	0.0350	B	0.0005
						Si	0.2200
						V	0.0010

Summary Results							
CE	0.39	Sum CuNiCrMo	0.0320	Sum Cr+Mo	0.0220	Sum Nb+V	0.0270
						MN/C RATIO	7.7059

TEST RESULTS			
Work Order:	1013372	Load Designation:	Test Set:

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 06/21/24
Time: 15:23:18
Page: 2/4

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 19899
Heat Number	Item Number	Item Description		Quantity
BD5203-1013372	12M----ISZC7BAP	12 CAP XH WPHY52 A860/MSS SP-75		

Result ID: 1		Charpy Test		
Specimen Size: .394 X .394 In		Test Temperature: 20 °F		
Sample Area: Base		Location: 1/2 T Transverse		
	Sample 1	Sample 2	Sample 3	
Shear(%)	70	72	71	Average Shear: 71
Absorbed Energy(ft-lbs)	181	184	183	Avg Absorbed Energy: 183 Minimum Absorbed Energy: 181
Lateral Expansion (In):	0.040	0.043	0.041	

Result ID: 2		Charpy Test		
Specimen Size: .394 X .394 In		Test Temperature: -50 °F		
Sample Area: Base		Location: 1/2 T Longitudinal		
	Sample 1	Sample 2	Sample 3	
Shear(%)	68	69	68	Average Shear: 68
Absorbed Energy(ft-lbs)	162	165	159	Avg Absorbed Energy: 162 Minimum Absorbed Energy: 159
Lateral Expansion (In):	0.036	0.038	0.038	

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 19899
Heat Number	Item Number	Item Description		Quantity
BD5203-1013372	12M----ISZC7BAP	12 CAP XH WPHY52 A860/MSS SP-75		

Result ID: 1		Tensile Test	
Specimen type: Transverse Rectangular		Gauge Length: 2.00 In	
Tensile Strength: 82.7 KSI		Yield Strength: 61.2 KSI	
Elongation: 34.4 %		Reduction:	

Result ID: 1	Hardness Test
Hardness: 169 – 172 HBW	

ALLOY PIPING PRODUCTS
740 NORTH MARKET STREET SHREVEPORT, LA 71107
Phone: (318)674-9860

Printed on: 06/21/24
Time: 15:23:18
Page: 4/4

Sold to:		Ship To:		
Sales Order #		Cust PO #		Book ID 19899
Heat Number	Item Number	Item Description	Quantity	
BD5203-1013372	12M-----ISZC7BAP	12 CAP XH WPHY52 A860/MSS SP-75		

SUPPLEMENTAL INFORMATION

Bevels in accordance with ASME B16.25, unless noted otherwise.

Dimensions and tolerances in accordance with the latest edition of ASME B16.9.

Material, when shipped, is free from contamination by mercury, radium, alpha source and low melting elements.

Material supplied in accordance with a Quality Management System certified to ISO:9001-2015. CERTIFICATE NUMBER: Q1674

Hardness is acceptable in accordance with NACE MR0175-2021/ISO 15156:2020 and MR0103/ISO 17945:2015

We hereby certify that the materials listed above have been manufactured, sampled, tested and inspected in accordance with specifications and grade listed, and have been found to meet the requirements.

Magnetic Particle Examination in accordance with Supplemental Requirement S53 of ASTM A960. No relevant indications found at time of inspection.

Heat Treat Statement:
Quenched at 1652°F and tempered at 1202°F

Starting Material Manufacturer: Jindal Steel, India (Heat: A25334)
Forming / Heat Treat: Sivanandha Pipe Fittings Ltd., India

Stacy Bellow
QA Manager

06/21/24
Date