

# CERTIFIED MILL TEST REPORT



The Best Value -  
Price, Quality, Service  
All The Time.

LOG NO. F00000000213443

Page 3 of 7

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: DNOW L.P.

DATE 12/10/2024

CUSTOMER

BONNEY ORDER NO. B000355839

ORDER NO.: 26687287

SHIP TO: DNOW L.P. (ODESSA)  
5301 WEST MURPHY STREET  
ODESSA TX 79763  
United States

| ITEM   | QUANTITY | LOT NO. | GRADE OR SPECIFICATION NO.<br>CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS: |         |
|--------|----------|---------|--------------------------------------------------------------------------------|---------|
|        |          |         |                                                                                |         |
| 89562  | 10 ✓     | D957 ✓  | 1 3000 A105 COUPT                                                              | SA/A105 |
|        |          |         | Al 0.023 C 0.200 Co 0.006 Cr 0.150 Cu 0.180 Mn 1.050 Mo 0.020 Nb 0.005         |         |
|        |          |         | Ni 0.060 P 0.011 S 0.019 Si 0.187 V 0.020                                      |         |
|        |          |         | CE(Long Formula) = 0.43                                                        |         |
|        |          |         | T/S(PSI) 73,600 Y/S(PSI) 50,100 EL(%) 46.00 RA(%) 51.00                        |         |
|        |          |         | Brinell Hardness 158 BHN 159 BHN                                               |         |
| 145279 | 11       | 51979   | 36-3/4X1/2 3000 A105 FLEX T                                                    | SA/A105 |
|        |          |         | Al 0.021 C 0.200 Co 0.010 Cr 0.130 Cu 0.120 Mn 0.980 Mo 0.010 Nb 0.002         |         |
|        |          |         | Ni 0.050 P 0.009 S 0.020 Si 0.250 V 0.004                                      |         |
|        |          |         | CE(Long Formula) = 0.40                                                        |         |
|        |          |         | T/S(PSI) 74,490 Y/S(PSI) 46,769 EL(%) 36.45 RA(%) 59.34                        |         |
|        |          |         | Brinell Hardness 144 BHN 144 BHN                                               |         |
| 89590  | 12       | 51887   | 2 3000 A105 90EL T                                                             | SA/A105 |
|        |          |         | Al 0.039 C 0.190 Co 0.006 Cr 0.200 Cu 0.250 Mn 1.010 Mo 0.020 Nb 0.003         |         |
|        |          |         | Ni 0.060 P 0.013 S 0.021 Si 0.225 V 0.020                                      |         |
|        |          |         | CE(Long Formula) = 0.43                                                        |         |
|        |          |         | T/S(PSI) 78,213 Y/S(PSI) 49,389 EL(%) 35.70 RA(%) 64.61                        |         |
|        |          |         | Brinell Hardness 141 BHN 139 BHN                                               |         |
| 89632  | 13 ✓     | 51816 ✓ | 1 3000 A105 TEE T                                                              | SA/A105 |
|        |          |         | Al 0.024 C 0.210 Co 0.002 Cr 0.120 Cu 0.030 Mn 1.050 Mo 0.004 Nb 0.011         |         |
|        |          |         | Ni 0.020 P 0.007 S 0.022 Si 0.220 V 0.003                                      |         |
|        |          |         | CE(Long Formula) = 0.41                                                        |         |
|        |          |         | T/S(PSI) 79,568 Y/S(PSI) 50,828 EL(%) 33.80 RA(%) 61.31                        |         |
|        |          |         | Brinell Hardness 153 BHN 153 BHN                                               |         |

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Billie Jo Clemens  
Billie Jo Clemens  
Quality Assurance Representative