



DL FLANGE

DL Flange
7200 Mykawa Rd.
Houston, TX 77033



ISO 9001

CERTIFIED MATERIAL TEST REPORT EN 10204 3.1

Date of Report: 06/11/2026 **Certificate No.** 30026784 Page 1 of 2

Customer: EDGEN MURRAY CORP.
PO BOX 84160
Baton Rouge, LA 70884-4160

Cust PO#: STL - 328792 **PO Line#:** 3
Customer Order No: WOSO1214642-5 **Qty:** 2.00
Allied Fitting, LP SO No: SOM1104735

Item Description: L9BR4 4 900# RF BLD A105
Specification: ASTM A105/A105M-26 / ASME SA105/SA105M-25
Heat C.E.: 0.41

Heat #: DL86224
Melt Practice: ELECTRIC FURNACE

Heat Treatment	Init Temperature	Tempering Temperature	Time
NORMALIZED	1,700 F	0 F	N=2.00HRS

Heat Composition

Heat Product	C 0.20	Mn 1.24	Si 0.25	P 0.014	S 0.008	Cr 0.03	Ni 0.01
Heat Product	Mo 0.00	Cu 0.01	V 0.00				

Mechanical Properties

Tensile Specimen Size: STD

Tensile Specimen Orientation:

Impact Specimen Size: 10 X 10

Impact Specimen Orientation: T

	Hardness	Ultimate Strength	Yield Strength	Elongation	Area Reduction
Base Weld HAZ	154 156 HBW	511 Mpa	359 Mpa	36 %	71 %

CHARPY IMPACT TEST

	Impact Value	Shear Fracture	Lateral Expansion	Temperature
Base Value	J 58 62 57	% 54 52 56	MM 0.03 0.03 0.03	-46.00 °C

Notes

ANSI/NACE MR0103-2015/ISO 17945:2015(R2023)
ANSI/NACE MR0175-2021/ISO 15156:2020+ERR:2025
DOMESTIC

Remarks

FULLY KILLED MADE TO FINE GRAIN PRACTICE



DL FLANGE

DL Flange
7200 Mykawa Rd.
Houston, TX 77033



ALLIED GROUP

ISO 9001

CERTIFIED MATERIAL TEST REPORT EN 10204 3.1

Date of Report: 06/11/2026

Certificate No. 30026784

Page 2 of 2

Material in accordance with the latest edition of the applicable Standard to which it is ordered including:

ASME Sect II-A, ASME B16.5, B16.36, B16.47, MSS-SP-44.

NO WELD REPAIR
FREE

MERCURY FREE RADIATION CONTAMINATION

Material conforms to both ASTM (A) and ASME (SA) applicable specifications.
We hereby certify that all information presented on this CMTR conforms to the above specification.

Troy Gorrell

Q.C Inspector