

Heat: R2493
Your PO: 662785189

Order: 4007515 Line: 1
Item: 10" 900# RF BL FLANGE A/SA105



RD FORGE PRIVATE LIMITED

MANUFACTURER & EXPORTER OF STEEL FORGINGS

AN ISO - 9001, PED, AD 2000 MERKBLATTWO & UKCA CERTIFIED CO.

Office : 13, Navyug Market, Ghaziabad-201001

Works : Khasra No. 1202/5, Village: Khera Dehat, Dhaulana Road,

Pilkhuwa-245304 Distt. Hapur (UP)

E-mail : info@rdforge.com Website : www.rdforge.com

MATERIAL TEST REPORT

EN 10204 TYPE 3.1

Certificate No. 10274	Dt: 22.01.2025	Inspection Agency: RDF	W.O. No.: 1277
Client: DODSON GLOBAL.		P.O. No.: 382002	P.O. Dt: 17.03.2024
		Invoice No.: RDF/E/M/0091	Invoice Dt: 22.01.2025
Material Specification: ASTM A105-2023 / SA 105 ASME SEC II PART A-2023 "FULLY KILLED STEEL" "FINE-GRAIN PRACTICE"			Order Status: Complete

We certify that the material detailed below meets the requirement of the purchase order/relevant specification

Item No	PO. S. NO.	Description	Heat No.	Qty.	H.T. Condition	H.T Temp	P/C
5.	22.	14" 600 RF SO FLANGE (150-200 AARH)	R2487	05	NORMALISED	910°C	C
6.	26.	10" 900 RF BL FLANGE (150-200 AARH)	R2493	15	NORMALISED	910°C	C


(DIMENSION AS PER ASME B16.5-2020)

CHEMICAL COMPOSITION (in percentage)

Heat No.	C	Mn	P	S	Si	Ni	Cr	Mo	V	Cu	Nb/Cb.	Al	CE	Cast No.
Req. Min.		0.60		0.040	0.10		0.30	0.12	0.08	0.40			0.43	
Req. Max.	0.27	1.35	0.035		0.35	0.40								
				LADDLE ANALYSIS										
	0.182	0.84	0.027	0.018	0.25	0.02	0.07	0.003	0.004	0.04	0.007	0.022	0.341	24K 1256
	0.184	0.82	0.024	0.009	0.25	0.02	0.11	0.005	0.006	0.04	0.008	0.026	0.349	24K 1642
				PRODUCT ANALYSIS										
R2487	0.192	0.85	0.025	0.016	0.24	0.03	0.05	0.004	0.003	0.05	0.006	0.024	0.350	24K 1256
R2493	0.192	0.84	0.025	0.007	0.26	0.03	0.12	0.004	0.004	0.03	0.009	0.025	0.362	24K 1642

MECHANICAL / PHYSICAL PROPERTIES

Heat No.	YS P.S 10.2% Offset method	UTS P.S. I	El% GL=4XD	RA %	HARDNESS BHN	Bend	Charpy V- notch - Impact Test Test Temp. °C (Joules) T.P. SIZE=10X10X55X2MM CVN	Remarks
Req. Min.	36000	70000	22	30	187			
Req. Max.								
R2487	48010	75919	29.60	55.91	150, 151	--	--	--
R2493	46827	76392	29.20	56.96	149, 152	--	--	--



Remarks

1. Steel-making process: Electric Melting Furnace- Refining with Argon Purging in Ladle. For Cast No. 24K 1256 & 24K 1642.
2. We certify that material is free from Mercury contamination and that no mercury-bearing equipment's used during manufacturing.
3. Material forged in single piece & no weld repair has been done.
4. Material conforms to NACE MR0175-2015.
5. Country of origin, melt and pour: INDIA