



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

WELDBEND CORPORATION
6600 S HARLEM AVE
ARGO, IL 60501
PO: SO83452

<u>Quantity</u>		<u>Product</u>								<u>Heat Code</u>				<u>Heat Treatment</u>				<u>Steel Mill</u>			
2		8" Std LR 90 Deg ELBOWS-HY 52								25N288				Heat Treat: Normalized				V & M STAR			
<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>	<u>Al</u>	<u>Ti</u>	<u>B</u>	<u>Cb</u>	<u>CE (SP75)</u>	<u>Tens.</u>	<u>Yield</u>	<u>Elong</u>	<u>ROA</u>	<u>BHN</u>	<u>BHN2</u>	SP75 WPHY 52-08 Dimensional Specification: SP75 
0.17	1.21	0.011	0.003	0.30	0.10	0.04	0.06	0.010	0.07	0.026	0.004	0.0003	0.000	0.407	82,300	53,600	38.40	73.70	156	160	
0.11	1.14	0.012	0.008	0.28	0.11	0.05	0.06	0.010	0.06	0.030	0.005	0.0005	0.005								

Melted And Manufactured in The USA

Test Temperature: -50 °F Percent Shear: 44/100/40 Average: 61
Absorbed Energy (ft/lbs): 50/72/45 Average: 56
Lateral Expansion (mils): 63/53/52 Average: 56

We hereby certify that the material meets the following

- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision.
- All fittings and flanges meet NACE MRO-103 - Latest Revision.
- All non high-yield fittings meet the requirements of ASTM A-234 WPB / ASME SA-234
- All non high-yield flanges meet the requirements of ASTM A-105 WPB / ASME SA-105
- All elbows, tees and reducers are seamless, except as noted.
- Plate for caps and welded fittings.
- Bars, Billets or Blooms for flanges and certain caps and tees.

• MTR only valid with QR code linking to traceability.weldbend.com
† This indicates that the reported yield is capped at 50,000 psi.

Copyright © 2025 Weldbend Corp.

Cert #449050

Richard Purpura

Richard Purpura
Quality Assurance Department
6/23/2026



Scan For Online
Report

We hereby certify that the material meets the following:

- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content.
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability.
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1

Generated by mcabada

Page 1 of 1