



2669 Martin Luther King Jr Blvd
Youngstown, OH 44510

VALLOUREC STAR LP
Seamless Tubular Products

Certified Test Report
12/26/2024
Revision: 0

Order: Y-221128237-001 Desc: Seamless Line Pipe- Normalized Rolled Customer: MRC Global (US) Inc. SLN / (Heat): ON0213
Grade: API SL X42/B N/BN PSL2 46th Edition May 01, 2019 Customer Order: S 9W7 656855 Split: 00
OD(In): 4.500 Wall(In): 0.337 Lbs/Ft: 15.00 Length: Double Random
End Finish: Plain End Beveled
Comments: Melted and Manufactured in Youngstown, Ohio USA
Pipe is also manufactured to: ASTM A106B/C-19a, ASTM A53B-24, ASME SA106B/C-2023, ASME SA53B-2023. Vallourec Star's QA program meets the requirements of Directive 2014/68/EU and DIN EN10204-2004 Type 3.1.
Satisfies NACE MR0175/ISO15156:2015 and ANSI/NACE MR0103/ISO17945:2015. Material has been produced using silicon killed carbon steel with aluminum fine grain practice.
No repair welding has been conducted. Material is free from Mercury.

Mechanical Properties

		Tensile Size Specimen Cross Section			Strength (ksi)			Elongation		
Orientation	Type	Width (In)	Thick (In)	Area (sqin)	Yield	Tensile	Y/T Ratio	Gage Length	% Elong	% RA
Longitudinal	Strip	0.990	0.360	0.3700	49.6	77.8	0.64	2	36.8	53.8

Required Min/Max Yield Strength (ksi): 42.1/71.8

Required Min/Max Tensile Strength (ksi): 70/95

Calculated Max Internal Yield (psi): 6496

Required Min Elongation(%): 30

Supplemental Requirements

Flattening Test	Passed
Hardness 3 Point	78.3 avg HRRBW
Hydrostatic Pressure	4730 psi
Hydrostatic Hold Time	5 seconds

Chemical Analysis

Chem Spec: 66S

WT%	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Nb	V	Al	Ca	B	Ti	N	C.E.
Heat	0.19	1.08	0.008	0.006	0.25	0.19	0.07	0.12	0.02	0.009	0.000	0.003	0.032	0.0023	0.0005	0.002	0.0092	0.41
Product 3	0.19	1.07	0.010	0.006	0.24	0.18	0.07	0.12	0.02	0.007	0.000	0.002	0.032	0.0024	0.0002	0.002	0.0081	0.41
Product 4	0.19	1.06	0.010	0.005	0.24	0.18	0.07	0.12	0.02	0.007	0.000	0.003	0.030	0.0021	0.0002	0.002	0.0081	0.41

Charpy Impact Testing - Not required per API.

This material has been produced and tested in accordance with the requirements of applicable specifications unless otherwise listed below. We hereby certify that the above test results are representative of those contained in the records of the company. Any modification to this certification as provided by Vallourec Star without the expressed written consent of Vallourec Star negates the validity of this test report. Vallourec Star is not responsible for the inability of this material to meet specific applications.

THIS CERTIFICATE IS NOTARIZED ONLY WHEN REQUESTED.

Signed: *Jourdan Calhoun*

Name: Jourdan Calhoun, Quality Assurance

Date Approved: 12/26/2024

This document is uncontrolled when printed. Always refer to the MTR System for the most current version. FS-VMS-8.2.4.1.1 Rev 7



2669 Martin Luther King Jr Blvd
Youngstown, OH 44510

VALLOUREC STAR LP
Seamless Tubular Products

Certified Test Report
12/26/2024
Revision: 0

Order: Y-221128237-001 Desc: Seamless Line Pipe- Normalized Rolled

Grade: API 5L X42B N/BN PSL2 46th Edition May 01, 2019

OD(In): 4.500

Wall(In): 0.337

Lbs/Ft: 15.00

Length: Double Random

End Finish: Plain End Beveled

Inspection Company: L Bay

Customer: MRC Global (US) Inc.

Customer Order: S 9W7 656855

SLN / (Heat): ON0213

Split: 00

Non-Destructive Evaluation Criteria

UT CHANNELS

ID

10% Longitudinal

10% Transverse

OD

5% Longitudinal

5% Transverse

WALL THICKNESS CHECK

87.5% Wall Reduction

Required Volumetric Coverage: 100%

ADDITIONAL REQUIREMENTS

Notch Length 1.5" Max

Notch Width .020" Max

Untested Ends Cropped

OD

Visual Insp. Full Length - White Light

ID

Visual Insp. Pipe Ends - White Light