

Our Order 2492378-5-1 Your Order 74769-03
Heat PW0071

Packing List 407599-1 (1/21/2026)

Image 556779

Desc Pipe SMLS ASTM A106-B, A333-1/6, API X52, 8.625 x .322 - 8" STD SRL

Job: 74769
PO: 7476903
BOM: 5
Pages: 1
Heat: PW0071



8603 Sheldon Road
HOUSTON, TX 77049

VALLOUREC STAR, LP
Seamless Tubular Products

Certified Test Report
01/14/2026

Order Line #: 0221130249-1	Desc: SEAMLESS QUINCH AND TEMPERED	Customer: EDDEN MURRAY CORP	SML (Heat): PW0071
Grade: API 5L X52 48th Edition May 1, 2018		Customer PO-Rev#: 05-119937-0	W/O Num: 001958
OD (in): 8.625	Wall (in): 0.322	Lot#: P943740	
End Finish: PE	Lot/Pl: 28.58	Length: 045	
Comment: Milled and Manufactured in the USA Vallourec Star's QA program meets the req. of DIN EN 10204-2004 Type 3.1 certifies NACE MR0175 PART 2/ISO 15156-2:2023 & ANSI/NACE MR0175/ISO 17946:2013 X52GL7 ASTM A333-34 01&04, ASME SA333-2023 01&04 ASTM A106-B/15a, ASME SA106-B/15 2023 ASTM A333-34, ASME SA333-2023/MSR-15 19L2			

Mechanical Properties

Orientation	Type	Tensile Size Specimen Cross Section			Strength (ksi)			Elongation	
		Width (in)	Thick (in)	Area (sqin)	Yield	Tensile	Y/T Ratio	Gage Length	%Elong
LONGITUDINAL	STRIP	1.493	0.315	0.4729	71.9	83.8	0.85	2	39.0
LONGITUDINAL	STRIP	1.494	0.346	0.5220	68.8	81.7	0.84	2	40.0
LONGITUDINAL	STRIP	1.493	0.303	0.4548	65.9	82.2	0.85	2	39.0
Calculated Max Internal Yield (psi): 4492									

Supplemental Requirement

Austenitizing Temp	1680 °F
Tempering Temp	1330 °F
Flattening	PASSED
Hardness	SEE ATTACHED
Collapse Min	N/A
Collapse Actual	N/A
Hydrostatic Pressure	3000 5 SEC HOLD
Other	N/A

Chemical Analysis

Chem Spec: 690

NDE SEE ATTACHED

WT%	C	Mn	P	S	Si	Cu	NI	Cr	Mo	Sn	Nb	V	Al	Ca	S	Ti	N	C.E.
HEAT	0.10	1.06	0.007	0.005	0.24	0.18	0.08	0.07	0.02	0.011	0.001	0.044	0.036	0.0019	0.0005	0.002	0.0093	0.32
PRODUCT 1	0.10	1.05	0.008	0.005	0.24	0.18	0.08	0.07	0.02	0.009	0.001	0.045	0.036	0.0017	0.0005	0.008	0.0083	0.32
PRODUCT 2	0.10	1.05	0.007	0.005	0.24	0.17	0.07	0.07	0.02	0.008	0.001	0.045	0.035	0.0016	0.0004	0.003	0.0089	0.31

Charpy Impact Testing

Notch	Direction	Size	Temp °F	Position	P1 Lbf 1	P1 Lbf 2	P1 Lbf 3	P1 Lbf Avg	Shear 1	Shear 2	Shear 3	Shear Avg
Min Target	—	TRANS	1/2	32	—	10	10	10	10			
Actual	V	TRANS	1/2	82	LEAD	110	112	114	112	100	100	100
Min Target	—	TRANS	1/2	-70	—	7	7	7	9			
Actual	V	TRANS	1/2	-70	LONG/L	128	129	123	125	100	100	100
Actual	V			-70	LONG/L	128	123	123	125	100	100	100

NDT Inspection: WMSEA

This material has been produced and tested in accordance with the requirements of applicable specifications unless otherwise stated below. We hereby certify that the above test results are representative of those contained in the records of the company. Any modifications to this certification as provided by Vallourec Star, without the expressed written consent of Vallourec Star, negates the validity of the test report. Vallourec Star is not responsible for the liability of this material to meet specific applications.

Signed:
Name: PETER YANG
Date Approved: 01/14/2026