



6600 South Harlem Avenue
Argo, IL 60501-1930

Material Test Report

WELDBEND CORP.
PO Box 84
Baton Rouge, LA
PO: STL-328795

Quantity		Product								Heat Code				Heat Treatment				Steel Mill		
7		SERIES 4000 8" Std STRAIGHT BAR TEE-Y52								1241396				Heat Treat: Normalized				INTERPIPE NIKO TUBE SP75 WPHY 52-08 Dimensional Specification: SP75		
C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	B	Cb	CE (IIW)	Tens.	Yield	Elong	ROA	BHN	BHN2
L 0.15	1.26	0.014	0.003	0.20	0.21	0.12	0.10	0.014	0.07	0.034	0.002	0.0004	0.001	0.416	101,000	75,600	30.00	79.20	214	215
Fine Grain Practice																				
Y-52																				

Fine Grain Practice

Test Temperature: -50 °F Percent Shear: 100/100/100 Average: 100
Absorbed Energy (ft/lbs): 191/135/156 Average: 161
Lateral Expansion (mils): 87/69/81 Average: 79

Y-52

We hereby certify that the material meets the following

- All fittings and flanges meet NACE MRO-175/ISO 15156-Latest Revision
- All fittings and flanges meet NACE MRO-103 - Latest Revision
- All non high-yield fittings meet the requirements of ASTM A-234 WPB / ASME SA-234
- All non high-yield flanges meet the requirements of ASTM A-105 WPB / ASME SA-105
- All elbows, tees and reducers are seamless, except as noted
- Plate for caps and welded fittings
- Bars, Billets or Blooms for flanges and certain caps and tees
- MTR only valid with QR code linking to traceability.weldbend.com

† This indicates that the reported yield is capped at 50,000 psi

Copyright © 2025 Weldbend Corp.

Cert #446919

Richard Purpura

Richard Purpura
Quality Assurance Department
5/29/2026



Scan For Online
Report

We hereby certify that the material meets the following

- ISO 9001:2015 CERTIFIED MANUFACTURER
- Test Results herein are correct as contained in test records retained by the company in accordance with PED Annex 1, Paragraph 4.3 of 2014/68/EU
- No Weld Repair Performed. No Lead Content. No Mercury Content
- Knowingly making false, fictitious, or fraudulent statements on a MTR may result in legal liability
- Material has been manufactured/supplied and tested in accordance with the most current version of the Weldbend Quality System Program
- MTR issued in accordance with EN 10204 paragraph 3.1

Generated by nkimala@weldbend.com

Page 1 of 1