

16" Pipe



MILL TEST CERTIFICATE

Number: 104788609.0.1
Page: 1/6

Date: May 08, 2023

Customer: Corpac Hickman GPU, 5000 North County Road 967, BLYTHEVILLE, AR 72315

Customer's Order Item: 39041718SO/10

Customer's Reference: 29524

Manufacturer's Works Order N°:

Manufacturing Process: HF W

Product type: Line Pipe

Standard or Specification: API Spec. SL 46th Ed. 04/2018

Steel Grade: X65M PSL 2

Dimensions: 16.000 x 0.500 in

Schedule: N/A

Length: Double Random

Quantity: 13 PCS
549 FT

Ends: Plain End Bevelled
Nominal Weight: 82.85 LB/FT

TENSILE TEST

Heat N°	Sample N°	Zone	Lot N°	Specimen condition			Specimen dimensions		Test temp	V.S.		U.T.S.		Y.S./U.T.S.		Elongation				
				Ls	Sc	Type	Ori	Size		h	F	5% BIL	Req.	U.T.S.	Req. Max	0.93	In	%	Min.	Obt.
213030	17710	E1	213030	B	AM	SA	T	1.500	R.T.	74 681	psi	86 420	psi	0.86	2.0	23.0	34.3	23.0		
223613	17749	E1	223613	B	AM	SA	T	1.500	R.T.	74 018	psi	84 990	psi	0.87	2.0	23.0	34.3	23.0		
223938	17714	E1	223938	B	AM	SA	T	1.500	R.T.	72 299	psi	85 117	psi	0.88	2.0	23.0	34.3	23.0		

AM: As manufactured
B: Body
E1 / E2: Ends of Sampling
Lo: Initial length
LS: Location of sample
Max: Maximum
Min: Minimum
OH: Orientation
Req. Max: Required maximum
Req. Required
RT: Room temperature
SC: Specimen condition
SS: Strip specimen
T: Transversal
U.T.S.: Ultimate tensile strength
Y.S.: Yield strength

Heat N°	Sample N°	Zone	Lot N°	Specimen condition				Specimen dimensions		Test temp	U.T.S. Req.	Elong. Max: 110 200
				Ls	Sc	Type	Ori	Size	h			
213030	17710	E1	213030	W	AM	SA	T	1.300		R.T		
213613	17749	E1	213613	W	AM	SA	T	1.300		R.T		
213938	17714	E1	213938	W	AM	SA	T	1.500		R.T		

AM: As manufactured

Min: Minimum

SC: Specimen condition

W: Weld

This certificate is issued by a computerized system and is valid with electronic signature. On this original certificate the trade-mark green colored "Tenaris" is stamped. In case of any doubt, the original certificate would release a copy of it. It must attest its conformity to the original one taking upon himself the responsibility for any fraud or not allowed use. Any alteration would nullify this certificate and will be subjected to the law.

MANAGER TUBE CORPORATION
3025 S. 28th St. Suite 100
Blytheville, AR 72315
(870) 770-5000
(870) 770-5001





MILL TEST CERTIFICATE

Page:

2 / 6

Number:

104788609.0.1

Date: May 08, 2023

Manufacturer's Works Order N°:

N/A

Customer's Order Item:

39041718/50/10

Customer: Corpac Hickman CPU, 5000 North County Road 967, BLYTHEVILLE, AR 72315

Product Type: Line Pipe

Manufacturing Process:

HFV

Standard or Specification:

API Spec. 5L 46th Ed. 04/2018

Steel Grade:

X65M PSL 2

Surface:

Barre

Ends:

Plain End Bevelled

Dimensions:

16.000 x 0.500 in

Schedule:

N/A

Length:

Double Random

Quantity: 13 PCS

549 FT

Nominal Weight:

82.85 LB/FT

TENSILE TEST

E1 / E2: Ends of Sampling

Location of sample

Max: Maximum

Off: Orientation

Req: Required

RT: Room temperature

Ss: Strip specimen

T: Transversal

U.T.S.: Ultimate tensile strength

CHEMICAL COMPOSITION

Heat N°		Sample N°		Lot N°		Ls		H Max Min		Composition %																			
										X1																			
C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Sn	Nb	V	Ti	Ca	B	N	Fe-Pb												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25												
0.12	1.6	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.														

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subject to the law.



MILL TEST CERTIFICATE

Page:

3 / 6

Number:

104788609.0.1

Date: May 08, 2023



MAVERICK TUBE CORPORATION
Head Office
2020 N. COLONY RD / 417
B. V. DEWITT, AR 72715
(870) 776-5500 Int.
(870) 776-5000 Fax

Customer: Corpac Hickman GPU, 5000 North County Road 967, BLYTHEVILLE,

AR 72315

Manufacturer's Works Order N°:

N/A

Customer's Reference:

29524

Customer's Order Item:

3904171850/10

Product Type:

Line Pipe

Manufacturing Process:

FW

Standard or Specification:

API Spec. 5L 46th Ed. 04/2018

Steel Grade:

X65M PSL 2

Dimensions:

16.000 ± 0.500 in

Schedule:

N/A

Length:

Double Random

Quantity:

13 PCS

Nominal Weight:

82.85 LB/FT

Ends:

Plain End Bevelled

CHEMICAL COMPOSITION

B.M: Base metal

CE-Pcm: CE-Pcm

H: Heat

LS: Location of sample

Max: Maximum

Min: Minimum

P: Product

THROUGH WALL HARDNESS

Heat N°	Sample N°	Zone	Required values			Individuals			Average			Hardness type: HRBW		
			Min: -	Max: -	94.0	Min: -	Max: -	Var: -	Min: -	Max: -	Var: -	Ls	Specimen condition	Sc
			Lot N°	Pipe N°										
2131080	177110	-	2131080	-	-	B	AM	AM	AM	AM	AM	HRBW	HRBW	HRBW
2231613	177149	-	2231613	-	-	B	AM	AM	AM	AM	AM	HRBW	HRBW	HRBW
2231988	177114	-	2231988	-	-	B	AM	AM	AM	AM	AM	HRBW	HRBW	HRBW

AM: As manufactured

Avg: Average

B: Body

LS: Location of sample

Max: Maximum

Min: Minimum

Quad: Quadrant

Sc: Specimen condition

Var: Variation

IMPACT TEST

Type: Charpy V	Position:	Heat N°	Sample N°	Lot N°	Temp: 32			Orientation: T			Unit: ft.lb			Shear area %		
					Min: -	Max: -	94.0	Min: -	Max: -	Var: -	Min: -	Max: -	Var: -	Min: -	Max: -	Var: -
					Lot N°	Pipe N°		Lot N°	Pipe N°		Lot N°	Pipe N°		Lot N°	Pipe N°	
2131080	177110	-	2131080	-	-	-	-	-	-	-	-	-	-	-	-	-
					LS	Sc	F	LS	Sc	F	LS	Sc	F	LS	Sc	F
					B	AM	32	B	AM	32	B	AM	32	B	AM	32
					1	2	3	1	2	3	1	2	3	1	2	3
					Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.	Avg.
					95	95	95	95	95	95	95	95	95	95	95	95

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original creating upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.



MAVERICK TUBE CORPORATION

10000 S. GUTHRIE BLVD.
BLYTHEVILLE, AR 72315
(870) 776-5000
(870) 776-5000 FAX



MILL TEST CERTIFICATE

Page:

4 / 6

Number:

104788609.0.1

Date: May 08, 2023

Customer's Reference:

29524

Customer's Order Item:

3904171850/10

Product Type:

Line Pipe

Manufacturer's Works Order N°:

N/A

Standard or Specification:

API Spec. 5L 46th Ed. 04/2018

Dimensions:

16.000 x 0.500 in

Schedule:

N/A

Length:

Double Random

Steel Grade:

X65M PSL 2

Quantity:

13 PCS

Nominal Weight:

82.85 LB/FT

Ends:

Plain End Bevelled

Surface:

Bare

IMPACT TEST

Type: Charpy V		Temp: 32		Orientation: T		Unit: ft-lb		Shear area %	
Heat N°	Sample N°	Lot N°	Size	Ind. Min. Req.	11	Req. Min. Avg.	15	Ind. Min. Req.	Req. Min. Avg.
2231613	177149	2231613	3/4	1	2	205	200	1	2
2231938	177114	2231938	3/4	1	2	206	194	1	2
				Avg.				Avg.	
				205				205	
				206				205	

AM: As manufactured

Avg. Average

B: Body

Ind. Min. Req: Individual Minimum Required

Ls: Location of sample

Req. Min. Avg: Required minimum average

Sc: Specimen condition

T.T: Test temperature

Temp: Temperature

FLATTENING TEST

Standard:		Standard:		Standard:	
Heat N°	Sample N°	Lot N°	Result	Heat N°	Sample N°
2231613	177110	2231613	Good	2231613	177149
2231938	177114	2231938	Good	2231938	177114

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.



Tenaris



NAVERICK TUBE CORPORATION

Headquarters
2420 N. COLONY RD. 667
DALLAS, TEXAS 75244
TEL: 972.242.2500
FAX: 972.242.2501

Customer: Corpac Hickman CRTU, 5000 North County Road 967, BLYTHEVILLE, AR 72315		MILL TEST CERTIFICATE		Number: 104788609.0.1		Page: 5 / 6	
Manufacturing Process: HEW		Product Type: Line Pipe		Date: May 08, 2023		Customer's Reference: 29524	
Standard or Specification: API Spec. 5L 46th Ed. 04/2018		Customer's Order Item: 390471850710		Manufacturer's Works Order N°:		N/A	

Dimensions: 16.000 x 0.500 in		Schedule: N/A		Length: Double Random		Quantity: 13 PCS		45453 LB	
Steel Grade: X65M PSL 2		Ends: Plain End Bevelled		Surface: Bare		Nominal Weight: 82.85 LB/FT			

HYDROSTATIC TEST

Pressure		Time		Results	
Unit	Value	Seconds			
psi	2,270	5			Satisfactory

SUPPLEMENTARY INFORMATION

Supplementary Information		Supplementary Information	
This material has been manufactured, sampled, tested and inspected in accordance with this specification and has been found to meet the requirements called for by the above order. This product is alloy steel and/or aluminum fully killed. NDT OK UT with ID/DI N-5 Notches verified by 1/16" PDH		INSPECTION CERTIFICATION IN ACCORDANCE WITH EN 10204-2004 BODY TENSILE SOURCED 100% FROM WELD LINE; CVN SAMPLES SOURCED 90% FROM WELD LINE; CVN SAMPLES TESTED BY Imm STRIKER	
Heat Treatment			
The minimum weld seam heat treatment temperature is 1600F.			
Steel Vendor Name and Manufactured		Steel Vendor Name and Manufactured	
231080, Steel Melted and Coils Manufactured in USA by Nucor Hickman, Ammon, AR		231080, Steel Melted and Coils Manufactured in USA by Nucor Hickman, Ammon, AR	
231613, Steel Melted and Coils Manufactured in USA by Nucor Hickman, Ammon, AR		231613, Steel Melted and Coils Manufactured in USA by Nucor Hickman, Ammon, AR	
This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any forgery or not allowed use. Any alteration and/or falsification will be subjected to the law.			



MAVERICK TUBE CORPORATION
1000 N. 10TH ST. SUITE 100
DALLAS, TEXAS 75201
(214) 770-5000
www.mavericktube.com



MILL TEST CERTIFICATE

Page:

6 / 6

Number:

104788609.0.1

Date: May 08, 2023

Customer: Corpac Hickman CPU, 5000 North County Road 967, BLYTHEVILLE, AR 72515		Customer's Order Item: 39041718/50/10		Customer's Reference: 29574		Manufacturer's Works Order N°: N/A	
Manufacturing Process: HFW		Product Type: Line Pipe		Surface: Bare		Ends: Plain End Bevelled	
Standard or Specification: API Spec. 5L 46th Ed. 04/2018		Steel Grade: X65M PSL 2		Quantity: 13 PCS		Nominal Weight: 82.85 LB/FT	
Dimensions: 16.000 ± 0.500 in		Length: Double Random		Quantity: 549 FT		Ends: Plain End Bevelled	
Schedule: N/A		Length: Double Random		Quantity: 549 FT		Nominal Weight: 82.85 LB/FT	

SUMMARY REPORT

Heat N°	Quantity	Length	Weight	Heat N°	Quantity	Length	Weight
2131030	(Pieces) 1	FT 3.621	LB 664.533	2231813	(Pieces) 5	FT 35.38	LB 6492.413
2131030	(Pieces) 1	FT 3.621	LB 664.533	2231813	(Pieces) 5	FT 35.38	LB 6492.413
2131030	(Pieces) 1	FT 3.621	LB 664.533	2231813	(Pieces) 5	FT 35.38	LB 6492.413

The product certified herein has been manufactured, sampled, tested and inspected in accordance with the stated specifications and has been found to meet the requirements.

This certificate is not a declaration of origin nor may it be used as a declaration of origin.

CUSTOMER: THIRD PARTY

TENARIS QUALITY DEPARTMENT SIGNATURE

INSPECTION COMPANY
COMPAÑIA DE INSPECCION
Company Name: N/A
Employee Name: N/A

QUALITY CERTIFICATION DEPT.
MCCORMICK Billy

CHIEF OF QUALITY CERTIFICATION DEPT.
Renato AVILA

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original declaring under penalty of the responsibility for any unlawful or not allowed use. Any alteration and/or application will be subjected to the law.