



Manufacturer of Piping and Pressure Vessel Components

4404 Haygood St - Houston, TX 77022

Phone: 713-695-3633 Fax: 713-695-3528

A Bonney Forge Company

This product has not come in direct contact with mercury or any of its compounds, nor with any mercury-containing device employing a single boundary of containment. No welding performed.

We certify that the contents of this report are correct and accurate, and that all test results and operations performed by WFI or its subcontractors are in compliance with the material specification and requirements of the referenced code or standard, and that the material conforms to the dimensional requirements of the order. This document is in accordance with EN10204 3.1.

Item	Quantity	Description
3	9	36 - 3 X 1 3M THP

A/SA105

REPLACEMENT FOR LINE 1

Chemical Composition

Ladle	Al	B	C	Cr	CR+MO	Cu	Mn	Mn/C	Mo	Nb	Nb+V	Ni
	0.023	0.0003	0.200	0.12	0.13	0.10	0.980	4.900	0.010	0.0010	0.00	0.040
P	RE(1)	S	Si	V								
	0.004	0.27	0.0210	0.230	0.00							
Carbon Equivalency (C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15):					0.40							

RE(1) = Cu + Ni + Cr + Mo + V

	Tensile PSI	Yield PSI	Elong (4D) %	RA %	Hardness
Product	73,071	45,415	32.55	65.60	139 BHN 137 BHN

MILL/COUNTRY OF ORIGIN: CHARTER STEEL (MELTED AND MANUFACTURED: SAUKVILLE, WISCONSIN / USA) - HEAT NO.: 21026530
(BONNEY FORGE (MT. UNION, PS (USA)) - HEAT NO.: 52417

IN ACCORDANCE WITH ANSI/NACE MR0175 / ISO 15156-2021

STEEL IS FULLY KILLED AND PRODUCED TO A FINE GRAIN PRACTICE

AS FORGED

1. ASME SECTION II, 2023 EDITION

Sold To: STUART C. IRBY COMPANY
1 CAPE MAY STREET
UNIT G
HARRISON NJ 07029-2402
United States

MTR #: 456,846

PO #: S014595410

Sales Order #: C002604659

Date: 06/18/2026

Certified Material Test Report

Heat Code: 52417

Material: A105 24

Monica Rogers Quality Assurance Representative