



Wednesday Mar-18-2026

Flowserve Facility:

Flowserve Nordstrom / Valbart Valves
1511 Jefferson St.
Sulphur Springs, TX 75482

cmtrs@flowserve.com

To:

CERTIFICATE OF CONFORMANCE

SERIAL #	HEAT #	PO #	Description	Valve Type	Class	End Connection
61-698691	71454	1175944	8" 2349	PLUG	900	FLG

We hereby certify that all the subject valves/parts/sealant have been manufactured in conformance with the applicable requirements of Flowserve Sulphur Springs Operations (FSSO) specifications and that the valve/parts/sealant materials for component parts meet the applicable requirements of FSSO drawings and ASTM specifications, ASME B16.34 (If Applicable), API Q1 10th edition, and API 6D 25th edition.(if applicable to the API monogram). Flowserve Dynamic Balanced Valves are provided with a Pressure balance feature unless specifically identified in the Valve description. All valves/parts/sealant meet all the requirements of the customer purchase order.

A handwritten signature in black ink, appearing to read "J. McKee", with a stylized flourish at the end.



INSPECTION CERTIFICATE

INSPECTION CERTIFICATE AS PER - EN 10204:2004-3.1

Customer : FLOWSERVE INDIA CONTROLS PVT.LTD										T.C. No : 48862P/25 T.C.Date : 07/06/2025					
P.Order : 10124039 Dt. 10/03/2025										Heat No : 71454 Date of Pouring : 20/05/2025					
Specification : ASTM A216/A216M Gr:WCC (UNS J02503) MOD-21 & MATERIAL SPEC:RMC90012 Rev.15										CASTING PROCESSED BY INDUCTION MELTING FOUNDRY IDENTIFICATION : MSI					

CHEMICAL COMPOSITION % (ASTM A751-2021)

Element	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	V	CE	RE	Al	N		
Minimum	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Maximum	0.23	0.60	1.20	0.025	0.020	0.50	0.20	0.50	0.30	0.03	0.42	0.50	0.06	0.015		
Actual	0.192	0.427	0.930	0.019	0.008	0.166	0.019	0.069	0.012	0.001	0.390	0.267	0.037	0.010		



HEAT TREATMENT : NORMALISED:SOAKED AT 920 °C FOR 4 HRS AND THEN AIR COOLED. (Cycle No :N7601)

Furnace No : G-003 Calib.Due.Date : 04/09/2025

MECHANICAL PROPERTIES (ASTM A370-2024a)

Requirments	Yield Strength		Tensile Strength		% Elongation	% Reduction	Hardness	Bend Test	Impact Test			
	Kgf/mm ²	MPa	Kgf/mm ²	MPa	GL :50 mm	In Area	HB	At --	(10mm X 10mm X 55mm)			
	0.2% Offset		-		-	-	-	-				
Minimum	29.53	290	49.44	485	22	35	---	-				
Maximum	---	---	66.77	655	---	---	233	-				
Actual	32.46	318.28	51.80	508.01	35.74	63.71	153,150,151					

ITEM DESCRIPTION

SL.No.	Description	Drawing No.	Part No.	Quantity
1	8"900 PLUG BODY-FLANGED	E-00122653 Rev20	N122653WCC	2
REVIEWED / NOTED WITNESSED  R.RANJITH  				

Remarks : Material According to:FTDC 001 REV.8,RMC 90012 Rev.15,RMP 61496 Rev.B&ASTM A216 Gr.WCC(UNS J02503)-2021 & NACE MR0175-2021/ISO 15156-1:2020, Magnetic particle Inspection of casting: Satisfactory According to RMC 90001 Rev B Visual Inspection of casting: Satisfactory According to MSS SP-55-2025, LUX Meter Sl.No:S924351,Cal Due Dt: 14.11.2025 Visual Inspection conforms to MSS SP-55-2025,Type 2 to Type 12 acceptance level A, Type 1 not found,Country of Origin:INDIA Dimensional Inspection : Satisfactory According to Approved Drawing, Certified that the products supplied is free from Radioactive element or contamination,Carbon fully killed material

We Confirm that the above material was manufactured, sampled, tested and inspected in accordance with the drawings, material specification and customer order requirements

ASTM A216/A216M Gr:WCC (UNS J02503) MOD-21 & MATERIAL SPEC:RMC90012 Rev.15

 (G.SIVA KUMAR) SNT-TC-1A-LEVEL II - MT,PT,VT		 (C.MUTHUKUMAR) HEAD QA
--	--	--

**KITZ CORPORATION OF AMERICA**

10750 CORPORATE DRIVE, STAFFORD, TX 77477

TEL: (281)491-7333 FAX: (281)491-9402

MESSRS.: KITZ CORPORATION OF AMERICADELIVER TO: HOUSTON

JOB & SHEET NO.: 25E16_6KW19F_012_1/5

P.O. NO. #3071006274/#3071006291DATE : JUN.11, 2025**CERTIFICATE OF COMPLIANCE**

TO WHOM IT MAY CONCERN

WE HEREBY CERTIFY THAT OUR PRODUCTS AS SHOWN ON DRAWINGS OF
KITZ MODEL AK6000SCTFWZM-FS CODE 6KW19F ARE MANUFACTURED, INSPECTED
AND TESTED FULLY IN ACCORDANCE WITH THE FOLLOWING STANDARDS:

PRESSURE-TEMPERATURE RATING	1/2" TO 2"	6170 PSIG @ 300°F MAX.
SHELL WALL THICKNESS	ANSI B16.34 CLASS 2500	
BODY & CAP	ASTM A105N	
SEAT MATERIAL	PEEK	
VALVE TESTING	API 598 ※	
FIRE TEST STANDARD	API 607 7 TH EDITION	
END CONNECTION	NPT THREADS TO ANSI B1.20.1	

※ HIGH PRESSURE SHELL TEST AND LOW PRESSURE SEAT TEST ARE PERFORMED 100%

● NACE MR-0175-2002 AND MR-0103 COMPLIANCE

JY VALVE & MFG. CO., LTD.

CHARLES CHAN, PRESIDENT



10750 CORPORATE DRIVE, STAFFORD, TX 77477

TEL: (281)491-7333 FAX: (281)491-9402

MESSRS.: KITZ CORPORATION OF AMERICA
T O : HOUSTON
P.O. NO.: #3071006274/#3071006291

JOB & SHEET NO.: 25E16_6KW19F_012_2/5
EXPORT NO.: JM250601
DATE : JUN. 11, 2025

WITNESSED BY: JY VALVE & MFG. CO., LTD.

LUO, XIAODONG, QC MANAGER

VALVEMODEL	DESCRIPTION	SIZE	Q'TY	PRESSURE TEST PSIG				MATERIAL	DIMENSION	VISUAL	OPERATION
		(INCH)	(PCS)	SHELL	SEAT		RESULT				
				HYDRO	HYDRO	AIR					
AK6000SCTFW ZM-FS CODE 6KW19F	CLASS 2500 3-PC TYPE FORGED CARBON STEEL 316 SS TRIM THREADED END BALL VALVES	1/2"	350	9275	6800	80	GOOD	GOOD	GOOD	GOOD	GOOD



KITZ CORPORATION OF AMERICA
10750 CORPORATE DRIVE, STAFFORD, TX 77477
TEL: (281)491-7333 FAX: (281)491-9402

MATERIAL TEST RESULTS

MESSRS. : KITZ CORPORATION OF AMERICA
TO : HOUSTON
P.O. NO. : #3071006274/#3071006291

JOB & SHEET NO.: 25E16_6KW19F_012_3/5
EXPORT NO : JM250601
DATE : JUN. 11, 2025

VALVE MODEL : AK6000SCTFWZM-FS CODE 6KW19F SIZE : 1/2"
CLASS 2500 BALL VALVE MATERIAL: ASTM-A105N-2014
REVIEWED BY: FUJIAN LI CHUAN FORGINGS CO.,LTD.


LUO, XIAODONG, QC MANAGER
JY VALVE & MFG. CO., LTD.

CHEMICAL REQUIREMENT(%)												
ELEMENT		C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	
SPEC (MAX.)												
Production No	Parts Name											
24KK	BODY	0.2120	0.8200	0.0120	0.0030	0.2200	0.0300	0.0300	0.0100	0.0200	0.0110	
24GK	CAP	0.2120	0.8200	0.0120	0.0030	0.2200	0.0300	0.0300	0.0100	0.0200	0.0110	
25DK	CAP	0.1700	0.8800	0.0170	0.0150	0.2500	0.0700	0.0150	0.0120	0.0300	0.0170	
TENSILE REQUIREMENTS		Tensile Strengt (MPa)		Yield Strength (MPa)		Elongation (%)		Reduction of area (%)		Hardness (HBW)		
Production No	Parts Name	Min. 485		Min. 250		Min. 22		Min. 30		#1	#2	
24KK	BODY	495		275		35		42		147	147	
24GK	CAP	495		275		35		42		147	147	
25DK	CAP	505		315		29		38		145	145	
Heat treatment	NORMALIZING AND TEMPERING											

WE HEREBY CERTIFY THAT THE MATERIAL HEREIN DESCRIBED ARE SATISFACTORY IN ACCORDANCE WITH THE SPECIFICATION.

MATERIAL TEST RESULTS

MESSRS. : KITZ CORPORATION OF AMERICA
 TO : HOUSTON
 P.O. NO. : #3071006274/#3071006291

JOB & SHEET NO.: 25E16_6KW19F_012_4/5
 EXPORT NO : JM250601
 DATE : JUN. 11. 2025

VALVE MODEL : AK6000SCTFWZM-FS CODE 6KW19F SIZE : 1/2"
 CLASS 2500 BALL VALVE MATERIAL: ASTM-A182-2018 GRADE F316
 REVIEWED BY: FUZHOU SHI GANG VALVE MANUFACTURE CO.,LTD.

LUO, XIAODONG, QC MANAGER
 JY VALVE & MFG. CO., LTD.

CHEMICAL REQUIREMENT(%)										
ELEMENT		C	Mn	P	S	Si	Ni	Cr	Mo	
SPEC (MAX.)										
Production No	Parts Name			0.045	0.030	1.000	10.0-14.0	16.0-18.0	2.00-3.00	
2408F0092	BALL	0.0280	0.9300	0.0380	0.0030	0.4100	10.0200	16.2600	2.0300	
TENSILE REQUIREMENTS		Tensile Strength (MPa)		Yield Strength (MPa)		Elongation (%)		Reduction of area (%)		Hardness (HB)
Production No	Parts Name	Min. 515		Min. 205		Min. 30		Min. 50		Max. 237
2408F0092	BALL	553		278		64		82		135
SOLUTION TREATMENT										
Heat treatment										

WE HEREBY CERTIFY THAT THE MATERIAL HEREIN DESCRIBED ARE SATISFACTORY IN ACCORDANCE WITH THE SPECIFICATION.



KITZ CORPORATION OF AMERICA
10750 CORPORATE DRIVE, STAFFORD, TX 77477
TEL: (281)491-7333 FAX: (281)491-9402

MATERIAL TEST RESULTS

MESSRS. : KITZ CORPORATION OF AMERICA
TO : HOUSTON
P.O. NO. : #3071006274/#3071006291

JOB & SHEET NO.: 25E16_6KW19F_012_5/5
EXPORT NO : JM250601
DATE : JUN. 11. 2025


VALVE MODEL : AK6000SCTFWZM-FS CODE 6KW19F SIZE : 1/2"
CLASS 2500 BALL VALVE. MATERIAL: ASTM-A276-2017 TYPE 316
REVIEWED BY: GAOYOU WEI DA STAINLESS STEEL CO., LTD.

Joe X. Wang

LUO, XIAODONG, QC MANAGER
JY VALVE & MFG. CO., LTD.

CHEMICAL REQUIREMENT(%)										
ELEMENT		C	Mn	P	S	Si	Cr	Ni	Mo	
SPEC (MAX.)		0.08	2.00	0.045	0.030	1.00	16.0-18.0	10.00-14.00	2.00-3.00	
Production No	Parts Name									
2405F0093	STEM	0.0510	0.6800	0.0020	0.0210	0.5500	16.4200	10.8400	2.2500	
TENSILE REQUIREMENTS		Tensile Strength (MPa)		Yield Strength (MPa)		Elongation (%)		Reduction of area (%)		Hardness (HB)
Production No	Parts Name	Min. 515		Min. 205		Min. 40		Min. 50		Max. 187
2405F0093	STEM	521		237		49		57		155
Heat treatment	COLD FINISHED									

WE HEREBY CERTIFY THAT THE MATERIAL HEREIN DESCRIBED ARE SATISFACTORY IN ACCORDANCE WITH THE SPECIFICATION.



01 2146030



Coating Inspection Report

Work Order Number:	204092
Line Number:	01
Item ID Number:	2GG685
Customer Spec / System / GCM WI:	CONSUMMERS SPEC 73700sp SECTION 11
Valve Description:	1 8" 900 NORDSTRM WCC PLUG RF

Coating System

☐ Epoxy Coating☐ Coal Tar☒ 2 Part☐ 3 Part

Atmospheric Conditions (Surface Preparation)

Ambient Temp: 74.3°F Rel. Humidity: 73.1% Date: 4/16/2026Surface Temp: 78.0°F Dew Point: 70.2°F Time: 11:00 AM

Surface Preparation Inspection

Blast Surface: SSPC SP-1 - SolventSoluble Salts Content (max 25 mg/m²): _____Blast Surface Criteria: ☐ SSPC-SP-5 ☐ SSPC-SP-6 ☒ SSPC-SP-10Surface Profile Requirements (mils): 2.0 - 3.0 Actual: _____Blast Technician: ROBERT M. Date / Time: 4/16/26 11:10 AMQC Inspector: VICTOR GARCIA Date / Time: 4/16/26 11:25 AM3rd Party Inspector: *Regan John* Date / Time: 4-22-26Testex
PRESS-O-FILM

213

X-Coarse

1.5 - 4.5 mils
40 - 115 µm



Atmospheric Conditions (1st Coat Epoxy / Primer Coat) (If Applicable)

Ambient Temp: 74.4°F Rel. Humidity: 80.2% Date: 4/16/2026
Surface Temp: 85.1°F Dew Point: 79.2°F Time: 11:45 AM

1st Coat Epoxy / Primer Coat (If Applicable)

Technician: VICTOR GARCIA Coating System: AMERON
Coating System: AMERLOCK 2 HI-SOLIDS
Batch No. – Part A: 9531901563 Batch No. – Part B: 9536915146
Thickness Req'd (mils): 6.0 - 8.0
Dry Film Thickness (min. of 5 readings): 8.2 7.9 8.3 7.5 8.4
Average DFT (mils): 8.1 Total DFT Req'd (mils): 6.0 - 8.0
Visual Inspection (free of pinholes, voids, bubbles, blisters, drips): ☒ Accepted ☐ Rejected
QC Inspector: VICTOR GARCIA Date / Time: 4/17/26 9:00 AM
3rd Party Inspector: *Ryan Johnson ACI* Date / Time: 4-22-26

Atmospheric Conditions (Intermediate Coat) (If Applicable)

Ambient Temp: 76.3°F Rel. Humidity: 53.8% Date: 4/17/26
Surface Temp: 84.6°F Dew Point: 64.3°F Time: 10:30 AM

Intermediate Coat (If Applicable)

Technician: VICTOR GARCIA Coating System: AMERON
Coating System: AMERSHIELD ALIPHATIC CONSUMERS GREEN RAL 6011
Batch No. – Part A: 00333854 Batch No. – Part B: NZ1008JE-1
Thickness Req'd (mils): 3.0-5.0
Dry Film Thickness (min. of 5 readings): 12.2 14.8 13.2 14.5 12.0
Average DFT (mils): 13.3 Total DFT Req'd (mils): 9.0-13.0
Visual Inspection (free of pinholes, voids, bubbles, blisters, drips): ☒ Accepted ☐ Rejected
QC Inspector: VICTOR GARCIA Date / Time: 4/18/26 8:30 AM
3rd Party Inspector: *Ryan Johnson ACI* Date / Time: 4-22-26



Atmospheric Conditions (Final Coat)

Ambient Temp: _____ Rel. Humidity: _____ Date: _____
Surface Temp: _____ Dew Point: _____ Time: _____

Final Coat

Technician: _____ Coating System: _____
Coating System: _____
Batch No. – Part A: _____ Batch No. – Part B: _____
Thickness Req'd (mils): _____
Dry Film Thickness (min. of 5 readings): _____
Average DFT (mils): 0.0 _____ Total DFT Req'd (mils): _____
Visual Inspection (free of pinholes, voids, bubbles, blisters, drips): ☐ Accepted ☐ Rejected
QC Inspector: _____ Date / Time: _____
3rd Party Inspector: _____ Date / Time: _____

Holiday Testing (If Required)

Holiday Test Method: _____
Voltage: _____
Allowable Discontinuities: _____
Inspection Determination: ☐ Accepted ☐ Rejected
QC Inspector: _____ Date / Time: _____
3rd Party Inspector: _____ Date / Time: _____

Notes