



Texas Tubular Products

P.O. Box 0388, 3681 FM 250, Lone Star, TX 75668

Print Date: 4/18/2024

Material Test Report

Results relate only to items tested. Test report not to be reproduced except in it's entirety.

Heat: B317535

Product: 8.625 0.322 X52 M PSL2 HFW

Mtr#: 15

Lot: 57

Specification: API 5L 46th Edition (05/01/19) X52 M, PSL2
ASTM A53/A53M-22 Grade B/ASME SA-53/SA-53M-17 Grade B, ERW
HARDNESS MEETS NACE MRO175.
HFW MANUFACTURED IN THE U.S.A.

Customer Order Number: STL-306371

Sold To:

EDGEN MURRAY CORPORATION

Ship To:

EDGEN MURRAY CORPORATION

BATON ROUGE LA 70884

Chemical Analysis, %

Acceptance Criteria % Max CEPcm = .25

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	B	Nb	Ti	Ca	N	CEIIW	CEPcm
Heat	0.06	0.64	0.013	0.0040	0.22	0.14	0.04	0.060	0.010	0.001	0.0001	0.028	0.018	0.0018	0.006	0.193	0.11
Product	0.06	0.62	0.011	0.0030	0.22	0.14	0.04	0.060	0.010	0.001	0.0001	0.020	0.010	0.0010	0.000	0.190	0.11
Product	0.05	0.62	0.010	0.0030	0.22	0.13	0.03	0.060	0.010	0.001	0.0001	0.020	0.010	0.0010	0.000	0.178	0.10

Mechanical Properties

Hardness Tests

Test	Dir	Loc	Yield KSI	Tensile KSI	Elong % in 2"	Fracture Location	Y/T Ratio	Hydrotest, PSI (5 sec. hold)	Scale	Loc	Hard 1
1	T	B-180	65.9	74.9	37.4		0.88	3900	HRBW	SUR	84.1
2	T	W		78.2		OW		Passed			
								Specimen Size 1.5			
								Heat Treat Type Seam Normalization			

Charpy Impact Tests

Acceptance Criteria Min. Ft/Lb 13

Test	Dir	Loc	Size	Temp	Energy 1	Energy 2	Energy 3	Avg	% Shear 1	%Shear 2	%Shear 3	Avg
1	T	B-90	2/3	32 F	112	23	113	112	100	100	100	100
2	T	W	2/3	32 F	56	63	102	56	55	60	100	55

Remarks

Inspection Performed

MINIMUM HEAT TREATMENT OF WELD SEAM 1600 DEG F
TENSILE TEST - STRIP

MEETS ISO 10424 3.1.B / EN 10204 3.1 / LATEST EDITIONS

COIL MELTED AND ROLLED AT: SDI-Columbus, MS

MANUFACTURED BY TEXAS TUBULAR PRODUCTS LONE STAR, TX

ULTRASONIC WELDLINE - N10 Notch
VISUAL

By:

Quality Manager

This is to certify that the product described herein was manufactured, sampled, tested, and /or inspected in accordance with the specifications/order and fulfills the requirements in such respects.

WE HEREBY VERIFY THAT THE ABOVE INFORMATION IS CORRECT AS CONTAINED IN THE RECORDS OF TEXAS TUBULAR PRODUCTS

TTFM-182/4

05/24/23



Texas Tubular Products

P.O. Box 0388, 3681 FM 250, Lone Star, TX 75668

Print Date: 6/7/2024

Material Test Report

Results relate only to items tested. Test report not to be reproduced except in it's entirety.

Heat: B317535

Product: 8.625 0.322 X52 M PSL2 HFW

Mtr#: 14

Lot: 58

Specification: API 5L 46th Edition (05/01/19) X52 M, PSL2
ASTM A53/A53M-22 Grade B/ASME SA-53/SA-53M-17 Grade B, ERW
HARDNESS MEETS NACE MRO175.
HFW MANUFACTURED IN THE U.S.A.

Customer Order Number: STL-306371

Sold To:

EDGEN MURRAY CORPORATION

Ship To:

EDGEN MURRAY CORPORATION

BATON ROUGE LA 70884

Chemical Analysis, %

Acceptance Criteria % Max CEPcm = .25

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	B	Nb	Ti	Ca	N	CEIIW	CEPcm
Heat	0.06	0.64	0.013	0.0040	0.22	0.14	0.04	0.060	0.010	0.001	0.0001	0.028	0.018	0.0018	0.006	0.193	0.11
Product	0.05	0.62	0.010	0.0030	0.22	0.13	0.03	0.060	0.010	0.001	0.0001	0.020	0.010	0.0010	0.000	0.178	0.10
Product	0.06	0.62	0.011	0.0030	0.22	0.14	0.04	0.060	0.010	0.001	0.0001	0.020	0.010	0.0010	0.000	0.190	0.11
Product																	

Mechanical Properties

Hardness Tests

Test	Dir	Loc	Yield KSI	Tensile KSI	Elong % in 2"	Fracture Location	Y/T Ratio	Hydrotest, PSI (5 sec. hold)	Scale	Loc	Hard 1
1	T	B-180	65.7	75.5	38.3		0.87	3900	HRBW	SUR	82.9
2	T	W		81.5		OW		Flattening Passed Specimen Size 1.5 Heat Treat Type Seam Normalization			

Charpy Impact Tests

Acceptance Criteria Min. Ft/Lb 13

Test	Dir	Loc	Size	Temp	Energy 1	Energy 2	Energy 3	Avg	% Shear 1	%Shear 2	%Shear 3	Avg
1	T	B-90	2/3	32 F	118	124	123	118	100	100	100	100
2	T	W	2/3	32 F	66	119	88	66	100	100	100	100

Remarks

Inspection Performed

MINIMUM HEAT TREATMENT OF WELD SEAM 1600 DEG F
TENSILE TEST - STRIP

MEETS ISO 10424 3.1.B / EN 10204 3.1 / LATEST EDITIONS

COIL MELTED AND ROLLED AT: SDI-Columbus, MS

MANUFACTURED BY TEXAS TUBULAR PRODUCTS LONE STAR, TX

ULTRASONIC WELDLINE - N10 Notch
VISUAL

By: 

Quality Manager

This is to certify that the product described herein was manufactured, sampled, tested, and /or inspected in accordance with the specifications/order and fulfills the requirements in such respects.

WE HEREBY VERIFY THAT THE ABOVE INFORMATION IS CORRECT AS CONTAINED IN THE RECORDS OF TEXAS TUBULAR PRODUCTS

TTFM-182/4

05/24/23