



The Best Value -
Price, Quality, Service
All The Time.

CERTIFIED MILL TEST REPORT

LOG NO. F00000000230915

Page 1 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
1	25	52186	36-11/2X3/4 3000 A105 FLEX T SA/A105 Al 0.026 C 0.210 Co 0.010 Cr 0.120 Cu 0.080 Mn 1.010 Mo 0.010 Nb 0.001 Ni 0.040 P 0.008 S 0.025 Si 0.240 V 0.003 CE(Long Formula) = 0.41 T/S(PSI) 75,324 Y/S(PSI) 46,689 EL(%) 35.15 RA(%) 61.49 Brinell Hardness 141 BHN 141 BHN Country Of Origin (Melt): UNITED STATES
2	25	52189	1 3000 A105 45EL T SA/A105 Al 0.021 C 0.190 Co 0.010 Cr 0.130 Cu 0.120 Mn 0.990 Mo 0.020 Nb 0.001 Ni 0.050 P 0.011 S 0.022 Si 0.220 V 0.003 CE(Long Formula) = 0.40 T/S(PSI) 75,306 Y/S(PSI) 46,724 EL(%) 34.45 RA(%) 62.02 Brinell Hardness 141 BHN 139 BHN Country Of Origin (Melt): UNITED STATES
3	25	52208	1/2 3000 A105 90EL T SA/A105 Al 0.023 C 0.190 Co 0.010 Cr 0.110 Cu 0.140 Mn 0.970 Mo 0.020 Nb 0.001 Ni 0.060 P 0.009 S 0.020 Si 0.220 V 0.003 CE(Long Formula) = 0.39 T/S(PSI) 74,780 Y/S(PSI) 46,908 EL(%) 34.80 RA(%) 66.89 Brinell Hardness 139 BHN 139 BHN Country Of Origin (Melt): UNITED STATES
4	25	52235	3/4 3000 A105 90EL T SA/A105 Al 0.023 C 0.200 Co 0.010 Cr 0.120 Cu 0.110 Mn 0.980 Mo 0.020 Nb 0.002 Ni 0.050 P 0.012 S 0.025 Si 0.240 V 0.003 CE(Long Formula) = 0.40 T/S(PSI) 75,368 Y/S(PSI) 44,491 EL(%) 33.10 RA(%) 60.94 Brinell Hardness 141 BHN 144 BHN Country Of Origin (Melt): UNITED STATES

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000230915

Page 2 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
5	125	52222	1 3000 A105 90EL T SA/A105 Al 0.022 C 0.200 Co 0.010 Cr 0.110 Cu 0.090 Mn 0.990 Mo 0.010 Nb 0.001 Ni 0.050 P 0.009 S 0.022 Si 0.240 V 0.003 CE(Long Formula) = 0.40 T/S(PSI) 73,265 Y/S(PSI) 43,332 EL(%) 33.20 RA(%) 65.37 Brinell Hardness 139 BHN 139 BHN Country Of Origin (Melt): UNITED STATES
6	25	J173	1 X 1/4 3M/6M A105 HXBU T SA/A105 Al 0.034 C 0.200 Co 0.004 Cr 0.090 Cu 0.180 Mn 0.980 Mo 0.010 Nb 0.001 Ni 0.060 P 0.006 S 0.022 Si 0.190 V 0.026 CE(Long Formula) = 0.40 T/S(PSI) 77,500 Y/S(PSI) 53,400 EL(%) 34.00 RA(%) 30.00 Brinell Hardness 166 BHN 166 BHN Country Of Origin (Melt): UNITED STATES
7	25	J173	1 X 3/8 3M/6M A105 HXBU T SA/A105 Al 0.034 C 0.200 Co 0.004 Cr 0.090 Cu 0.180 Mn 0.980 Mo 0.010 Nb 0.001 Ni 0.060 P 0.006 S 0.022 Si 0.190 V 0.026 CE(Long Formula) = 0.40 T/S(PSI) 77,500 Y/S(PSI) 53,400 EL(%) 34.00 RA(%) 30.00 Brinell Hardness 166 BHN 166 BHN Country Of Origin (Melt): UNITED STATES
8	25	J216	1 X 3/4 3M/6M A105 HXBU T SA/A105 Al 0.023 C 0.200 Co 0.003 Cr 0.120 Cu 0.040 Mn 1.060 Mo 0.004 Nb 0.010 Ni 0.020 P 0.006 S 0.024 Si 0.190 V 0.003 CE(Long Formula) = 0.41 T/S(PSI) 79,800 Y/S(PSI) 49,400 EL(%) 30.00 RA(%) 56.60 Brinell Hardness 162 BHN 161 BHN Country Of Origin (Melt): CANADA

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by 

Billie Jo Clemens
Quality Assurance Representative

CMTR: Rev 3

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000230915

Page 3 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
9	25	J125	1/4 3M/6M A105 HXPL T SA/A105 C 0.170 Cb 0.000 Co 0.000 Cr 0.100 Cu 0.160 Mn 0.740 Mo 0.010 Ni 0.060 P 0.009 S 0.014 Si 0.190 V 0.003 CE(Long Formula) = 0.33 T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00 Brinell Hardness 150 BHN 159 BHN
10	150	J229	1/2 3M/6M A105 HXPL T SA/A105 C 0.160 Cr 0.080 Cu 0.080 Mn 0.730 Mo 0.020 Ni 0.050 P 0.007 S 0.002 Si 0.180 V 0.002 CE(Long Formula) = 0.31 T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00 Brinell Hardness 141 BHN 156 BHN Country Of Origin (Melt): UNITED STATES
11	50	J249	3/4 3M/6M A105 HXPL T SA/A105 C 0.160 Cr 0.080 Cu 0.080 Mn 0.730 Mo 0.020 Ni 0.050 P 0.007 S 0.002 Si 0.180 V 0.002 CE(Long Formula) = 0.31 T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00 Brinell Hardness 139 BHN 150 BHN Country Of Origin (Melt): UNITED STATES
12	500	J260	1 3M/6M A105 HXPL T SA/A105 Al 0.024 C 0.210 Cb 0.024 Co 0.010 Cr 0.050 Cu 0.070 Mn 0.930 Mo 0.010 Ni 0.030 P 0.008 S 0.003 Si 0.170 Sn 0.005 V 0.003 CE(Long Formula) = 0.38 T/S(PSI) 70,000 Y/S(PSI) 57,500 EL(%) 33.00 RA(%) 69.00 Brinell Hardness 149 BHN 149 BHN Country Of Origin (Melt): UNITED STATES

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by Billie Jo Clemens

Billie Jo Clemens
Quality Assurance Representative

CMTR: Rev 3

Heat J279

Desc Forged Hex Plug ASTM A/SA105 NPT Threaded, 2"

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000230915

Page 4 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
13	450	J279	2 3M/6M A105 HXPL T	SA/A105
			Al 0.031 C 0.180 Cb 0.003 Co 0.005 Cr 0.150 Cu 0.260 Mn 0.990 Mo 0.010 Ni 0.070 P 0.009 S 0.025 Si 0.221 V 0.023 CE(Long Formula) = 0.40 T/S(PSI) 78,700 Y/S(PSI) 51,800 EL(%) 25.00 RA(%) 56.00 Brinell Hardness 161 BHN 161 BHN Country Of Origin (Melt): UNITED STATES	
14	20	52173	1 3000 A105 TEE T	SA/A105
			Al 0.025 C 0.200 Co 0.003 Cr 0.120 Cu 0.040 Mn 1.030 Mo 0.002 Nb 0.009 Ni 0.010 P 0.005 S 0.018 Si 0.220 V 0.003 CE(Long Formula) = 0.40 T/S(PSI) 78,262 Y/S(PSI) 49,703 EL(%) 32.85 RA(%) 63.24 Brinell Hardness 141 BHN 144 BHN Country Of Origin (Melt): CANADA	
15	5	52112	1 X1 X 3/4 3000 A105 TEE T	SA/A105
			Al 0.023 C 0.200 Co 0.005 Cr 0.140 Cu 0.250 Mn 1.040 Mo 0.020 Nb 0.003 Ni 0.070 P 0.009 S 0.019 Si 0.184 V 0.024 CE(Long Formula) = 0.43 T/S(PSI) 81,772 Y/S(PSI) 53,772 EL(%) 30.65 RA(%) 61.00 Brinell Hardness 156 BHN 159 BHN Country Of Origin (Melt): UNITED STATES	
16	100	52200	1 3000 A105 90EL S	SA/A105
			Al 0.023 C 0.190 Co 0.010 Cr 0.110 Cu 0.120 Mn 0.980 Mo 0.020 Nb 0.001 Ni 0.050 P 0.008 S 0.018 Si 0.200 V 0.003 CE(Long Formula) = 0.39 T/S(PSI) 75,299 Y/S(PSI) 45,756 EL(%) 34.55 RA(%) 66.43 Brinell Hardness 139 BHN 139 BHN Country Of Origin (Melt): UNITED STATES	

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Quality Assurance Representative

CMTR: Rev 3

Heat J279

Desc Forged Hex Plug ASTM A/SA105 NPT Threaded,2"

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000230915

Page 5 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
17	25	D914	1/2 3000 A105 COUP S	SA/A105
Al 0.026 C 0.200 Co 0.012 Cr 0.070 Cu 0.300 Mn 1.050 Mo 0.020 Nb 0.005				
Ni 0.090 P 0.009 S 0.023 Si 0.233 V 0.022				
CE(Long Formula) = 0.42				
T/S(PSI) 77,700 Y/S(PSI) 54,500 EL(%) 35.00 RA(%) 35.00				
Brinell Hardness 167 BHN 169 BHN				
Country Of Origin (Melt): UNITED STATES				
18	25	J148	3/4 3000 A105 COUP S	SA/A105
Al 0.025 C 0.200 Co 0.002 Cr 0.120 Cu 0.030 Mn 1.080 Mo 0.002 Nb 0.010				
Ni 0.010 P 0.007 S 0.024 Si 0.230 V 0.004				
CE(Long Formula) = 0.41				
T/S(PSI) 78,400 Y/S(PSI) 47,600 EL(%) 34.00 RA(%) 66.60				
Brinell Hardness 159 BHN 159 BHN				
Country Of Origin (Melt): CANADA				
19	50	D993	1 3000 A105 COUP S	SA/A105
Al 0.029 C 0.180 Co 0.006 Cr 0.070 Cu 0.260 Mn 1.040 Mo 0.020 Nb 0.001				
Ni 0.080 P 0.004 S 0.025 Si 0.215 V 0.025				
CE(Long Formula) = 0.40				
T/S(PSI) 73,500 Y/S(PSI) 49,600 EL(%) 32.00 RA(%) 38.00				
Brinell Hardness 163 BHN 163 BHN				
Country Of Origin (Melt): UNITED STATES				
20	25	52256	1 3000 A105 TEE S	SA/A105
Al 0.040 C 0.190 Co 0.005 Cr 0.110 Cu 0.220 Mn 0.970 Mo 0.020 Nb 0.001				
Ni 0.070 P 0.007 S 0.023 Si 0.224 V 0.024				
CE(Long Formula) = 0.40				
T/S(PSI) 81,824 Y/S(PSI) 53,109 EL(%) 29.95 RA(%) 52.16				
Brinell Hardness 156 BHN 156 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Quality Assurance Representative

CMTR: Rev 3

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000230915

Page 6 of 6

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 10/25/2025

CUSTOMER

BONNEY ORDER NO. B000371622

ORDER NO.: RMS-321849

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2


HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
21	36	52130	3 X 2 3M/6M A105 HXBU T	SA/A105
			Al 0.031 C 0.200 Co 0.005 Cr 0.090 Cu 0.260 Mn 0.970 Mo 0.020 Nb 0.005	
			Ni 0.080 P 0.007 S 0.023 Si 0.245 V 0.021	
			CE(Long Formula) = 0.41	
			T/S(PSI) 80,711 Y/S(PSI) 52,025 EL(%) 31.85 RA(%) 60.01	
			Brinell Hardness 147 BHN 147 BHN	

1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2 - 2015 EDITION.
3. CERTIFYING ASTM A105-24 / ASME SA105-23 EDITION.
4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
5. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.
6. ITEM - 9, 10, 11 -THE MATERIAL SUPPLIED IDENTIFIED AS SA/A105-QT WAS QUENCHED AND TEMPERED IN ACCORDANCE WITH ASTM A105 HEAT TREATING REQUIREMENTS.
7. ITEM - 12 -THE MATERIAL SUPPLIED WAS NORMALIZED IN ACCORDANCE WITH ASTM A105 HEAT TREATING REQUIREMENTS.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by 
Billie Jo Clemens
Quality Assurance Representative

CMTR: Rev 3