

Material Test Report

Material Test Report#

31426

Date

05/21/2026

Sold To

DNOW LP.

Order#	Line#	Quantity	PO#	Tag#	Batch
2333667	1	7	662980298	COST CENTER 107334	F26DF6

Specifications

Heat Code	Specification	Revision/Year	Description
P26D2	S62 A/SA105N HF	2018	2.06 2K XH RTJ WELDNECK FLANGE 6B 45K TEMP L MC BB PSL1
P26D2	API 6A 45K PSL-1		2.06 2K XH RTJ WELDNECK FLANGE 6B 45K TEMP L MC BB PSL1

Chemical Analysis

Heat Code	CE%	CR%	PM%	CP%	MN%	MO%	NI+CU%	NI%	P%	SI%	S%	V+NB%	V%	AL%
P26D2	0.43	0.2	0.001	0.11	1.12	0.04	0.14	0.04	0.007	0.25	0.012	0.004	0.002	0.029
P26D2	0.43	0.2	0.001	0.11	1.12	0.04		0.04	0.007	0.25	0.012		0.002	0.029
Heat Code	B%	CA%	N%	CU%	NB%	SB%	SN%	AS%	CO%					
P26D2	0.0003	0.001	0.0092	0.1	0.002	0.003	0.007	0.003	0.004					
P26D2	0.0003	0.001	0.0092	0.1	0.002	0.003	0.007	0.003	0.004					

Mechanical Properties

Heat Code	Elong%	HB	R of A	Tensile PSI	Yield PSI
P26D2	35.2	152 / 152	69.6	70600	46100
P26D2	35.2	152 / 152	69.6	70600	46100

Impact Tests


Heat Code	Charpy V Notch	EVM Temp	Lateral Expansion	Shear
P26D2	30 / 45 / 48	-50F	.031 / .043 / .046	10% / 20% / 20%
P26D2	30 / 45 / 48	-50F	.031 / .043 / .046	10% / 20% / 20%

Heat Treatments

Heat Code	Heat Treatment
P26D2	NORMALIZED @ 1650°F FOR 1 HR PER INCH OF THICKNESS AND AIR COOLED.
P26D2	NORMALIZED @ 1650°F FOR 1 HR PER INCH OF THICKNESS AND AIR COOLED.

I HEREBY CERTIFY THAT THE INFORMATION SUPPLIED ABOVE IS TRUE AND CORRECT AND MATCHED THE INFORMATION KEPT IN OUR FILES. THE MATERIAL IS ALSO IN COMPLIANCE WITH ALL APPLICABLE SPECIFICATIONS. ANY ALTERATION IS PUNISHABLE UNDER FEDERAL LAW. DIN 50049 3.1.B EN 10204 3.1 ISO 10474 3.1.B ISO 9001:2015

Approved By
Sam Brown



Material Test Report

Material Test Report#

31426

Date

05/21/2026

Sold To

DNOW L.P.

Order#	Line#	Quantity	PO#	Tag#	Batch
2333667	1	7	662980298	COST CENTER 107334	F26DF6

Supplementals

Heat Code	Supplemental
P26D2	CONFORMS TO NACE MR0175/ISO 15156:2015 & MR0103/ISO 17945:2015. CHARPY V-NOTCH IMPACT RESULTS ARE STATED IN FT. LBS. MELTED & MANUFACTURED IN THE USA. FINE GRAIN PRACTICE. VACUUM DEGASSED. LATERAL EXPANSION IS IN MILS. ELECTRIC ARC FURNACE. LONGITUDINAL DIRECTION FOR CHARPY V-NOTCH IMPACT TESTING.
P26D2	CONFORMS TO NACE MR0175/ISO 15156:2015 & MR0103/ISO 17945:2015. CHARPY V-NOTCH IMPACT RESULTS ARE STATED IN FT. LBS. MELTED & MANUFACTURED IN THE USA. FINE GRAIN PRACTICE. VACUUM DEGASSED. LATERAL EXPANSION IS IN MILS. ELECTRIC ARC FURNACE. LONGITUDINAL DIRECTION FOR CHARPY V-NOTCH IMPACT TESTING.

I HEREBY CERTIFY THAT THE INFORMATION SUPPLIED ABOVE IS TRUE AND CORRECT AND MATCHED THE INFORMATION KEPT IN OUR FILES. THE MATERIAL IS ALSO IN COMPLIANCE WITH ALL APPLICABLE SPECIFICATIONS. ANY ALTERATION IS PUNISHABLE UNDER FEDERAL LAW. DIN 50049 3.1.B EN 10204 3.1 ISO 10474 3.1.B ISO 9001:2015

Approved By
Sam Brown

