

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

1 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert			Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564		Manufacturer's Works Order N°: N/A	
Manufacturing Process: HFW			Product Type: Line Pipe					Surface: Fusion - Bond
Standard or Specification: API 5L 46th Edition					Steel Grade: X52M PSL 2		Ends: Plain End Bevelled	
Dimensions: 12.750 x 0.500 in		Schedule: N/A	Length: Double Random		Quantity:		Nominal Weight: 65.48 LB/FT	

TENSILE TEST

Heat N°	Sample N°	Zone	Lot N°	Specimen condition				Specimen dimensions	Test temp	Y.S.	U.T.S.	Elongation		
				Ls	Sc	Type	Ori			.5% EUL	Req.	Lo	Min.	Obt.
										Min: 52 200	Min: 66 700			
										Max: 76 900	Max: 110 200			
								F	psi	psi	in	%	%	
2136530	185226	E1	2136530	B	AM	Ss	T	1.500	RT	64 808	72 570	2.0	29.0	39.0
2136531	185217	E1	2136531	B	AM	Ss	T	1.500	RT	65 501	73 438	2.0	29.0	39.3
2136532	185215	E1	2136532	B	AM	Ss	T	1.500	RT	66 567	73 808	2.0	29.0	38.7
2237228	185218	E1	2237228	B	AM	Ss	T	1.500	RT	64 907	73 238	2.0	29.0	39.5

AM: As manufactured

B: Body

E1 / E2: Ends of Sampling

Lo: Initial length

Ls: Location of sample

Max: Maximum

Min: Minimum

Obt: Obtained

Ori: Orientation

Req: Required

RT: Room temperature

Sc: Specimen condition

Ss: Strip specimen

T: Transversal

U.T.S: Ultimate tensile strength

Y.S: Yield strength

Heat N°	Sample N°	Zone	Lot N°	Specimen condition				Specimen dimensions	Test temp	U.T.S.
				Ls	Sc	Type	Ori			Req.
										Min: 66 700
								Max: 110 200		
								F	psi	
2136530	185226	E1	2136530	W	AM	Ss	T	1.500	RT	78 657
2136531	185217	E1	2136531	W	AM	Ss	T	1.500	RT	78 178
2136532	185215	E1	2136532	W	AM	Ss	T	1.500	RT	80 712
2237228	185218	E1	2237228	W	AM	Ss	T	1.500	RT	77 194

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

2 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert			Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564		Manufacturer's Works Order N°: N/A		
Manufacturing Process: HFW			Product Type: Line Pipe				Surface: Fusion - Bond		
Standard or Specification: API 5L 46th Edition					Steel Grade: X52M PSL 2		Ends: Plain End Bevelled		
Dimensions: 12.750 x 0.500 in		Schedule: N/A		Length: Double Random		Quantity:		Nominal Weight: 65.48 LB/FT	

TENSILE TEST

AM: As manufactured	Min: Minimum	Sc: Specimen condition	W: Weld
E1 / E2: Ends of Sampling	Ori: Orientation	Ss: Strip specimen	
Ls: Location of sample	Req: Required	T: Transversal	
Max: Maximum	RT: Room temperature	U.T.S: Ultimate tensile strength	

CHEMICAL COMPOSITION

					Composition %																	
					x 1																	
					C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Sn	Nb	V	Ti	Ca	B	N	CE-Pcm
Heat N°	Sample N°	Lot N°	Ls	H	0.22	1.4	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25
				Max Min	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--
				P	0.22	1.4	0.025	0.015	0.45	0.5	0.3	0.3	0.15	--	--	--	--	--	--	0.001	--	0.25
				Max Min	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--
2136530	4098683	2136530	B.M.	H	0.04	1.11	0.011	0.001	0.18	0.08	0.03	0.04	0.01	0.03	0	0.043	0.004	0.013	0.001	0	0.006	0.109
2136531	4098692	2136531	B.M.	H	0.04	1.12	0.012	0.002	0.18	0.11	0.03	0.05	0.01	0.04	0.01	0.041	0.004	0.013	0.001	0	0.006	0.112
2136532	4098684	2136532	B.M.	H	0.04	1.13	0.013	0.002	0.19	0.12	0.03	0.05	0.01	0.03	0.01	0.044	0.004	0.014	0.001	0	0.006	0.113
2237228	4098693	2237228	B.M.	H	0.05	1.11	0.01	0.001	0.19	0.13	0.03	0.04	0.01	0.03	0.01	0.041	0.004	0.012	0.002	0	0.007	0.122
2136530	185194	2136530	B.M.	P	0.038	1.24	0.009	0.001	0.23	0.08	0.02	0.04	0.01	0.036	0.003	0.045	0.004	0.013	0.002	0.001	--	0.12
2136530	185195	2136530	B.M.	P	0.037	1.19	0.009	0.001	0.22	0.08	0.02	0.04	0.01	0.034	0.003	0.042	0.003	0.012	0.002	0.001	--	0.116
2136531	185135	2136531	B.M.	P	0.042	1.21	0.01	0.002	0.22	0.11	0.03	0.05	0.01	0.044	0.004	0.041	0.003	0.013	0.002	0.001	--	0.124
2136531	185136	2136531	B.M.	P	0.041	1.19	0.009	0.001	0.22	0.08	0.03	0.04	0.01	0.034	0.004	0.042	0.003	0.012	0.002	0.001	--	0.12
2136532	185133	2136532	B.M.	P	0.036	1.2	0.011	0.001	0.21	0.12	0.03	0.05	0.01	0.035	0.004	0.042	0.003	0.013	0.002	0.001	--	0.118

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

3 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert			Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564		Manufacturer's Works Order N°: N/A		
Manufacturing Process: HFW			Product Type: Line Pipe				Surface: Fusion - Bond		
Standard or Specification: API 5L 46th Edition					Steel Grade: X52M PSL 2		Ends: Plain End Bevelled		
Dimensions: 12.750 x 0.500 in		Schedule: N/A		Length: Double Random		Quantity:		Nominal Weight: 65.48 LB/FT	

CHEMICAL COMPOSITION

					Composition %																		
					x 1																		
					C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Sn	Nb	V	Ti	Ca	B	N	C-E-Pcm	
Heat N°	Sample N°	Lot N°	Ls	H	Max	0.22	1.4	0.025	0.015	0.45	0.5	0.3	0.3	0.15	—	—	—	—	—	—	0.001	—	0.25
				Min	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Heat N°	Sample N°	Lot N°	Ls	P	Max	0.22	1.4	0.025	0.015	0.45	0.5	0.3	0.3	0.15	—	—	—	—	—	—	0.001	—	0.25
				Min	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
2136532	185134	2136532	B.M.	P		0.041	1.2	0.01	0.001	0.22	0.11	0.03	0.05	0.01	0.039	0.004	0.041	0.003	0.013	0.002	0.001	--	0.123
2237228	185163	2237228	B.M.	P		0.047	1.22	0.009	0	0.23	0.12	0.03	0.04	0.01	0.038	0.004	0.042	0.003	0.013	0.003	0.001	--	0.13
2237228	185164	2237228	B.M.	P		0.044	1.22	0.008	0	0.24	0.12	0.03	0.04	0.01	0.037	0.004	0.042	0.004	0.013	0.004	0.001	--	0.128

B.M: Base metal

H: Heat

Max: Maximum

P: Product

CE-Pcm: CE-Pcm

Ls: Location of sample

Min: Minimum

THROUGH WALL HARDNESS

Required values			Individuals			Average			Hardness type:HRBW		
			Min: -	Max: 94.0	Var: --	Min: --	Max: --	Var: --			
Heat N°	Sample N°	Zone	Lot N°	Pipe N°	Specimen condition			Quad.			Avg.
						Ls	Sc				
2136530	185226	-	2136530	-	B			AM			89.6
2136531	185217	-	2136531	-	B			AM			88.6
2136532	185215	-	2136532	-	B			AM			88.9
2237228	185218	-	2237228	-	B			AM			84.4

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

4 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert			Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564		Manufacturer's Works Order N°: N/A			
Manufacturing Process: HFW			Product Type: Line Pipe					Surface: Fusion - Bond		
Standard or Specification: API 5L 46th Edition					Steel Grade: X52M PSL 2			Ends: Plain End Bevelled		
Dimensions: 12.750 x 0.500 in		Schedule: N/A		Length: Double Random		Quantity:			Nominal Weight: 65.48 LB/FT	

THROUGH WALL HARDNESS

AM: As manufactured

Ls: Location of sample

Quad: Quadrant

Avg: Average

Max: Maximum

Sc: Specimen condition

B: Body

Min: Minimum

Var: Variation

IMPACT TEST

Type: Charpy V			Orientation: T				Unit: ft.lb				Shear area %			
Position:			Temp: 32		Unit: F		Ind.Min.Req: 11		Req.Min.Avg: 15		Ind.Min.Req: -		Req.Min.Avg: -	
Heat N°	Sample N°	Lot N°	Ls	Sc	T.T F	Size	Results				Results			
						-	1	2	3	Avg.	1	2	3	Avg.
2136530	185226	2136530	B	AM	32	3/4	188	198	198	195	100	100	100	100
2136531	185217	2136531	B	AM	32	3/4	198	191	185	191	100	100	100	100
2136532	185215	2136532	B	AM	32	3/4	201	199	195	198	100	100	100	100
2237228	185218	2237228	B	AM	32	3/4	197	196	197	197	100	100	100	100

AM: As manufactured

Ind. Min. Req: Individual Minimum Required

Sc: Specimen condition

Avg: Average

Ls: Location of sample

T.T: Test temperature

B: Body

Req. Min. Avg: Required minimum average

Temp: Temperature

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

5 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert		Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564	Manufacturer's Works Order N°: N/A
Manufacturing Process: HFW		Product Type: Line Pipe			Surface: Fusion - Bond
Standard or Specification: API 5L 46th Edition			Steel Grade: X52M PSL 2		Ends: Plain End Bevelled
Dimensions: 12.750 x 0.500 in	Schedule: N/A	Length: Double Random		Quantity:	Nominal Weight: 65.48 LB/FT

FLATTENING TEST

Standard:				Standard:				Standard:				Standard:			
Heat N°	Lot N°	Sample N°	Result	Heat N°	Lot N°	Sample N°	Result	Heat N°	Lot N°	Sample N°	Result	Heat N°	Lot N°	Sample N°	Result
2136530	2136530	185226	Good	2136531	2136531	185217	Good	2136532	2136532	185215	Good	2237228	2237228	185218	Good

HYDROSTATIC TEST

Pressure		Time	Results
Unit	Value	Seconds	
psi	2,970	5	Satisfactory

SUPPLEMENTARY INFORMATION

Supplementary Information	Supplementary Information
This material has been manufactured, sampled, tested and inspected in accordance with this specification and has been found to meet the requirements called for by the above order. This product is silicon and/or aluminum fully killed. NDT OK; Longitudinal UT with ID/OD N-10 Notches (2.0" L x .040" W) verified by 1/8" FDH	COMPLIANT TO ASTM A53-18 GRADE B AND ASME SA53 GRADE B Material meets the maximum hardness requirement of section A.2.1.2 of NACE MRO 175 BODY TENSILE SOURCED 180° FROM WELD LINE; CVN SAMPLES SOURCED 90° FROM WELD LINE; CVN SAMPLES TESTED BY 8mm STRIKER

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.

**MAVERICK TUBE CORPORATION**

Hickman Plant
5020 N COUNTY RD 967
BLYTHEVILLE, AR 72315
(870) 776-5000 tel
(870) 776-5008 fax

MILL TEST CERTIFICATE

Number:

9900901.0.9

Page:

6 / 6Date: **January 03, 2024**

Customer: Edgen, Summary Cert		Customer's Order Item: 9900901/SO/90		Customer's Reference: 301564	Manufacturer's Works Order N°: N/A
Manufacturing Process: HFW		Product Type: Line Pipe			Surface: Fusion - Bond
Standard or Specification: API 5L 46th Edition			Steel Grade: X52M PSL 2		Ends: Plain End Bevelled
Dimensions: 12.750 x 0.500 in	Schedule: N/A	Length: Double Random		Quantity:	Nominal Weight: 65.48 LB/FT

SUPPLEMENTARY INFORMATION

Heat Treatment

The minimum weld seam heat treatment temperature is 1650F.

Steel Vendor Name and Manufactured

2136530,NUCOR STEEL HICKMAN,ARMOREL,AR,Melted and Manufactured in USA
2136531,NUCOR STEEL HICKMAN,ARMOREL,AR,Melted and Manufactured in USA

Steel Vendor Name and Manufactured

2136532,NUCOR STEEL HICKMAN,ARMOREL,AR,Melted and Manufactured in USA
2237228,NUCOR STEEL HICKMAN,ARMOREL,AR,Melted and Manufactured in USA

The product certified herein has been manufactured, sampled, tested and inspected in accordance with the stated specifications and has been found to meet the requirements.
This certificate is not a declaration of origin nor may it be used as a declaration of origin.

CUSTOMER . THIRD PARTY

INSPECTION COMPANY
COMPAÑIA DE INSPECCIÓN

Company Name: N/A
Employee Name: N/A

TENARIS QUALITY DEPARTMENT SIGNATURE

QUALITY CERTIFICATION DEPT.

MCCORMICK Billy

CHIEF OF QUALITY CERTIFICATION DEPT.

Renato AVILA

This certificate is issued by a computerized system and it is valid with electronic signature. On the original certificate the trade-mark green colored "Tenaris" is stamped. In case the owner of the original certificate would release a copy of it, he must attest its conformity to the original one taking upon himself the responsibility for any unlawful or not allowed use. Any alteration and/or falsification will be subjected to the law.