

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428 Page 1 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
6	25	J236	1/2 3000 A105 COUP T	SA/A105
Al 0.019 C 0.190 Co 0.010 Cr 0.110 Cu 0.100 Mn 0.990 Mo 0.010 Nb 0.002				
Ni 0.040 P 0.009 S 0.019 Si 0.200 V 0.002				
CE(Long Formula) = 0.39				
T/S(PSI) 74,900 Y/S(PSI) 50,000 EL(%) 32.00 RA(%) 67.00				
Brinell Hardness 155 BHN 163 BHN				
Country Of Origin (Melt): UNITED STATES				
7	25	J176	1/2X 1/4 3M/6M A105 HXBU T	SA/A105
Al 0.024 C 0.160 Cb 0.000 Co 0.000 Cr 0.080 Cu 0.080 Mn 0.630 Mo 0.010				
Ni 0.040 P 0.005 S 0.001 Si 0.240 Sn 0.005 V 0.002				
CE(Long Formula) = 0.29				
T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00				
Brinell Hardness 141 BHN 185 BHN				
Country Of Origin (Melt): UNITED STATES				
9	75	J216	1 X 1/2 3M/6M A105 HXBU T	SA/A105
Al 0.023 C 0.200 Co 0.003 Cr 0.120 Cu 0.040 Mn 1.060 Mo 0.004 Nb 0.010				
Ni 0.020 P 0.006 S 0.024 Si 0.190 V 0.003				
CE(Long Formula) = 0.41				
T/S(PSI) 79,800 Y/S(PSI) 49,400 EL(%) 30.00 RA(%) 56.60				
Brinell Hardness 162 BHN 161 BHN				
Country Of Origin (Melt): CANADA				
10	50	J186	11/2X 1 3M/6M A105 HXBU T	SA/A105
Al 0.025 C 0.190 Co 0.004 Cr 0.110 Cu 0.080 Mn 1.060 Mo 0.008 Nb 0.012				
Ni 0.030 P 0.006 S 0.017 Si 0.230 V 0.003				
CE(Long Formula) = 0.40				
T/S(PSI) 84,800 Y/S(PSI) 55,900 EL(%) 27.50 RA(%) 52.00				
Brinell Hardness 156 BHN 157 BHN				
Country Of Origin (Melt): CANADA				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.


by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

CERTIFIED MILL TEST REPORT



LOG NO. F00000000232428

Page 2 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
11	25	J244	2 X 1/2 3M/6M A105 HXBU T	SA/A105
Al 0.019 C 0.190 Co 0.010 Cr 0.120 Cu 0.120 Mn 0.980 Mo 0.020 Nb 0.002				
Ni 0.050 P 0.011 S 0.019 Si 0.230 V 0.002				
CE(Long Formula) = 0.39				
T/S(PSI) 74,800 Y/S(PSI) 43,000 EL(%) 33.00 RA(%) 66.00				
Brinell Hardness 150 BHN 155 BHN				
Country Of Origin (Melt): UNITED STATES				
12	75	J279	2 X 1 3M/6M A105 HXBU T	SA/A105
Al 0.031 C 0.180 Cb 0.003 Co 0.005 Cr 0.150 Cu 0.260 Mn 0.990 Mo 0.010				
Ni 0.070 P 0.009 S 0.025 Si 0.221 V 0.023				
CE(Long Formula) = 0.40				
T/S(PSI) 78,700 Y/S(PSI) 51,800 EL(%) 25.00 RA(%) 56.00				
Brinell Hardness 161 BHN 161 BHN				
Country Of Origin (Melt): UNITED STATES				
13	25	J125	1/4 3M/6M A105 HXPL T	SA/A105
C 0.170 Cb 0.000 Co 0.000 Cr 0.100 Cu 0.160 Mn 0.740 Mo 0.010 Ni 0.060				
P 0.009 S 0.014 Si 0.190 V 0.003				
CE(Long Formula) = 0.33				
T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00				
Brinell Hardness 150 BHN 159 BHN				
14	50	J229	1/2 3M/6M A105 HXPL T	SA/A105
C 0.160 Cr 0.080 Cu 0.080 Mn 0.730 Mo 0.020 Ni 0.050 P 0.007 S 0.002				
Si 0.180 V 0.002				
CE(Long Formula) = 0.31				
T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00				
Brinell Hardness 141 BHN 156 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens
Quality Assurance Representative

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 3 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
15	400	J305	1 3M/6M A105 HXPL T	SA/A105
Al 0.028 C 0.200 Cb 0.001 Co 0.000 Cr 0.060 Cu 0.070 Mn 0.930 Mo 0.010				
Ni 0.030 P 0.008 S 0.003 Si 0.200 Sn 0.005 V 0.002				
CE(Long Formula) = 0.38				
T/S(PSI) 71,500 Y/S(PSI) 61,000 EL(%) 27.00 RA(%) 69.00				
Brinell Hardness 137 BHN 185 BHN				
Country Of Origin (Melt): UNITED STATES				
16	75	J263	1/2 3M/6M A105 RDPL T	SA/A105
Al 0.023 C 0.190 Co 0.010 Cr 0.110 Cu 0.120 Mn 0.980 Mo 0.020 Nb 0.001				
Ni 0.050 P 0.008 S 0.018 Si 0.200 V 0.003				
CE(Long Formula) = 0.39				
T/S(PSI) 76,400 Y/S(PSI) 51,000 EL(%) 33.00 RA(%) 70.00				
Brinell Hardness 149 BHN 156 BHN				
Country Of Origin (Melt): UNITED STATES				
17	25	J295	3/4 3M/6M A105 SQPL T	SA/A105
C 0.160 Cb 0.000 Co 0.000 Cr 0.060 Cu 0.070 Mn 0.740 Mo 0.020 Ni 0.040				
P 0.008 S 0.002 Si 0.170 V 0.002				
CE(Long Formula) = 0.31				
T/S(PSI) 0 Y/S(PSI) 0 EL(%) 0.00 RA(%) 0.00				
Brinell Hardness 165 BHN 153 BHN				
Country Of Origin (Melt): UNITED STATES				
18	25	J174	11/4 3M/6M A105 SQPL T	SA/A105
Al 0.033 C 0.200 Co 0.005 Cr 0.150 Cu 0.260 Mn 0.980 Mo 0.020 Nb 0.004				
Ni 0.060 P 0.008 S 0.025 Si 0.221 V 0.020				
CE(Long Formula) = 0.42				
T/S(PSI) 76,400 Y/S(PSI) 52,000 EL(%) 50.00 RA(%) 53.00				
Brinell Hardness 165 BHN 163 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 4 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
19	25	52180	1/2 3000 A105 TEE T	SA/A105
Al 0.031 C 0.200 Co 0.005 Cr 0.090 Cu 0.260 Mn 0.970 Mo 0.020 Nb 0.005				
Ni 0.080 P 0.007 S 0.023 Si 0.245 V 0.021				
CE(Long Formula) = 0.41				
T/S(PSI) 80,711 Y/S(PSI) 52,025 EL(%) 31.85 RA(%) 60.01				
Brinell Hardness 147 BHN 147 BHN				
Country Of Origin (Melt): UNITED STATES				
20	120	52182	1 3000 A105 TEE T	SA/A105
Al 0.023 C 0.200 Co 0.003 Cr 0.120 Cu 0.040 Mn 1.040 Mo 0.003 Nb 0.009				
Ni 0.010 P 0.005 S 0.021 Si 0.220 V 0.003				
CE(Long Formula) = 0.40				
T/S(PSI) 77,623 Y/S(PSI) 49,391 EL(%) 33.10 RA(%) 60.01				
Brinell Hardness 141 BHN 139 BHN				
Country Of Origin (Melt): CANADA				
22	75	52111	1 3000 A105 90EL S	SA/A105
Al 0.018 C 0.190 Co 0.005 Cr 0.130 Cu 0.250 Mn 0.970 Mo 0.020 Nb 0.004				
Ni 0.070 P 0.007 S 0.024 Si 0.217 V 0.021				
CE(Long Formula) = 0.41				
T/S(PSI) 82,990 Y/S(PSI) 54,733 EL(%) 32.00 RA(%) 59.91				
Brinell Hardness 153 BHN 159 BHN				
Country Of Origin (Melt): UNITED STATES				
24	25	D993	1 3000 A105 COUP S	SA/A105
Al 0.029 C 0.180 Co 0.006 Cr 0.070 Cu 0.260 Mn 1.040 Mo 0.020 Nb 0.001				
Ni 0.080 P 0.004 S 0.025 Si 0.215 V 0.025				
CE(Long Formula) = 0.40				
T/S(PSI) 73,500 Y/S(PSI) 49,600 EL(%) 32.00 RA(%) 38.00				
Brinell Hardness 163 BHN 163 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens
Quality Assurance Representative

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 5 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
25	25	52256	1/2 6000 A105 TEE T	SA/A105
Al 0.040 C 0.190 Co 0.005 Cr 0.110 Cu 0.220 Mn 0.970 Mo 0.020 Nb 0.001				
Ni 0.070 P 0.007 S 0.023 Si 0.224 V 0.024				
CE(Long Formula) = 0.40				
T/S(PSI) 81,824 Y/S(PSI) 53,109 EL(%) 29.95 RA(%) 52.16				
Brinell Hardness 156 BHN 156 BHN				
Country Of Origin (Melt): UNITED STATES				
26	15	52010	1 6000 A105 TEE T	SA/A105
Al 0.032 C 0.200 Co 0.002 Cr 0.090 Cu 0.040 Mn 1.040 Mo 0.016 Nb 0.009				
Ni 0.020 P 0.005 S 0.024 Si 0.240 V 0.003				
CE(Long Formula) = 0.40				
T/S(PSI) 80,101 Y/S(PSI) 52,396 EL(%) 33.90 RA(%) 61.19				
Brinell Hardness 156 BHN 153 BHN				
Country Of Origin (Melt): CANADA				
		52268	1 6000 A105 TEE T	SA/A105
Al 0.035 C 0.200 Co 0.005 Cr 0.100 Cu 0.230 Mn 0.970 Mo 0.020 Nb 0.001				
Ni 0.070 P 0.005 S 0.025 Si 0.210 V 0.023				
CE(Long Formula) = 0.41				
T/S(PSI) 79,171 Y/S(PSI) 51,251 EL(%) 32.80 RA(%) 61.49				
Brinell Hardness 153 BHN 153 BHN				
Country Of Origin (Melt): UNITED STATES				
27	15	52179	2 6000 A105 TEE T	SA/A105
Al 0.026 C 0.170 Co 0.003 Cr 0.110 Cu 0.120 Mn 1.100 Mo 0.020				
Ni 0.050 P 0.008 S 0.015 Si 0.260 V 0.034				
CE(Long Formula) = 0.40				
T/S(PSI) 81,413 Y/S(PSI) 55,059 EL(%) 31.90 RA(%) 65.12				
Brinell Hardness 147 BHN 141 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

Heat J305

Desc Forged Hex Plug ASTM A/SA105 NPT Threaded, 1"

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 6 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2

HOUSTON TX 77049

United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
31	150	52205	36-3X1 3000 A105 FLEX T	SA/A105
Al 0.020 C 0.200 Co 0.003 Cr 0.120 Cu 0.030 Mn 1.050 Mo 0.000 Nb 0.009				
Ni 0.010 P 0.006 S 0.022 Si 0.220 V 0.004				
CE(Long Formula) = 0.40				
T/S(PSI) 81,115 Y/S(PSI) 53,860 EL(%) 31.30 RA(%) 60.19				
Brinell Hardness 156 BHN 159 BHN				
Country Of Origin (Melt): CANADA				
32	50	52141	36-8 X 2 3000 A105 FLEX T	SA/A105
Al 0.027 C 0.200 Co 0.002 Cr 0.110 Cu 0.030 Mn 1.060 Mo 0.002 Nb 0.011				
Ni 0.010 P 0.005 S 0.020 Si 0.200 V 0.003				
CE(Long Formula) = 0.40				
T/S(PSI) 78,399 Y/S(PSI) 49,733 EL(%) 33.85 RA(%) 57.47				
Brinell Hardness 144 BHN 144 BHN				
Country Of Origin (Melt): CANADA				
33	10	52063	14-6X3 3000 A105 FLEX T	SA/A105
Al 0.040 C 0.200 Co 0.005 Cr 0.160 Cu 0.220 Mn 0.990 Mo 0.010 Nb 0.002				
Ni 0.060 P 0.009 S 0.018 Si 0.266 V 0.025				
CE(Long Formula) = 0.42				
T/S(PSI) 77,275 Y/S(PSI) 51,807 EL(%) 33.75 RA(%) 64.33				
Brinell Hardness 144 BHN 144 BHN				
Country Of Origin (Melt): UNITED STATES				
34	10	52069	36-16X3 3000 A105 FLEX T	SA/A105
Al 0.038 C 0.190 Co 0.005 Cr 0.110 Cu 0.240 Mn 0.980 Mo 0.010 Nb 0.002				
Ni 0.060 P 0.005 S 0.025 Si 0.233 V 0.024				
CE(Long Formula) = 0.40				
T/S(PSI) 80,398 Y/S(PSI) 52,177 EL(%) 33.10 RA(%) 58.25				
Brinell Hardness 147 BHN 147 BHN				
Country Of Origin (Melt): UNITED STATES				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Quality Assurance Representative

CMTR: Rev 3

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 7 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906
www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE 11/17/2025

CUSTOMER

BONNEY ORDER NO. B000373693

ORDER NO.: RMS-323234

SHIP TO: EDGEN MURRAY CORPORATION

8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	
			CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:	
35	100	52204	36-11/2 X 3/4 6000 A105 FLEX T	SA/A105
Al 0.023 C 0.190 Co 0.003 Cr 0.100 Cu 0.040 Mn 1.040 Mo 0.014 Nb 0.011 Ni 0.030 P 0.005 S 0.020 Si 0.190 V 0.003 CE(Long Formula) = 0.39 T/S(Psi) 77,442 Y/S(Psi) 52,239 EL(%) 30.50 RA(%) 63.28 Brinell Hardness 150 BHN 150 BHN Country Of Origin (Melt): CANADA				
36	25	52184	36-3 X 1 6000 A105 FLEX T	SA/A105
Al 0.023 C 0.190 Co 0.010 Cr 0.130 Cu 0.120 Mn 0.980 Mo 0.020 Nb 0.001 Ni 0.050 P 0.010 S 0.017 Si 0.200 V 0.003 CE(Long Formula) = 0.40 T/S(Psi) 76,265 Y/S(Psi) 47,874 EL(%) 33.10 RA(%) 62.99 Brinell Hardness 144 BHN 141 BHN Country Of Origin (Melt): UNITED STATES				
37	15	52168	36-8X2 6000 A105 FLEX T	SA/A105
Al 0.023 C 0.190 Co 0.010 Cr 0.130 Cu 0.090 Mn 0.990 Mo 0.030 Nb 0.001 Ni 0.040 P 0.011 S 0.022 Si 0.220 V 0.004 CE(Long Formula) = 0.40 T/S(Psi) 72,070 Y/S(Psi) 43,968 EL(%) 33.60 RA(%) 64.19 Brinell Hardness 137 BHN 137 BHN Country Of Origin (Melt): UNITED STATES				
38	25	52151	36-8X2 STD A105 FLEX B	SA/A105
Al 0.021 C 0.200 Co 0.003 Cr 0.130 Cu 0.060 Mn 1.050 Mo 0.002 Nb 0.009 Ni 0.020 P 0.006 S 0.018 Si 0.250 V 0.003 CE(Long Formula) = 0.41 T/S(Psi) 79,462 Y/S(Psi) 51,412 EL(%) 32.25 RA(%) 61.77 Brinell Hardness 153 BHN 150 BHN Country Of Origin (Melt): CANADA				

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

Desc Forged Hex Plug ASTM A/SA105 NPT Threaded, 1"

CERTIFIED MILL TEST REPORT



The Best Value -
Price, Quality, Service
All The Time.

LOG NO. F00000000232428

Page 8 of 8

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: EDGEN MURRAY CORPORATION

DATE: 11/17/2025

CUSTOMER

ORDER NO.: RMS-323234

BONNEY ORDER NO. B000373693

SHIP TO: EDGEN MURRAY CORPORATION
8445 MILLER RD 2
HOUSTON TX 77049
United States

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
39	50	52151	36-8X2 XS A105 FLEX B SA/A105 Al 0.021 C 0.200 Co 0.003 Cr 0.130 Cu 0.060 Mn 1.050 Mo 0.002 Nb 0.009 Ni 0.020 P 0.006 S 0.018 Si 0.250 V 0.003 CE(Long Formula) = 0.41 T/S(Psi) 79,462 Y/S(Psi) 51,412 EL(%) 32.25 RA(%) 61.77 Brinell Hardness 153 BHN 150 BHN Country Of Origin (Melt): CANADA

1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2 - 2015 EDITION.
3. CERTIFYING ASTM A105-24 / ASME SA105-23 EDITION.
4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
5. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.
6. ITEM - 7, 13, 14, 17 -THE MATERIAL SUPPLIED IDENTIFIED AS SA/A105-QT WAS QUENCHED AND TEMPERED IN ACCORDANCE WITH ASTM A105 HEAT TREATING REQUIREMENTS.
7. ITEM - 15-THE MATERIAL SUPPLIED WAS NORMALIZED IN ACCORDANCE WITH ASTM A105 HEAT TREATING REQUIREMENTS.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Billie Jo Clemens

Billie Jo Clemens

Quality Assurance Representative

CMTR: Rev 3