



KERKAU
MANUFACTURING

Flanges-Precision Machining

1321 Valley Center Dr.
Bay City, MI 48706

Phone (989) 686-0350
Toll Free (800) 248-5060
Fax (989) 686-0399

Material Test Report

Date: 05/19/2026

Sold To: DNOW - MT.PLEASANT
P.O. BOX 40985

Ship To: DNOW-MT PLEASANT
1701 GOVER PKWY

USA

USA

Order No: 0796080

Ship Instructions:

PO No: 662980292

Item Description

2 X .75 1500# THR RF A105 W/NO HUB ASTM A105/A105M-24/ASME
SA105/SA105M-24 NORMALIZED

Lot No.

LD4

C%	Mn%	P%	S%	Si%	Cr%	Cu%	Ni%	Mo%	V%	Cb%	Al%	Ti%	B%
0.19000	1.02000	0.01000	0.02000	0.21000	0.07000	0.29000	0.09000	0.02000	0	0.00100	0.00200	0.00100	0.0003
Tensile (PSI)		Yield (PSI)		Elong %		Reduction %		Brinell		Rockwell		CE	
80,800		50,000		31		53		149-149				.403	
Grain Size		Test Size		Impact		Charpy		Shear		Lateral Exp.			
		.492		//				//		//			

"THE RECORDING OF FALSE, FICTITIOUS, OR FRAUDULENT STATEMENT OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE."

DIN 50049/EN 10204:2004 /ISO 10474 3.1.B

NACE MR0175/ISO 15156-2 2015 NACE MR0103/ISO 17945 2015

NO WELD REPAIR/MERCURY FREE. FINE GRAIN PRACTICE.

ELONGATION FROM A ROUND SPECIMEN. FULLY KILLED.

YIELD STRENGTH WAS DETERMINED USING THE 0.2% OFFSET METHOD.

NORMALIZED @ 1675°F 4 HRS, AIR COOLED.

THIS IS A DIGITALLY CREATED DOCUMENT

(H) is Heat Analysis and (P) is Product Analysis

Justin Plowdrey

Justin Plowdrey / QA MANAGER