



CERTIFICATE OF ANALYSIS

SPEC-R3 Revision A

SUPPLIER	SUP-WEST · Western Polymers	SITE	SITE-W1
LOT	LOT-1003	PURCHASE ORDER	PO-86
MATERIAL	MAT-RESIN-3 — Resin 3	QUANTITY	200 kg
DATE OF MANUFACTURE	2026-02-20	DATE OF RECEIPT	2026-03-08
SPECIFICATION	SPEC-R3 Revision A		

VISCOSITY DETERMINATION · TWO METHODS REPORTED

Requirement REQ-R3-A-1 · 200.0–400.0 cP (ASTM-D2196, 25 °C)

DIRECT METHOD		ALTERNATE METHOD	
viscosity: 178 cP (ASTM-D2196, 25C)		viscosity: 312 cP (ASTM-D445, 25C)	
METHOD	CONDITION	METHOD	CONDITION
ASTM-D2196	25 °C	ASTM-D445	25 °C

METHOD NOTE

Rotational viscometry (ASTM-D2196) and kinematic viscosity (ASTM-D445) were both performed at 25 °C on the retained sample.

Results conform to SPEC-R3 Revision A.

ANALYST · LM

QA APPROVED

